- Description
- Specification
- Reviews (0)

Polyamide-imide / PAI sheets

Polyamideimides (PAI) has a very high mechanical strength and hardness at low temperatures and under very high. Polyamideimides (PAI) have stability temperature of the mold and a glass transition temperature (+ 280 ° C).

The PAI polymer sheets will not change its properties even at the highest possible operating temperature, and the Polyamideimide parts will work flawlessly even under excessive heat.

Polyamide-imide / PAI is used for manufacturing of:

- Moving parts, track rollers, bearings, gears, bearing washers (axial bearings) in the production of gearboxes, hydraulic controllers balls.
- Bushings, vanes, seals, jacks and panels, electrical components and bushings, gears, plugs,
- connectors, parts of pneumatic and hydraulic pumps, seals, valves, components for cryogenic technology,
- housing, items furnaces conveyors, hydraulic valves, air grilles, security features
- clutch seals bearing and sliding bearing portion. It can be glass-reinforced, high quality and stable.
- PAI - polyamide-imide is used for runners, guide rollers for the paper in printers, copiers, office equipment.
- Details plugs and test sockets for testing chips in the microelectronic industry, lamp holders.

Mechanical Properties

MECHANICAL PROPERTIES	VALUE	UNIT	PARAMETER	NORM
Impact strength (Charpy)	81	kJ/m2	max. 7,5J	DIN EN ISO 179-1eU
Shore hardness	85	-	D scale	DIN EN ISO 868
Compression strength	12/32/90	MPa	1% / 2% / 5%	EN ISO 604
Modulus of elasticity (tensile test)	3600	MPa	1 mm/min	DIN EN ISO 527-2
Tensile strength at break	122	MPa	5mm/min	DIN EN ISO 527-2
Modulus of elasticity (flexural test)	3600	MPa	2mm/min, 10 N	DIN EN ISO 178
Elongation at break	8	%	5mm/min	DIN EN ISO 527-2
Flexural strength	173	MPa	2mm/min, 10 N	DIN EN ISO 178
Ball indentation hardness	221	MPa		ISO 2039-1

Thermal Properties

THERMAL PROPERTIES	VALUE	UNIT	PARAMETER	NORM
Thermal expansion (CLTE)	4,2	10-5*1/K	23-60°C, longitudinal	DIN EN ISO 11359-1;2

THERMAL PROPERTIES	VALUE	UNIT	PARAMETER	NORM
Glass transition temperature	285	C		DIN EN ISO 11357
Thermal expansion (CLTE)	4,2	10-5*1/K	23-100°C, longitudinal	DIN EN ISO 11359-1;2

Electrical Properties

ELECTRICAL PROPERTIES	VALUE	UNIT	PARAMETER	NORM
Dielectric constant	3,5	-	@ 1 MHz	DIN 53 481
Dielectric constant	3,8	-	@ 100 Hz	DIN 53 481
Dissipation factor	0,019	Ω/sq	@ 1 MHz	DIN 53 481
Dielectric strength	26	kV/mm		ISO 60243-1
Dissipation factor	0,0055	%	@ 100 Hz	DIN 53 481

Other Properties

OTHER PROPERTIES	VALUE	UNIT	PARAMETER	NORM
Flammability (UL94)	V0	-	3,2 mm	-
Moisture absorption	0,4 / 0,57	%	24h / 96h (23°C)	DIN EN ISO 62

General specification	
Applications:	• General Industries • Connectors, switches, relays, thrust washers, • spline liners, valve seats, check balls, poppets, • mechanical linkages, bushings, • wear rings, Insulators, cams, picker fingers, ball bearings, rollers, and thermal insulators
Temperature resistance °C	220 °C
Weight:	1.38 g/cm^3

General specification

Technical datasheet	[Polyamide-imide sheets - TDS]

There are no reviews for this product.

Write a review

* **Your Name**

* **Your Review**

Note: HTML is not translated!

* **Rating** Bad Good

Continue

Polyamide-imide/ PAI sheets

- Brand: GTeek
- Product Code: Polyamide-imide / PAI sheetings
- Availability: On stock

Available Options

* **Gasket sheet thickness**

- 1 mm
- 1.5 mm
- 2.0 mm
- 3.0 mm
- 4.0 mm
- 5.0 mm
- 6.0 mm

* **Sheet Size**

- 1000x1000 mm
- 1200x1200 mm
- 1500x1500 mm

Qty 1

Send Inquiry

0 reviews / Write a review

Tags: Polyamide-imide, PAI, sheets

Information

- About Us
- History
- General T&C
- Privacy Policy
- GDPR
- info@gteek.com

Customer Service

- Contact Us
- Returns
- Site Map

Extras

- Brands
- Clients
- Useful Resources

My Account

- My Account
-