

SS 465 data from harshsteel

REFERENCE LINK

<http://www.harshsteel.com/stainless-steel-465.html>

Typical Mechanical Properties

Material	Condition	Orientation	0.2 % Yield Strength (Mpa)	Ultimate Tensile Strength (Mpa)	% Elongation in 4D	% Reduction of Area	Notch Tensile Strength	NTS/UTS	Charpy V Notch Impact	Rockwell C Hardness
Alloy 465 Bar 3" to 9" Round Custom 465®	H950	Long	1655	1765	12	57	2475	1.40	16	49.5
Alloy 465 Bar 3" to 9" Round Custom 465®	H950	Trans	1648	1765	11	49	2386	1.35	13	49.5
Alloy 465 Bar 3" to 9" Round Custom 465®	H1000	Long	1496	1593	14	63	2427	1.52	35	47.5
Alloy 465 Bar 3" to 9" Round Custom 465®	H1000	Trans	1503	1600	13	57	2392	1.50	28	47.5

Specifications