

DATA POINTS FOR SS 465 1025 CONDITION

REFERENCE LINK

<https://f.hubspotusercontent20.net/hubfs/7407324/Material%20Safety%20Data%20Sheets/Custom%20465.pdf>

500 F (482 C) Age											
-------------------	--	--	--	--	--	--	--	--	--	--	--

Typical Room Temperature Mechanical Properties – Custom 465® Stainless

4-1/2" x 1-1/2" and 4-1/2" x 2-3/4" Forged Bars

Condition	Orientation	0.2% Yield Strength		Ultimate Tensile Strength		% Elong. in 4D	% Reduction of Area	NTS ^a		NTS/UTS	Hardness (HRC)
		ksi	MPa	ksi	MPa			ksi	MPa		
Annealed/CT	L	99	683	138	951	20	80	--	--	--	28
H950	L	235	1620	254	1751	14	63	362	2496	1.43	49
	T	230	1586	250	1724	12	53	355	2448	1.42	
H1000	L	217	1496	231	1593	15	65	352	2427	1.52	47
	T	211	1455	227	1565	15	61	349	2406	1.54	
H1025	L	204	1407	218	1503	17	65	343	2365	1.57	46
	T	204	1407	218	1503	16	61	341	2351	1.56	
H1050	L	198	1365	215	1482	18	67	326	2248	1.52	45
	T	196	1351	213	1469	17	63	324	2234	1.52	
H1075	L	179	1234	203	1400	20	69	313	2158	1.54	43
	T	180	1241	202	1393	19	67	309	2130	1.53	
H1100	L	159	1096	190	1310	22	71	280	1931	1.47	40
	T	158	1089	190	1310	21	65	278	1917	1.46	
H1150	L	98	676	170	1172	24	72	243	1675	1.43	36
	T	104	717	172	1186	22	66	241	1662	1.40	--
H1150M	L	77	531	156	1076	25	72	223	1538	1.43	30
	T	78	538	159	1096	22	62	221	1524	1.39	--

^aNotch tensile strength with $K_t = 10$