

DATA POINTS OF SS 465 FOR CONDITION H1025,H1050

REFERENCE LINKS

<https://www.carpentertechnology.com/hubfs/7407324/Material%20Safety%20Data%20Sheets/Custom%20465.pdf>

Effects of Exposure at Elevated Temperatures on Room Temperature Mechanical Properties—Custom 465 Stainless Bar*

Thermal Stability, 10" Diameter Bar

Condition	0.2% Yield Strength		Ultimate Tensile Strength		% Elongation in 4D	% Reduction of Area	Notch Tensile Strength**		Charpy V-Notch Impact		Hardness (HRC)
	ksi	MPa	ksi	MPa			ksi	MPa	ft-lbs	J	
H1025	214	1475	227	1565	15	67	353	2434	36	49	47
H1025 + 600°F (316°C), 1000 hrs, AC	217	1496	230	1586	15	68	353	2434	32	43	47
H1025 + 700°F (371°C), 1000 hrs, AC	224	1544	235	1620	15	68	349	2406	23	31	48
H1025 + 800°F (427°C), 1000 hrs, AC	231	1593	244	1682	14	63	344	2372	13	18	49
H1025 + 900°F (482°C), 1000 hrs, AC	219	1510	232	1600	16	66	331	2282	25	34	48
H1050	205	1413	220	1517	17	66	336	2317	43	58	46
H1050 + 600°F (316°C), 1000 hrs, AC	205	1413	220	1517	17	68	337	2324	39	53	46
H1050 + 700°F (371°C), 1000 hrs, AC	210	1448	225	1551	17	66	338	2330	28	38	47
H1050 + 800°F (427°C), 1000 hrs, AC	221	1524	234	1613	15	60	334	2303	18	24	48
H1050 + 900°F (482°C), 1000 hrs, AC	206	1420	221	1524	17	65	322	2220	30	41	46.5