

Table 2 — Typical room temperature mechanical properties of Custom 465 stainless

Condition/ Hardness, HRC	Longitudinal Transverse	0.2% yield strength, MPa (ksi)	Ultimate tensile strength, MPa (ksi)	Elongation in 4D, %	Reduction in area, %	Notch tensile strength,* MPa (ksi)	NTS/ UTS
H900/ 50	L	1640 (238)	1772 (257)	13	58	2413 (350)	1.36
	T	1613 (234)	1772 (257)	12	52	2330 (338)	1.32
H950/ 49	L	1620 (235)	1751 (254)	14	63	2496 (362)	1.43
	T	1585 (230)	1724 (250)	12	53	2448 (355)	1.42
H1000/ 47	L	1496 (217)	1593 (231)	15	65	2427 (352)	1.52
	T	1455 (211)	1565 (227)	15	61	2406 (349)	1.54
H1050/ 45	L	1365 (198)	1482 (215)	18	67	2248 (325)	1.52
	T	1351 (196)	1468 (213)	17	63	2234 (324)	1.52

*Notch tensile strength with $K_t = 10$. Forged bars 4.5x1.5 in. and 4.5x2.75 in.