

Condition	Longitudinal Transverse	0.2% Yield Strength, MPa (ksi)	Ultimate tensile strength, MPa (ksi)	Elongation in 4D, %	Reduction in area, %	Notch tensile strength, * MPa	NTS/UTS
H950	L	1620 (235)	1751 (254)	14	65	2496 (362)	1.43
	T	1585 (230)	1724 (250)	12	53	2448 (355)	1.42
H1000	L	1496 (217)	1594 (231)	15	65	2427 (352)	1.52
	T	1455 (211)	1565 (227)	13	61	2406 (349)	1.54
H1050	L	1365 (198)	1482 (215)	18	67	2248 (326)	1.52
	T	1351 (196)	1468 (213)	17	63	2234 (324)	1.52