

SS 465 YIELD STRENGTH FOR CONDITION H950

Mechanical Properties

Condition	H950
Yield Strength, MPa (ksi)	1648 (239)
Ultimate Tensile Strength MPa (ksi)	1751 (254)
Elongation	14%
Reduction in Area	63%
Fracture Toughness	98 (89)
Charpy V-Notch Energy, J (ft-lb)	27 (20)