

Component elements properties						
Aluminum, Al	87.1–91.4%	Manganese, Mn	<= 0.30%			
Chromium, Cr	0.18–0.28%	Silicon, Si	<= 0.40%			
Copper, Cu	1.2–2.0%	Titanium, Ti	<= 0.20%			
Iron, Fe	<= 0.50%	Zinc, Zn	5.1–6.1%			
Magnesium, Mg	2.1–2.9%	Others	<= 0.15%			
Mechanical Properties						
Density (g/cm ³)	Ultimate Tensile Strength (MPa)	Tensile Yield Strength (MPa)	Modulus of Elasticity (GPa)	Poisson's Ratio	Shear Modulus (GPa)	Shear Strength (MPa)
2.81	572	503	71.7	0.33	26.9	31