

Properties	Al6061	Al7075
Elastic modulus (GPa)	70-80	70-80
Density (g/cc)	2.7	2.81
Poisson's ratio	0.33	0.33
Hardness (HB500)	30	60
Tensile strength (MPa)	115	115