

## Titanium Grade 2, Annealed

### Titanium Grade 2, Annealed

**Categories:** [Metal](#); [Nonferrous Metal](#); [Titanium Alloy](#); [Unalloyed/Modified Titanium](#)

**Material Notes:** Information provided by Allvac and the references.

**Applications:** Airframe components, cryogenic vessels, heat exchangers, CPI equipment, condenser tubing, pickl

Forms typically available: billet, bar, plate, sheet, strip, rod, wire, extrusions, tubing.

Titanium Grades 1,2,3,4,7,11,and 12 are all considered unalloyed and have similar mechanical properties.

**Key Words:** ASTM Grade 2; UNS R50400, CP titanium, C.P. titanium alloy

**Vendors:** [Click here to view all available suppliers for this material.](#)

Please [click here](#) if you are a supplier and would like information on how to add your listing to this material.

 [Printer friendly version](#)  [Download as PDF](#)  [Download to Excel \(requires Excel and Windows\)](#)  
 [Export data to your CAD/FEA program](#)

| Physical Properties | Metric    |
|---------------------|-----------|
| Density             | 4.51 g/cc |

| Mechanical Properties      | Metric                                                      |
|----------------------------|-------------------------------------------------------------|
| Hardness, Brinell          | 200                                                         |
| Hardness, Rockwell B       | 98                                                          |
| Tensile Strength           | 193 MPa<br>@Temperature 316 °C @Ter                         |
| Tensile Strength, Ultimate | 430 MPa                                                     |
| Tensile Strength, Yield    | 340 MPa                                                     |
| Elongation at Break        | 28 %                                                        |
| Rupture Strength           | >= 138 MPa<br>@Temperature 316 °C,<br>Time 3.60e+6 sec @Ter |
| Tensile Modulus            | 102 GPa                                                     |
| Modulus of Rigidity        | 38.6 GPa                                                    |
| Compressive Yield Strength | 340 MPa                                                     |

<https://www.matweb.com/search/DataSheet.aspx?MatGUID=49a4b764217b44ee953205822af5fbc9&ckck=1>