

**Kara Metal Çelik**

TR

EN

HOME

CORPORATE

PRODUCTS

SERVICES

STEEL PROPERTIES

TECHNICAL INFORMATION

CONTACT

Application Information

Public Id

X46Cr13 - 1.4034

Grade (EU)
Number

X46Cr13
1.4034

Classification

X46Cr13 - 1.4034

EN 10088-2: 2005

EN 10088-3: 2005

EN 10088-1: 2005

Chemical Composition

X46Cr13 - 1.4034

C	0.43 - 0.5
Si	max 1.00
Mn	max 1
P	max 0.04
S	max 0.015
Cr	12.5 - 14.5

Mechanical Properties

X46Cr13 - 1.4034

Rm - Tensile strength (MPa) (+A)	850 - 1000
Rm - Tensile strength (MPa) (+QT800)	780


Kara Metal Çelik

TR

EN

HOME

CORPORATE

PRODUCTS

SERVICES

STEEL PROPERTIES

TECHNICAL INFORMATION

CONTACT

X46Cr13 - 1.4034

A - Min. elongation at fracture (%)

10 - 12

X46Cr13 - 1.4034

Brinell hardness (HB): (+A)

245

X6CrNi17-1 - 1.4017

Equivalent References

Grade	X6CrNi17-1
Number	1.4017
---	---
---	---

[Detailed Feature Table...](#)

X12Cr13 - 1.4006

Equivalent References

USA	410
France, AFNOR	Z10C13
England, BS	410S21
Russia, GOST	12KH13L

[Detailed Feature Table...](#)

X20Cr13 - 1.4021

Equivalent References

USA	420
France, AFNOR	X20Cr13
England, BS	420S29
Russia, GOST	20KH13

[Detailed Feature Table...](#)

X30Cr13 - 1.4028

Equivalent References

USA	420
France, AFNOR	1.4028
England, BS	420S45
Russia, GOST	30KH13

[Detailed Feature Table...](#)

X38CrMo14 - 1.4419

Equivalent References

Grade	X38CrMo14
Number	1.4419
---	---
---	---

[Detailed Feature Table...](#)

X46Cr13 - 1.4034

Equivalent References

EU, EN	X46Cr13
Poland, PN	4H13
Russia, GHST	40KH13
---	---

[Detailed Feature Table...](#)
KARA METAL ÇELİK © 2005 - 2020

Esenşehir Mahallesi Des Sanayi Sitesi 113.Sokak C8 Blok No:2
P.K.34776 Yukarı Dudullu - Ümraniye / İSTANBUL - TURKEY



Kara Metal Çelik

TR

EN

HOME

CORPORATE

PRODUCTS

SERVICES

STEEL PROPERTIES

TECHNICAL INFORMATION

CONTACT