

SS 465 data from aerometals

REFERENCE LINK

https://www.aerometals-alloys.com/wp-content/uploads/2020/06/UK-Custom465_-FT039.pdf

➤ MECHANICAL PROPERTIES

Condition	Rm Tensile strength (MPa)	Rp0.2 Yield strength (MPa)	4D elongation (%)	Ra (%)
Solution heat treated	951	683	20	
H950 - 510°C	1765	1669	13	62
H975 - 524°C	1703	1620	13	61
H1000 - 538°C	1593	1510	15	63
H1050 - 566°C	1482	1386	17	66

➤ PHYSICAL PROPERTIES

Density (g/cm ³)	7.8
Typical hardness (HRc)	47-50
Modulus of elasticity at 20°C (N/mm ²)	202 x10 ³
Thermal conductivity at 20°C (W/m °C)	15
Electrical resistance µohm-mm	824 (H900)
Magnetic	YES

<https://acrobat.adobe.com/id/urn:aaid:sc:ap:94f9f73c-f97e-49ca-9a78-1b57cae4d47c>