

SS 465 ANNEALED AND H900
FOR CONDITION ANNEALED,H900
REFERENCE LINK

<https://www.carpentertechnology.com/hubfs/7407324/Material%20Safety%20Data%20Sheets/Custom%20465.pdf>

Typical Room Temperature Mechanical Properties—Custom 465 Stainless Wire

Condition	0.2% Yield Strength		Ultimate Tensile Strength		% Elongation in 4D	% Reduction of Area	Hardness (HRC)
	ksi	MPa	ksi	MPa			
Annealed/CT	112	772	138	951	20	75	29.5
H900	247	1703	258	1779	14	51	50
71% Cold Drawn	163	1124	174	1200	12	74	38.5
71% Cold Drawn + 900°F (482°C) Age	293	2020	303	2089	10	57	55