

SS 465 DATA FROM LINTSTEELS

REFERENCE LINK

<https://www.lintsteels.com/custom-465-forgings-circle-supplier-stock-ist/>



Physical Properties Of Stainless Steel Custom 465 Circle

Density	Annealed/CT	Condition H 900	Condition H 950	Condition H 1000
	7810 kg/m ³	7820 kg/m ³	7830 kg/m ³	7840 kg/m ³