

SS 465 data from spacematdb

REFERENCE LINK

<https://www.spacematdb.com/spacemat/manudatasheets/custo>

Modulus of Elasticity (E)	
Condition H 1000	199 x 10 ³ MPa
Condition H 1100	196 x 10 ³ MPa

Modulus of Elasticity (E)

Condition	X10 ³ ksi
H1000	28.8
H1100	28.4

[m465.pdf](#)