

SS 465 DATA FROM INDIAMART

REFERENCE LINK

<https://5.imimg.com/data5/SELLER/Doc/2021/7/MW/KW/YQ/11391831/custom-455-uns-s45500-round-bar.pdf>

FOR CONDITION **H950,H1000**

Stainless Steel, Custom 465

This grade is a registered trademark of Carpenter Technology Corporation. This alloy is a Martensitic Age Hardenable Stainless with exceptional tensile strength and corrosion resistance. The strength of this grade is superior to that of Custom 455. The applications are generally used in the Aerospace and Defence Industries.

Chemical Composition (Weight %)

	C	Mn	Si	P	S	Cr	Ni	Mo	Ti	N
Min						11.00	10.75	0.75	1.50	
Max	0.02	0.25	0.25	0.015	0.01	12.50	11.25	1.25	1.80	0.01

Typical Mechanical Properties (Min)

Condition	Tensile Strength, MPa	Yield Strength 0.2%, MPa	Elongation %	Reduction of Area %	Hardness HRC
H950	1655	1515	10	45	
H1000	1515	1380	10	50	