



This datasheet of **ALCOM POM 770/1 PTFE10** from **MOCOM Compounds GmbH & Co. KG** is provided by the international plastics database **CAMPUS**.

ALCOM POM 770/1 PTFE10 | (POM+PTFE) | MOCOM Compounds GmbH & Co. KG

Product Texts

Base Polymer	Polyoxymethylene/general
Filler/Additive System	10 % PTFE
Special Features	heat stabilised,easy release (demoulding),improved sliding / wear
Market Segment	various
Application Area	various

Rheological properties

	Value	Unit
Melt volume-flow rate, MVR	6.5	cm ³ /10min
Temperature	190	°C
Load	2.16	kg

Mechanical properties

	Value	Unit
Tensile modulus	2550	MPa
Yield stress	55	MPa
Yield strain	10	%
Charpy impact strength, +23°C	80	kJ/m ²
Charpy notched impact strength, +23°C	5	kJ/m ²

Thermal properties

	Value	Unit
Temp. of deflection under load, 1.80 MPa	90	°C
Vicat softening temperature, 50°C/h 50N	145	°C

Other properties

	Value	Unit
Density	1440	kg/m ³

This website uses cookies. By using this website, you agree to the use of cookies.

[Privacy Policy](#)

[Close](#)

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information

Injection molding

	in a dry air (dessiccant) dryer 100-110 °C for 2-3 h
Pre-Drying Conditions	in an air circulating dryer 100-110 °C for 3-5 h dependant on moisture content
Processing Injection Moulding	melt temperature 180-220 °C mould temperature 60-120 °C
Storage	dry, protected from light not above 30°C

Disclaimer

These are guide values and not a specification. The test values mentioned are representative values only and not binding minimum or maximum figures. These test values have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by MOCOM for any medical, pharmaceutical or diagnostic application is conditional to an assessment by MOCOM in terms of compliance with MOCOM internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, MOCOM does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC or EU Medical Device Regulation (MDR) 2017/745 or risk class 3 FDA
- Medical devices described in list A according IVDD (98/79/EG) or risk class D in EU 2017/746 in vitro diagnostic medical devices (IVDR)
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.

The CAMPUS internet database is hosted by Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. Any decision about the application of materials must be double checked with the producer of this material.

CAMPUS® is a registered trademark of CWFG mbH, Frankfurt am Main, 2025

This website uses cookies. By using this website, you agree to the use of cookies.

[Privacy Policy](#)

[Close](#)