

☐ POLYMER SEARCH

[HOME](#) / [POLYMER SEARCH](#) / [Composite Core Material](#) /
[Sawbones Solid Rigid Polyurethane Foam 10 pcf Density](#)

Sawbones Solid Rigid Polyurethane Foam 10 pcf Density

Category	Other Engineering Material , Composite Core Material , Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane Foam, Unreinforced
Manufacturer	Sawbones
Trade Name	
Port	Shanghai port,China
Trade Terms	FOB, CFR, CIF
Payment Terms	L/C, T/T, Western Union
Download PDF	Sawbones Solid Rigid Polyurethane Foam 10 pcf Density.pdf 
Price	EMAIL US ☐ sales@lookpolymers.com

☐ **IN STOCK**☐ Documents ☐ SGS ☐ MSDS ☐ Factory Documents☐ Online Service ☐ lookpolymers ☐ 27660005

Material Notes:

Solid Rigid Polyurethane Foam
Primary Use Solid rigid polyurethane foam is primarily used as an alternative test medium for human cancellous bone. These products are not intended to replicate the mechanical properties of human bone, however, it does provide consistent and uniform material with properties in the range of human cancellous bone. Relevant mechanical properties for comparison to human cancellous bone may depend on the particular test method that is being developed. The ASTM F-1839-08 "Standard Specification for Rigid Polyurethane Foam for Use as a Standard Material for Testing Orthopaedic Devices and Instruments" states that, "The uniformity and consistent properties of rigid polyurethane foam make it an ideal material for comparative testing of bones screws and other medical devices and instruments."
Description Solid rigid polyurethane foam has a closed cell content ranging from 96.0 to 99.9%. Foam is available in a range of sizes and densities, from 0.08 to 0.80 grams per cubic centimeter (5 to 50 pounds per cubic foot).. Standard block size: 13cm X 18cm X 4cm Standard sheet size: 13cm X 18cm X 3mm
Other Notes Water absorption ranges from 0.301 to 0.0 kg/m² Foam meets ASTM F-1839-08. Block dimensions are within $\hat{A}\pm 2$ mm and sheet thickness is within $\hat{A}\pm 0.3$ mm. Foam density may vary $\hat{A}\pm 10\%$. Properties parallel to direction of the rise of foam. Information provided by Sawbones.

Physical Properties	Metric	English	Comments
Density	0.160 g/cc	0.00578 lb/in $\hat{A}^3$	

Mechanical Properties	Metric	English	Comments
Tensile Strength	2.10 MPa	305 psi	
Tensile Modulus	0.0860 GPa	12.5 ksi	
Compressive Yield Strength	2.20 MPa	319 psi	
Compressive Modulus	0.0580 GPa	8.41 ksi	
Poissons Ratio	0.30	0.30	Calculated
Shear Modulus	0.0190 GPa	2.76 ksi	
Shear Strength	1.60 MPa	232 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	63.0 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$	35.0 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature -46.0 - 93.0 $\text{Å}^\circ\text{C}$	@Temperature -50.8 - 199 $\text{Å}^\circ\text{F}$	

Users viewing this material also viewed the following:
Polykemi AB POLYblend 65V PC/ABS-Blend, Flame Retardant
Johnson Matthey JM A25 Soft Solder/Flux
SABIC Innovative Plastics Noryl GTX GTX966 PPE+PA66 (Europe-Africa-Middle East)
SCG Chemicals EL-Leneâ„ç H570P High Density Polyethylene Pipe Resin
Teknor Apex Tekbond® TB 1372A Thermoplastic Elastomer
Chengdu Polyster 7502 High Performance Grade TPV
Eastman Eastar AN001 Copolyester, Natural
Cytec Thornel® T-650/42 12K Carbon Fiber, Polyacrylonitrile (PAN) Precursor
Domo 1101P Polypropylene Homopolymer

HOME

ABOUT US

POLYMER SEARCH

COMPANY NEWS

PRODUCT NEWS

CONTACT US [RFQ](#)

Copyright © lookpolymers.com All Rights Reserved