

Typical Properties of AGIS-1500 Micro Cellular Urethane Foam

Description: AGIS-1500 is a 15 pcf density cellular polyurethane foam. This microcellular foam, and its family, have been specially developed to solve mechanical energy control problems. AGIS-1500 has a very fine cell structure, a low compression set, and excellent recovery properties. These properties give AGIS-1500 open cell foam superior shock absorption and vibration isolation performance. AGIS-1500 has a temperature range of -40° F to +150° F, low outgassing, and meets the FMVSS-302 Flammability rating, allowing it to be used in automotive applications.

AGIS-1500's excellent compression set characteristics and dimensional stability allow it to be used in many applications such as automotive, electrical goods, medical and safety equipment. Microcellular urethane is often added to protect electronic devices from shock, such as a dropped cell phone. It makes an excellent gasket for many applications and is listed with UL for the gasketing and sealing requirements of UL 50, UL 508, and UL 514.

AGIS-1500's has a compression deflection @ 25% of 7 psi, making it a soft to medium range compression foam. It is also offered in the denser 20 and 25 pcf density AGIS-2500. All cellular urethane products can be supplied with or without adhesive backing in full rolls up to 54" wide, or narrow as 1/4". We can also die cut or waterjet cut parts to your exact specifications.

Polymer

POLYURETHANE

FLAMMABILITY SPECIFICATIONS

UL 94 HBF	LISTED
FMVSS-302	PASS

UL SPECS

UL 50	LISTED
UL 508	LISTED
UL 514B	LISTED

Physical Property	Test Method	Unit of Measure	Result
DENSITY	ASTM D3574	pcf kg/m³	15 240
TENSILE STRENGTH	ASTM D3574	psi kPa	85 586
ELONGATION	ASTM D3574	%	100
TEAR STRENGTH	ASTM D624	lb /in kN/m	8 1.4
COMPRESSION SET 50% - 22 HRS @ 73°F	ASTM D1667	%	.19
COMPRESSION SET 50% - 22 HRS @ 158°F	ASTM D3574	%	3

COMPRESSION SET 50% - AFTER 5 HR AUTOCLAVE @ 250°F	ASTM D3574	%	1.4
COMPRESSION DEFLECTION @ 25%	ASTM D3574	psi kPa	7 48
COMPRESSION DEFLECTION @ 50%	ASTM D3574	psi kPa	15 103
LOW TEMPERATURE	N/A	°F °C	-40°F -40°C
HIGH TEMPERATURE	N/A	°F °C	225°F 107°C
MAXIMUM RECOMMENDED INTERMITTENT TEMPERATURE	N/A	°F °C	248°F 120°C
VOLUME RESISTIVITY	ASTM D257	ohms	1.3 X 10 ¹¹
HARDNESS SHORE OO, 15 SEC POST IMPACT	ASTM D2240	DUROMETER	50
BRITTLINESS	ASTM D746	°F °C	-62°F -52°C
CORROSION RESISTANCE	AMS D3568	N/A	EXCELLENT
COLD FLEXIBILITY 4 HRS AT -18° C (0° F)	AMS D3568	N/A	PASSES
DIELECTRIC STRENGTH	ASTM D149	V/mil	56
ROHS COMPLIANT	N/A	N/A	YES

This information is for reference only. Atlantic Gasket shall not be held responsible for its content or use. It is the customer's responsibility to obtain and test samples to determine the material for a specific application.



[Click here](#) to download a specification Word document.