

PRODUCT DATA SHEET

LDPE C03920

Low Density Polyethylene

Blown Film

Applications

- Heavy duty bags
- Agricultural film
- Construction film
- Blend partner
- Pallet shrink film
- Profile extrusion

Property	Value	Unit	Test Method
Melt Index	0.3	g/10min	
Density	.920	g/cm ³	
Tensile Strength at Yield MD/TD	1800/1700	psi	ASTM D 882
Tensile Strength at Break MD/TD	4500/3900	psi	ASTM D 882
Elongation at Break MD/TD	160/650	%	ASTM D 882
1% Secant Modulus MD/TD	32000/43000	psi	ASTM D 882
Elmendorf Tear Strength MD/TD	120/120	g	ASTM D 1922
Haze	16	%	ASTM D 1003
Dart Drop Impact, F50	170	g	ASTM D 1709
Gloss	38		ASTM D 2457

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.

www.globalplastics.net

New York Office

145 Hudson Street Suite 200A
New York City, NY 10013
(P) 1 800 417-4605
(F) 1 800 431-8614

San Diego Office

113 W G Street Suite 521
San Diego, CA 92101
(P) 1 619 446-6508
(F) 1 800 431-8614