



TECHNICAL DATASHEET

Commercially
FT 0

The four types of commercially pure titanium currently on the market (1/2/3/4) are combined with excellent corrosion resistance, moderate strength and good weldability. The variations in content of oxygen, carbon, hydrogen and nitrogen, the variations in content of which define each grade's mechanical properties (Grade 1) through to the hardest and strongest (Grade 4).

Grade 2 titanium is the most popular and widely-available of the four commercial grades. It has a good balance of corrosion resistance and formability to Grade 1, but with higher strength.

APPLICATIONS

Industrial
Medical
Aeronautic

STANDARDS

ASTM B348 / ASME SB348
ASTM B265 / ASME SB265
ASTM B338 / ASME SB338
ASTM B861 / ASTM B862
ASTM B381
NACE MR0175
AWS A5.16 ERTi2
ASTM F67
ISO 5832-2
AMS 4902

Typical dimensions

some of

➤ CHEMICAL COMPOSITION

%	Fe	O	N	C
min				
max	0.3	0.25	0.03	0.08

➤ MECHANICAL PROPERTIES

Rm Tensile strength (MPa)	Rp0.2 Yield strength (MPa)	Elongation (%)
345	275	