



Industrial Piping Products

AISI 303 / UNS S30300 / DIN 1.4305

High Sulphur Free Machining Austenitic Stainless Steel

Alloy 303 Data Sheet

Introduction

AISI 303 is a non magnetic austenitic stainless steel and a modified version of Alloy 304 with addition of Sulphur to improve machinability. It has improved chemistry as compared to 18/8 Stainless Steel to display extra machining performance maintaining good mechanical & corrosion properties. Stainless Steel 303 offers excellent toughness though sulphur addition imparts cutback to some limit.

Chemical Composition (Typical)

Element	Limits	
	min	max
Carbon	0.000	0.150
Manganese	0.000	2.000
Phosphorus	0.000	0.200
Sulphur	0.000	0.150
Silicon	0.000	1.000
Chromium	17.000	19.000
Nickel	8.000	10.000
Iron	Remainder	

Mechanical Properties (Typical)

Parameter	Value
Yield 0.2 % (Mpa/Nmm ²), Min	310
Tensile (Mpa/Nmm ²), Min	620
Elongation (% in 50MM), Min	30
Reduction Area(%), Min	40
Hardness (BHN), Min	170

Physical Properties

Parameter	Value
Density (Kg/m ³)	8027
Elastic Modulus (Gpa)	193
*Co-eff of Expansion ($\mu\text{m/m/}^{\circ}\text{C}$)	18.4
*Thermal Condc. (W/m.K)	21.5
Electric Resistivity (n Ω .m) 20°C	720
*Note : @500°C	

Corrosion Data

Alloy 303 is fairly corrosion resistance as compared to other 300 Series Stainless Steel like 304, 316 etc. For better corrosion resistance, Alloy 303 should be used in annealed condition with passivation of parts. Due to Sulphur addition, SS 303 should not be exposed to marine environment resulting in Corrosion Pitting. Due to Sulphur alignment in rolling direction, Alloy 303 offers least corrosion resistance in cross section.

Equivalent Grade Designation

AISI 303
UNS S30300
BS 303S31
DIN EN 1.4305
X8CrNiS18-9
SS 2346
SUS 303

Alloy 303 Data Sheet

Available Product Forms

Round bars
Square bars
Hexagon Bars
Flat bars
Precision Components
Fasteners - Bolts & Nuts
Forged Components
Mechanical Tubings

Common Manufacturing Specifications

ASTM A194 (303, 8F, 8FA), A314, A320, A473, A581, A582, A895,
ASME SA194 (303, 8F, 8FA), SA276, SA314, SA320, SA473, SA581, SA582, SA895,
ASTM F593, F594, F836, F837, F880
AMS 5640 (TYPE 1), AMS 5640 (type 2), AMS 5641, AMS 5738,
MIL SPEC MIL-S-862, SAE J405

Alternate to Alloy

Alloy 304 is next best alternative to Alloy 303 with better corrosion resistance, weldability but at cost of machinability. Another possible alternative is Alloy 316 with improved corrosion compared to 303 & 304. AISi 416 is also a possible alternative with higher machinability with lower corrosion resistance than 303.

Applications & Industries

Fasteners - Nuts & Bolts
Bushings & Shafftings
Aircraft & Engine Components
Valve components
Automotive Gears & Equipments
Electrical components & parts
General engineering applications

Excellence Inherent

With 3 decade long experience inherited, we aim at providing better solutions for Industrial Piping Sector. Skilled Team, passion drives our *will* to be better with resolute for continous customer & vendor concurrence. We also perceive our duty towards planet for its unconditional support & try to minimise any harm caused due to our activity. For Instance, *We Stay Paperless*

The Information contained in this data sheet is for reference purpose only and actual data may vary from product to product. Complete rely on these values for product design recommended. User will be solely responsible for any failure. **FERROBEND™** is trademark Property of **FERROBEND**.



Reach Us

Unit # 1, 109/111, S S Maharaj Marg, 2nd Lane, Goldeol, Mumbai 400004. Maharashtra. India.

Tel : 91 - 22 - 6666 5432 / 6636 3375

www.ferrobend.com