

Normalized energy release rate $\frac{G_{(\cdot)}}{G_0}$ as function of crack angular semi-aperture $\Delta\theta$, calculated with in-house force-based and stress-based VCCT post-processing routines with stresses extracted on the fiber side of the interface

