

Normalized energy release rate  $\frac{G_{(\cdot)}}{G_0}$  as function of crack angular semi-aperture  $\Delta\theta$ , calculated with in-house force-based VCCT and Abaqus built-in J-Integral (\*CONTOUR INTEGRAL) post-processing routines

