

Normalized energy release rate  $\frac{G(\cdot)}{G_0}$  as function of crack angular semi-aperture  $\Delta\theta$ , calculated with in-house force-based and stress-based VCCT post-processing routines with stresses extracted on the fiber side of the interface

