

# Similarity laws of the fiber-matrix interface crack in polymer composites

Luca Di Stasio<sup>a,b</sup>, Janis Varna<sup>a</sup> and Zoubir Ayadi<sup>b</sup>

<sup>a</sup>Luleå University of Technology, University Campus, SE-97187 Luleå, Sweden

<sup>b</sup>Université de Lorraine, EEIGM, IJL, 6 Rue Bastien Lepage, F-54010 Nancy, France

## ARTICLE INFO

### Keywords:

Fiber Reinforced Polymer Composite (FRPC)

Debonding

Similarity

Dimensional analysis

## ABSTRACT

This template helps you to create a properly formatted L<sup>A</sup>T<sub>E</sub>X manuscript.

\begin{abstract} ... \end{abstract} and \begin{keyword} ... \end{keyword} which contain the abstract and keywords respectively.

Each keyword shall be separated by a \sep command.

## 1. Introduction

One of the most promising developments in Fiber Reinforced Polymer Composites (FRPCs) for advanced structural applications is currently represented by *thin-ply* laminates [1]. Constituted by extremely thin plies, with  $t_{90^\circ}$  as small as just  $\sim 4-5$  fiber diameters, this family of laminates is characterized by its damage tolerance, in particular the capability of delaying to higher strains and even suppressing the onset and propagation of transverse cracks [2]. The recent experimental assessment of transverse cracks suppression in *thin-ply* laminates [3, 4, 5] validates the existence of a *ply-thickness* effect [5] at scales  $10\times$  smaller than those at which it was originally observed at the end of the 1970's [6]. Onset of transverse cracks coincides at the microscopic level with the formation of fiber/matrix interface cracks [7], or debonds. After the inter-fiber stress [8] and strain concentration [9] causes the matrix to fail at or close the fiber interface, debonds grow along the fiber arc direction until a maximum or critical size is reached. If the applied load is increased, debonds move into the matrix or “kink” out of the fiber/matrix interface [10, 11]. Coalescence of debonds then occurs, which corresponds macroscopically to through-the-thickness transverse crack propagation [10, 12]. Finally, propagation through the specimen width occurs [10].

Given that *thin-ply*s, as previously noted, can reach nowadays thicknesses of just  $\sim 4-5$  fiber diameters, the characteristic size of the ply, i.e. the thickness  $t_{90^\circ}$ , is now comparable in magnitude to the characteristic size of debonds, i.e. the fiber diameter  $2R_f$ , such that  $t_{90^\circ}/(2R_f) \sim \mathcal{O}(1)$ . This has motivated in recent years a renewed interest in debond growth modeling [13, 14, 15, 16]. Since the elastic solution to the interface crack problem implies an oscillating solution at the crack tip [17] in the *open* case (crack faces not in contact), Stress Intensify Factors (SIFs) are not defined and debond growth characterization has focused on the determination of Mode I, Mode II and total Energy Release Rate (ERR). Many authors have reported their results in normalized form [11, 18, 19], by defining a reference ERR  $G_0$ . The definition of such reference ERR would be useful to establish similarity laws and thus to allow comparisons between

different material systems, scales, loads and microstructural arrangement. However, no agreement can be found in the literature on the very definition of  $G_0$  and expressions vary between authors. Furthermore, no clear derivation of  $G_0$  has been proposed. In this brief contribution, we provide a derivation of  $G_0$  based on arguments of dimensional analysis, material homogenization and fracture mechanics; we then apply the derived expression of reference ERR to the analysis of debond growth in Representative Volume Elements (RVEs) of UD composites and cross-ply laminates.

## 2. Dimensional analysis

We first recall that the Energy Release Rate  $G$  has units of energy  $E$  per unit area:

$$[G] = \frac{E}{L^2}, \quad (1)$$

where  $L$  stands for unit of length. By algebraic manipulation of Equation 1 we can write the units of ERR as

$$\frac{E}{L^2} = \frac{F \cdot L}{L^2} = \frac{F}{L^2} \frac{L}{L}, \quad (2)$$

where  $F$  stands for unit of force. We recognize that, in Equation 2

$$\frac{F}{L^2} = [\sigma] \quad \frac{L}{L} = [\epsilon], \quad (3)$$

where  $\sigma$  and  $\epsilon$  are respectively stress and strain. The Energy Release Rate is thus dimensionally equivalent to a reference stress  $\sigma_{ref}$  times a reference strain  $\epsilon_{ref}$  times a reference length  $l_{ref}$  and we can write

$$G \sim \sigma_{ref} \epsilon_{ref} l_{ref}. \quad (4)$$

## 3. Linear Elastic Fracture Mechanics (LEFM) considerations

In the case of uniaxial loading, we can assume that: in a stress-controlled experiment,  $\sigma_{ref}$  is equal to the applied

ORCID(s):

stress  $\sigma_0$  and  $\epsilon_{ref}$  to the average strain  $\epsilon_0$  in the Representative Volume Element (RVE); in a strain-controlled experiment,  $\epsilon_{ref}$  is equal to the applied strain  $\epsilon_0$  and  $\sigma_{ref}$  to the average stress  $\sigma_{av}$  in the Representative Volume Element (RVE).

Under the assumption of linear elastic material constituents, we have, respectively for a stress- and strain-controlled experiment:

$$\epsilon_{av} = E_{homo} \sigma_0 \quad \sigma_{av} = E_{homo} \epsilon_0, \quad (5)$$

where  $E_{homo}$  is a homogenized RVE Young's modulus which measures the RVE elastic response in the presence of different material phases and damage. It is worth to point out here that, as we are interested in studying debond growth in the context of transverse crack onset, RVEs are loaded in the direction transverse to the fibers in the layer where debonds are present. Furthermore, we consider RVEs that are 2-dimensional and under the assumption of plane strain or plane stress conditions. This implies, considering the elastic response of a transversely isotropic material in its plane of transverse isotropy (indices 2–3, index 1 corresponds to the axis of rotational symmetry) with no damage, that [20, 21]

$$E_{homo} = \frac{E_2}{1 - \nu_{12}\nu_{21}} \quad E_{homo} = E_2, \quad (6)$$

respectively for plane strain and plane stress, with  $E_2$  the homogenized transverse Young's modulus of the ply and  $\nu_{12}$ ,  $\nu_{21}$  the major and minor Poisson's ratios. Notice that homogenized elastic properties depend on constituents' elastic properties and the presence of damage, we can assume the homogenized Young's modulus of the damaged RVE to be a fraction of the undamaged modulus  $E_{homo}^0$  (expressed in Eq. 6):

$$E_{homo} = f(\Delta\theta) E_{homo}^0, \quad (7)$$

where  $0 < f(\Delta\theta) < 1$  is a function of the damage state in the material, in this case represented by the debond half-size  $\Delta\theta$  (debond size is  $2\Delta\theta$ ). By substituting Eq. 5, Eq. 6 and Eq. 7 in Eq. 4, we have

$$G \sim f(\Delta\theta) \frac{E_2}{1 - \nu_{12}\nu_{21}} \epsilon_0^2 l_{ref} \quad G \sim f(\Delta\theta) E_2 \epsilon_0^2 l_{ref}, \quad (8)$$

respectively for plane strain and plane stress conditions under applied strain  $\epsilon_0$ , and

$$G \sim f(\Delta\theta) \frac{1 - \nu_{12}\nu_{21}}{E_2} \sigma_0^2 l_{ref} \quad G \sim f(\Delta\theta) \frac{\sigma_0^2}{E_2} l_{ref}, \quad (9)$$

respectively for plane strain and plane stress conditions under applied strain  $\sigma_0$ . Notice that, incidentally: the plane strain expression in Eq. 9 is the same as the ERR expression used for *in-situ* strength modeling in [22] and derived

in [23] by considering the fiber-reinforced polymer as a 3-phase composite with one phase constituted by sharp voids (cracks); the plane stress expression in Eq. 9 is the same as the Mode I ERR in [24], derived from the definition of ERR and problem geometry.

#### 4. Representative Volume Elements (RVEs)

#### 5. Similarity laws

#### 6. Conclusions

#### References

- [1] A. Kopp, S. Stappert, D. Mattsson, K. Olofsson, E. Marklund, G. Kurth, E. Mooij, E. Roorda, The aurora space launcher concept, CEAS Space Journal 10 (2017) 167–187.
- [2] J. Cugnoni, R. Amacher, S. Kohler, J. Brunner, E. Kramer, C. Dransfeld, W. Smith, K. Scobbie, L. Sorensen, J. Botsis, Towards aerospace grade thin-ply composites: Effect of ply thickness, fibre, matrix and interlayer toughening on strength and damage tolerance, Composites Science and Technology 168 (2018) 467–477.
- [3] H. Sasayama, K. Kawabe, S. Tomoda, I. Ohsawa, K. Kageyama, N. Ogata, Effect of lamina thickness on first ply failure in multidirectionally laminated composites, in: Proceedings of the 8<sup>th</sup> Japan SAMPE Symposium, SAMPE, 2003.
- [4] H. Saito, H. Takeuchi, I. Kimpura, Experimental evaluation of the damage growth restraining in 90° layer of thin-ply cfrp cross-ply laminates, Advanced Composite Materials 21 (2012) 57–66.
- [5] R. Amacher, J. Cugnoni, J. Botsis, L. Sorensen, W. Smith, C. Dransfeld, Thin ply composites: Experimental characterization and modeling of size-effects, Composites Science and Technology 101 (2014) 121–132.
- [6] J. E. Bailey, P. T. Curtis, A. Parvizi, On the transverse cracking and longitudinal splitting behaviour of glass and carbon fibre reinforced epoxy cross ply laminates and the effect of poisson and thermally generated strain, Proceedings of the Royal Society A: Mathematical, Physical and Engineering Sciences 366 (1979) 599–623.
- [7] J. E. Bailey, A. Parvizi, On fibre debonding effects and the mechanism of transverse-ply failure in cross-ply laminates of glass fibre/thermoset composites, Journal of Materials Science 16 (1981) 649–659.
- [8] L. Asp, L. Berglund, R. Talreja, Prediction of matrix-initiated transverse failure in polymer composites, Composites Science and Technology 56 (1996) 1089–1097.
- [9] J. A. Kies, Maximum strains in the resin of fibreglass composites, NRL Report 5752, AD-274560, Washington (DC): U.S. Naval Research Laboratory, 1962.
- [10] H. Zhang, M. Ericson, J. Varna, L. Berglund, Transverse single-fibre test for interfacial debonding in composites: 1. experimental observations, Composites Part A: Applied Science and Manufacturing 28 (1997) 309–315.
- [11] F. Paris, E. Correa, V. Mantić, Kinking of transversal interface cracks between fiber and matrix, Journal of Applied Mechanics 74 (2007) 703.
- [12] L. Zhuang, R. Talreja, J. Varna, Transverse crack formation in unidirectional composites by linking of fibre/matrix debond cracks, Composites Part A: Applied Science and Manufacturing 107 (2018) 294–303.
- [13] L. Zhuang, A. Pupurs, J. Varna, R. Talreja, Z. Ayadi, Effects of inter-fiber spacing on fiber-matrix debond crack growth in unidirectional composites under transverse loading, Composites Part A: Applied Science and Manufacturing 109 (2018) 463–471.
- [14] C. Sandino, E. Correa, F. Paris, Numerical analysis of the influence of a nearby fibre on the interface crack growth in composites under transverse tensile load, Engineering Fracture Mechanics 168 (2016) 58–75.

- [15] J. Varna, L. Q. Zhuang, A. Pupurs, Z. Ayadi, Growth and interaction of debonds in local clusters of fibers in unidirectional composites during transverse loading, *Key Engineering Materials* 754 (2017) 63–66.
- [16] C. Sandino, E. Correa, F. París, Interface crack growth under transverse compression: nearby fibre effect, in: *Proceeding of the 18<sup>th</sup> European Conference on Composite Materials (ECCM-18)*, 2018.
- [17] M. Comninou, The interface crack, *Journal of Applied Mechanics* 44 (1977) 631.
- [18] M. Toya, A crack along the interface of a circular inclusion embedded in an infinite solid, *Journal of the Mechanics and Physics of Solids* 22 (1974) 325–348.
- [19] F. París, J. C. Caño, J. Varna, The fiber-matrix interface crack — a numerical analysis using boundary elements, *International Journal of Fracture* 82 (1996) 11–29.
- [20] S. P. Timoshenko, J. N. Goodier, *Theory of elasticity*, Engineering societies monographs, McGraw-Hill, 1987.
- [21] V. Mantič, Interface crack onset at a circular cylindrical inclusion under a remote transverse tension. application of a coupled stress and energy criterion, *International Journal of Solids and Structures* 46 (2009) 1287–1304.
- [22] P. P. Camanho, C. G. D’Ávila, S. T. Pinho, L. Iannucci, P. Robinson, Prediction of in situ strengths and matrix cracking in composites under transverse tension and in-plane shear, *Composites Part A: Applied Science and Manufacturing* 37 (2006) 165 – 176. CompTest 2004.
- [23] N. Laws, G. Dvorak, M. Hejazi, Stiffness changes in unidirectional composites caused by crack systems, *Mechanics of Materials* 2 (1983) 123 – 137.
- [24] J. Varna, 2.10 crack separation based models for microcracking, in: P. W. Beaumont, C. H. Zweben (Eds.), *Comprehensive Composite Materials II*, Elsevier, Oxford, 2018, pp. 192 – 220. doi:<https://doi.org/10.1016/B978-0-12-803581-8.09910-0>.