

Constitutive modeling for laminates with fiber/matrix interface cracks under transverse loading

Luca Di Stasio^a, Janis Varna^a

^a*Luleå University of Technology, University Campus, SE-97187 Luleå, Sweden*

Abstract

Keywords: Fiber Reinforced Polymer Composite (FRPC), Debonding, Finite element analysis (FEA)

1. Introduction

Main ref [1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11]

2. Derivation of constitutive relations

2.1. Reference frames

- 5 **Local reference frame of k -th layer:** index 1 is the in-plane longitudinal or fiber or 0° -direction; index 2 is the in-plane transverse or 90° -direction; index 3 is the out-of-plane or through-the-thickness direction.

Global reference frame of laminate: index x is the in-plane longitudinal or laminate 0° direction; index y is the in-plane transverse direction; index
10 z is the out-of-plane or through-the-thickness direction.

2.2. Crack density

Scalar density Normalized volume of cracks V_{an} is the ratio of cracked volume V_a to material volume V

$$V_{an} = \frac{V_a}{V} \quad (1)$$

V_a is equal to the product of total crack surface S_C and average crack opening u_a

$$V_{an} = \frac{S_C u_a}{V} = \frac{S_C}{V} u_a = \rho_C u_a \quad (2)$$

The ratio $\frac{S_C}{V}$ has a size of $\frac{1}{length}$ and correspond to the crack density ρ_C . It means: product of crack density and average crack opening is equal to normalized volume of cracks.

Applying the previous Principle to debonds, we have:

$$\begin{aligned} \rho_D &= \frac{\text{total area of debonds}}{\text{total layer volume}} = \frac{n_D w R_f \Delta \theta}{L_{lam} w t_{90^\circ}} = \frac{n_D \mathcal{W}}{L_{lam} \mathcal{W} t_{90^\circ}} R_f \Delta \theta = \frac{1}{n 2L} \frac{1}{k 2L} R_f \Delta \theta = \\ &= \frac{1}{nk 4L^2} R_f \Delta \theta = \frac{V_f}{nk \pi R_f^2} R_f \Delta \theta = \frac{V_f}{nk R_f} \frac{\Delta \theta}{\pi} \end{aligned} \quad (3)$$

20 Second-order tensor density

Fourth-order tensor density

2.3. Homogenization

$$\sigma_{ij}^{avg} = \frac{1}{V} \int_V \sigma_{ij} dV \quad \varepsilon_{ij}^{avg} = \frac{1}{V} \int_V \varepsilon_{ij} dV \quad (4)$$

$$\tilde{\sigma}_k^{avg} = \tilde{\underline{\underline{Q}}}_k (\tilde{\underline{\underline{\varepsilon}}}_k^{avg} - \tilde{\underline{\underline{\alpha}}}_k \Delta T) \quad (5)$$

$$\tilde{\sigma}_{LAM} = \tilde{\sigma}^{avg} = \frac{1}{V} \int_V \tilde{\sigma} dV = \frac{1}{V} \sum_{k=1}^N \int_{V_k} \tilde{\sigma} dV_k = \sum_{k=1}^N \tilde{\sigma}_k^{avg} \frac{t_k}{h} \quad (6)$$

$$\varepsilon_{ij}^{avg} = \frac{1}{V} \int_V \varepsilon_{ij} dV = \frac{1}{V} \int_V \frac{1}{2} (u_{i,j} + u_{j,i}) dV = \frac{1}{V} \int_S \frac{1}{2} (u_i n_j + u_j n_i) dS \quad (7)$$

$$\begin{aligned}
\varepsilon_{ij}^{avg} &= \frac{1}{V} \int_S \frac{1}{2} (u_i n_j + u_j n_i) dS = \\
&= \frac{1}{V} \int_{S_B} \frac{1}{2} (u_i n_j + u_j n_i) dS + \frac{1}{V} \int_{S_C} \frac{1}{2} (u_i n_j + u_j n_i) dS = \\
&= \varepsilon_{ij}^{applied} + \beta_{ij}
\end{aligned} \tag{8}$$

$$\tilde{\varepsilon}_k^{avg} = \tilde{\varepsilon}_k^{applied} + \tilde{\beta}_{\underline{k}} = \tilde{\varepsilon}_k^{LAM} + \tilde{\beta}_{\underline{k}} \tag{9}$$

$$\tilde{\sigma}_{LAM} = \frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{\underline{k}} \left(\tilde{\varepsilon}_k^{LAM} - \tilde{\alpha}_k \Delta T + \tilde{\beta}_{\underline{k}} \right) \tag{10}$$

$$\tilde{\sigma}_{LAM} = Q_{\underline{\underline{eff}}}^{LAM} \tilde{\varepsilon}^{LAM} \tag{11}$$

$$Q_{\underline{\underline{eff}}}^{LAM} \tilde{\varepsilon}^{LAM} = \left(\frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{\underline{k}} \right) \tilde{\varepsilon}^{LAM} + \frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{\underline{k}} \tilde{\beta}_{\underline{k}} \tag{12}$$

$$Q_{\underline{\underline{eff}}}^{LAM} \tilde{\varepsilon}^{LAM} \cdot \frac{\tilde{\varepsilon}^{LAM}}{\tilde{\varepsilon}^{LAM} \cdot \tilde{\varepsilon}^{LAM}} = \left(\frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{\underline{k}} \right) \tilde{\varepsilon}^{LAM} \cdot \frac{\tilde{\varepsilon}^{LAM}}{\tilde{\varepsilon}^{LAM} \cdot \tilde{\varepsilon}^{LAM}} + \left(\frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{\underline{k}} \tilde{\beta}_{\underline{k}} \right) \cdot \frac{\tilde{\varepsilon}^{LAM}}{\tilde{\varepsilon}^{LAM} \cdot \tilde{\varepsilon}^{LAM}} \tag{13}$$

$$Q_{\underline{\underline{eff}}}^{LAM} = \left(\frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{\underline{k}} \right) + \frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{\underline{k}} \frac{\tilde{\beta}_{\underline{k}} \cdot \tilde{\varepsilon}^{LAM}}{\tilde{\varepsilon}^{LAM} \cdot \tilde{\varepsilon}^{LAM}} \tag{14}$$

$$T_{\underline{k}} = \begin{bmatrix} \cos^2(\theta_k) & \sin^2(\theta_k) & 2 \cos(\theta_k) \sin(\theta_k) \\ \sin^2(\theta_k) & \cos^2(\theta_k) & -2 \cos(\theta_k) \sin(\theta_k) \\ -\cos(\theta_k) \sin(\theta_k) & \cos(\theta_k) \sin(\theta_k) & \cos^2(\theta_k) - \sin^2(\theta_k) \end{bmatrix} \tag{15}$$

$$\tilde{Q}_{\underline{k}} = T_{\underline{k}}^{-1} Q_{\underline{k}} \left(T_{\underline{k}}^{-1} \right)^T \tag{16}$$

$$\begin{aligned}
Q_{\underline{\underline{eff}}}^{LAM} &= \left(\frac{1}{h} \sum_{k=1}^N t_k T_{\underline{k}}^{-1} Q_{\underline{k}} \left(T_{\underline{k}}^{-1} \right)^T \right) + \frac{1}{h} \sum_{k=1}^N t_k T_{\underline{k}}^{-1} Q_{\underline{k}} \left(T_{\underline{k}}^{-1} \right)^T \frac{T_{\underline{k}}^{-1} \tilde{\beta}_{\underline{k}} \left(T_{\underline{k}}^{-1} \right)^T \cdot \tilde{\varepsilon}^{LAM}}{\tilde{\varepsilon}^{LAM} \cdot \tilde{\varepsilon}^{LAM}} = \\
&= \frac{1}{h} \sum_{k=1}^N t_k T_{\underline{k}}^{-1} Q_{\underline{k}} \left(T_{\underline{k}}^{-1} \right)^T \left(1 + \frac{T_{\underline{k}}^{-1} \tilde{\beta}_{\underline{k}} \left(T_{\underline{k}}^{-1} \right)^T \cdot \tilde{\varepsilon}^{LAM}}{\tilde{\varepsilon}^{LAM} \cdot \tilde{\varepsilon}^{LAM}} \right)
\end{aligned} \tag{17}$$

$$Q_{eff,lmij}^{LAM} \tilde{\varepsilon}_{ij}^{LAM} = \left(\frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{k,lmij} \right) \tilde{\varepsilon}_{ij}^{LAM} + \frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{k,lmij} \tilde{\beta}_{k,ij} \quad (18)$$

$$Q_{eff,lmij}^{LAM} \tilde{\varepsilon}_{ij}^{LAM} (\tilde{\varepsilon}_{ij}^{LAM})^{-1} = \left(\frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{k,lmij} \right) \tilde{\varepsilon}_{ij}^{LAM} (\tilde{\varepsilon}_{ij}^{LAM})^{-1} + \frac{1}{h} \left(\sum_{k=1}^N t_k \tilde{Q}_{k,lmij} \tilde{\beta}_{k,ij} \right) (\tilde{\varepsilon}_{ij}^{LAM})^{-1} \quad (19)$$

$$Q_{eff,lmij}^{LAM} = \left(\frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{k,lmij} \right) + \frac{1}{h} \sum_{k=1}^N t_k \left(\tilde{Q}_{k,lmij} \tilde{\beta}_{k,ij} (\tilde{\varepsilon}_{ij}^{LAM})^{-1} \right) \quad (20)$$

$$Q_{eff,lmij}^{LAM} = \frac{1}{h} \sum_{k=1}^N t_k \tilde{Q}_{k,lmij} \left(\frac{1}{2} (\delta_{ik} \delta_{jl} + \delta_{il} \delta_{jk}) + \tilde{\beta}_{k,ij} (\tilde{\varepsilon}_{ij}^{LAM})^{-1} \right) \quad (21)$$

$$Q_{eff,lmij}^{LAM} = \frac{1}{h} \sum_{k=1}^N t_k T_{k,lmrs}^{-1} Q_{k,rs pq} \left(\underline{T}_k^{-1} \right)_{pqij}^T \left(\frac{1}{2} (\delta_{ik} \delta_{jl} + \delta_{il} \delta_{jk}) + T_{k,ip}^{-1} \tilde{\beta}_{k,pq} \left(\underline{T}_k^{-1} \right)_{qj}^T T_{k,lmrs}^{-1} (\tilde{\varepsilon}_{pq}^{LAM})^{-1} \left(\underline{T}_k^{-1} \right)_{qj}^T \right) \quad (22)$$

2.4. Exact expression of the Vakulenko-Kachanov tensor

In the local reference frame of k -th layer, the outer normal at crack faces
 25 has components:

$$n_1 = 0 \quad n_2 \neq 0 \quad n_3 \neq 0 \quad (23)$$

while crack face displacement has components:

$$u_1 = 0 \quad u_2 \neq 0 \quad u_3 \neq 0 \quad (24)$$

Definition of Vakulenko-Kachanov tensor:

$$\beta_{ij} = \frac{1}{V_k} \int_{S_C} \frac{1}{2} (u_i n_j + u_j n_i) dS \quad (25)$$

Expand the expression for each component and simplify based on the fact that $u_1 = 0$:

$$\begin{aligned}
\beta_{11} &= \frac{1}{V_k} \int_{S_C} \frac{1}{2} (u_1 n_1 + u_1 n_1) dS = \frac{1}{V_k} \int_{S_C} \mu_1^{\rightarrow 0} n_1 dS = 0 \\
\beta_{22} &= \frac{1}{V_k} \int_{S_C} \frac{1}{2} (u_2 n_2 + u_2 n_2) dS = \frac{1}{V_k} \int_{S_C} u_2 n_2 dS \\
\beta_{33} &= \frac{1}{V_k} \int_{S_C} \frac{1}{2} (u_3 n_3 + u_3 n_3) dS = \frac{1}{V_k} \int_{S_C} u_3 n_3 dS \\
\beta_{12} &= \frac{1}{V_k} \int_{S_C} \frac{1}{2} (\mu_1^{\rightarrow 0} n_2 + u_2 \mu_1^{\rightarrow 0}) dS = 0 \\
\beta_{13} &= \frac{1}{V_k} \int_{S_C} \frac{1}{2} (\mu_1^{\rightarrow 0} n_3 + u_3 \mu_1^{\rightarrow 0}) dS = 0 \\
\beta_{23} &= \frac{1}{V_k} \int_{S_C} \frac{1}{2} (u_2 n_3 + u_3 n_2) dS \\
\beta_{21} &= \frac{1}{V_k} \int_{S_C} \frac{1}{2} (u_2 \mu_1^{\rightarrow 0} + \mu_1^{\rightarrow 0} n_2) dS = 0 \\
\beta_{31} &= \frac{1}{V_k} \int_{S_C} \frac{1}{2} (u_3 \mu_1^{\rightarrow 0} + \mu_1^{\rightarrow 0} n_3) dS = 0 \\
\beta_{32} &= \frac{1}{V_k} \int_{S_C} \frac{1}{2} (u_3 n_2 + u_2 n_3) dS = \beta_{23}
\end{aligned} \tag{26}$$

30 Only 3 independent components of the tensor β_{ij} remain: β_{22} , β_{33} and β_{23} . Split total crack surface S_C into total matrix crack surface S_C^m and total fiber

crack surface S_C^f and remember that $n_i^f = -n_i^m$ for $i = 2, 3$

$$\begin{aligned}
\beta_{22} &= \frac{1}{V_k} \int_{S_C} u_2 n_2 dS = \frac{1}{V_k} \left[\int_{S_C^m} u_2^m n_2^m dS + \int_{S_C^f} u_2^f n_2^f dS \right] = \\
&= \frac{1}{V_k} \left[\int_{S_C^m} u_2^m n_2^m dS + \int_{S_C^f} u_2^f (-n_2^m) dS \right] \\
\beta_{33} &= \frac{1}{V_k} \int_{S_C} u_3 n_3 dS = \frac{1}{V_k} \left[\int_{S_C^m} u_3^m n_3^m dS + \int_{S_C^f} u_3^f n_3^f dS \right] = \\
&= \frac{1}{V_k} \left[\int_{S_C^m} u_3^m n_3^m dS + \int_{S_C^f} u_3^f (-n_3^m) dS \right] \\
\beta_{23} &= \frac{1}{V_k} \int_{S_C} (u_2 n_3 + u_3 n_2) dS = \\
&= \frac{1}{V_k} \left[\int_{S_C^m} (u_2^m n_3^m + u_3^m n_2^m) dS + \int_{S_C^f} (u_2^f n_3^f + u_3^f n_2^f) dS \right] = \\
&= \frac{1}{V_k} \left[\int_{S_C^m} u_2^m n_3^m dS + \int_{S_C^f} u_2^f (-n_3^m) dS + \int_{S_C^m} u_3^m n_2^m dS + \int_{S_C^f} u_3^f (-n_2^m) dS \right] \\
&\hspace{15em} (27)
\end{aligned}$$

The total matrix debonded surface S_C^m is equal to the total fiber debonded surface S_C^f and equal to:

$$S_C^m = S_C^f = n_D R_f \Delta \theta \quad (28)$$

With Eq. 28, we can recast Eq. 27 as

$$\begin{aligned}
\beta_{22} &= \frac{1}{V_k} \left[n_D R_f w \int_0^{\Delta\theta} (u_2^m - u_2^f) n_2^m d\theta \right] = \\
&= \frac{1}{L_{lam} w t_{90^\circ}} \left[n_D R_f w \int_0^{\Delta\theta} (u_2^m - u_2^f) n_2^m d\theta \right] = \\
&= \frac{1}{L_{lam}} \frac{n_D R_f}{t_{90^\circ}} \left[\int_0^{\Delta\theta} (u_2^m - u_2^f) n_2^m d\theta \right] = \\
&= \rho_D \left[\frac{1}{\Delta\theta} \int_0^{\Delta\theta} (u_2^m - u_2^f) n_2^m d\theta \right] \\
\beta_{33} &= \rho_D \left[\frac{1}{\Delta\theta} \int_0^{\Delta\theta} (u_3^m - u_3^f) n_3^m d\theta \right] \\
\beta_{23} &= \rho_D \left[\frac{1}{\Delta\theta} \int_0^{\Delta\theta} (u_2^m - u_2^f) n_3^m d\theta + \frac{1}{\Delta\theta} \int_0^{\Delta\theta} (u_3^m - u_3^f) n_2^m d\theta \right]
\end{aligned} \tag{29}$$

We can express the displacement jumps at the interface as a function of the local Crack Opening Displacement (COD) and Crack Sliding Displacement (CSD) as

$$\begin{aligned}
u_2^m - u_2^f &= (u_r^m - u_r^f) \cos(\theta) - (u_\theta^m - u_\theta^f) \sin(\theta) = \\
&= COD(\theta) \cos(\theta) - CSD(\theta) \sin(\theta) \\
u_3^m - u_3^f &= (u_r^m - u_r^f) \sin(\theta) + (u_\theta^m - u_\theta^f) \cos(\theta) = \\
&= COD(\theta) \sin(\theta) + CSD(\theta) \cos(\theta)
\end{aligned} \tag{30}$$

where θ is the local angular coordinate at the interface. We can similarly
40 express n_2^m and n_3^m as a function of θ :

$$\begin{aligned}
n_2^m &= \cos(\theta) - \sin(\theta) \\
n_3^m &= \sin(\theta) + \cos(\theta)
\end{aligned} \tag{31}$$

Thus, Eq. 29 becomes

$$\begin{aligned}
& \beta_{22} = \\
& = \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} [COD(\theta) (\cos^2(\theta) - \cos(\theta) \sin(\theta)) - CSD(\theta) (\sin(\theta) \cos(\theta) - \sin^2(\theta))] d\theta = \\
& = \rho_D \frac{1}{2\Delta\theta} \int_0^{\Delta\theta} [COD(\theta) (1 + \cos(2\theta) - \sin(2\theta)) + CSD(\theta) (1 - \cos(2\theta) - \sin(2\theta))] d\theta = \\
& = \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left[\frac{COD(\theta) + CSD(\theta)}{2} (1 - \sin(2\theta)) + \frac{COD(\theta) - CSD(\theta)}{2} \cos(2\theta) \right] d\theta \\
& \beta_{33} = \\
& = \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} [COD(\theta) (\sin(\theta) \cos(\theta) + \sin^2(\theta)) + CSD(\theta) (\cos^2(\theta) + \cos(\theta) \sin(\theta))] d\theta = \\
& = \rho_D \frac{1}{2\Delta\theta} \int_0^{\Delta\theta} [COD(\theta) (1 + \sin(2\theta) - \cos(2\theta)) + CSD(\theta) (1 + \sin(2\theta) + \cos(2\theta))] d\theta = \\
& = \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left[\frac{COD(\theta) + CSD(\theta)}{2} (1 + \sin(2\theta)) - \frac{COD(\theta) - CSD(\theta)}{2} \cos(2\theta) \right] d\theta \\
& \beta_{23} = \\
& = \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} COD(\theta) (2 \sin(\theta) \cos(\theta) + \cos^2(\theta) - \sin^2(\theta)) + \\
& \quad - \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} CSD(\theta) (\sin^2(\theta) - \cos^2(\theta) + 2 \cos(\theta) \sin(\theta)) d\theta = \\
& = \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} 2 \left[\frac{COD(\theta) + CSD(\theta)}{2} \cos(2\theta) + \frac{COD(\theta) - CSD(\theta)}{2} \sin(2\theta) \right] d\theta \\
& \hspace{25em} (32)
\end{aligned}$$

2.5. Analytical modeling of $COD(\theta)$ and $CSD(\theta)$

The Crack Opening Displacement (COD) and Crack Sliding Displacement (CSD) are in general a function of θ , the angular coordinate along the crack
45 which varies between 0 and $\Delta\theta$. Without making any approximation, the Crack Opening Displacement (COD) and Crack Sliding Displacement (CSD) can be expressed as the sum of their average value and a term, respectively $\delta COD(\theta)$

and $\delta CSD(\theta)$, that represents the variation of the function from its average:

$$\begin{aligned} COD(\theta) &= COD_{avg} + \delta COD(\theta) \\ CSD(\theta) &= CSD_{avg} + \delta CSD(\theta). \end{aligned} \quad (33)$$

By defining $\Delta\Psi$

$$\Delta\Psi = \min(\Delta\theta, \Delta\Phi), \quad (34)$$

50 we introduce at this point an approximation and assume that the functions $\delta COD(\theta)$ and $\delta CSD(\theta)$ can be expressed as the product of the maximum value of the displacement and a function, respectively $f\left(\theta - \frac{\Delta\Psi}{2}\right)$ and $g\left(\theta - \frac{\Delta\theta}{2}\right)$:

$$\begin{aligned} COD(\theta) &= COD_{avg} + \delta COD(\theta) = COD_{avg} + COD_{max} f\left(\theta - \frac{\Delta\Psi}{2}\right) \\ CSD(\theta) &= CSD_{avg} + \delta CSD(\theta) = CSD_{avg} + CSD_{max} g\left(\theta - \frac{\Delta\theta}{2}\right), \end{aligned} \quad (35)$$

where $f\left(\theta - \frac{\Delta\Psi}{2}\right)$ and $g\left(\theta - \frac{\Delta\theta}{2}\right)$ are assumed to be odd functions over their respective integration domain $[0, \Delta\Psi]$ and $[0, \Delta\theta]$

$$\int_0^{\Delta\theta} f\left(\theta - \frac{\Delta\Psi}{2}\right) d\theta = 0 \quad \int_0^{\Delta\theta} g\left(\theta - \frac{\Delta\theta}{2}\right) d\theta = 0. \quad (36)$$

55 We assume the two functions $f\left(\theta - \frac{\Delta\Psi}{2}\right)$ and $g\left(\theta - \frac{\Delta\theta}{2}\right)$ to be two odd polynomials of degree $2n - 1$:

$$\begin{aligned} f\left(\theta - \frac{\Delta\Psi}{2}\right) &= \begin{cases} \sum_{k=0}^{n-1} a_{2k+1} \left(\theta - \frac{\Delta\Psi}{2}\right)^{2k+1} & 0 \leq \theta \leq \Delta\Psi \\ 0 & otherwise \end{cases} \\ g\left(\theta - \frac{\Delta\theta}{2}\right) &= \begin{cases} \sum_{k=0}^{n-1} b_{2k+1} \left(\theta - \frac{\Delta\theta}{2}\right)^{2k+1} & 0 \leq \theta \leq \Delta\theta \\ 0 & otherwise \end{cases} \end{aligned} \quad (37)$$

which satisfy by construction the conditions expressed in Equation 36. The coefficients a_{2k+1} and b_{2k+1} are determined by imposing that

$$\begin{aligned} COD(\Delta\Psi) &= 0 \\ CSD(\Delta\theta) &= 0. \end{aligned} \quad (38)$$

The explicit construction of the polynomials $f\left(\theta - \frac{\Delta\Psi}{2}\right)$ and $g\left(\theta - \frac{\Delta\theta}{2}\right)$ for
⁶⁰ $n = 1, 2, 3$ (or degree $2n - 1 = 1, 3, 5$) is reported in Appendix A.

We recall the expressions of the non-zero components of the Vakulenko-Kachanov tensor

$$\begin{aligned}
\beta_{22} &= \\
&= \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left[\frac{COD(\theta) + CSD(\theta)}{2} (1 - \sin(2\theta)) + \frac{COD(\theta) - CSD(\theta)}{2} \cos(2\theta) \right] d\theta \\
\beta_{33} &= \\
&= \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left[\frac{COD(\theta) + CSD(\theta)}{2} (1 + \sin(2\theta)) - \frac{COD(\theta) - CSD(\theta)}{2} \cos(2\theta) \right] d\theta \\
\beta_{23} &= \\
&= \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} 2 \left[\frac{COD(\theta) + CSD(\theta)}{2} \cos(2\theta) + \frac{COD(\theta) - CSD(\theta)}{2} \sin(2\theta) \right] d\theta
\end{aligned} \tag{39}$$

and proceed to the integration of the different summands:

1.

$$\begin{aligned}
& \frac{1}{\Delta\theta} \int_0^{\Delta\theta} COD(\theta) d\theta = \\
& = \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left(COD_{avg} + COD_{max} \sum_{k=0}^{n-1} a_{2k+1} \left(\theta - \frac{\Delta\Psi}{2} \right)^{2k+1} \right) d\theta = \\
& = \frac{1}{\Delta\theta} \int_0^{\Delta\theta} COD_{avg} d\theta + \\
& + \frac{1}{\Delta\theta} \int_0^{\Delta\Psi} COD_{max} \sum_{k=0}^{n-1} a_{2k+1} \left(\theta - \frac{\Delta\Psi}{2} \right)^{2k+1} d\theta + \\
& + \frac{1}{\Delta\theta} \int_{\Delta\Psi}^{\Delta\theta} COD_{max} \sum_{k=0}^{n-1} a_{2k+1} \left(\theta - \frac{\Delta\Psi}{2} \right)^{2k+1} d\theta = \\
& = \frac{1}{\Delta\theta} [COD_{avg}\theta] \Big|_0^{\Delta\theta} + \frac{1}{\Delta\theta} \left[COD_{max} \sum_{k=0}^{n-1} \frac{a_{2k+1}}{2(k+1)} \left(\theta - \frac{\Delta\Psi}{2} \right)^{2(k+1)} \right] \Big|_0^{\Delta\Psi} = \\
& = COD_{avg} + COD_{max} \sum_{k=0}^{n-1} \frac{a_{2k+1}}{2(k+1)\Delta\theta} \left(\left(\frac{\Delta\Psi}{2} \right)^{2(k+1)} - \left(-\frac{\Delta\Psi}{2} \right)^{2(k+1)} \right) = \\
& = COD_{avg}
\end{aligned} \tag{40}$$

2.

$$\frac{1}{\Delta\theta} \int_0^{\Delta\theta} CSD(\theta) d\theta = CSD_{avg} \tag{41}$$

3.

$$\begin{aligned}
& \frac{1}{\Delta\theta} \int_0^{\Delta\theta} COD(\theta) \sin(2\theta) d\theta = \\
& = \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left(COD_{avg} + COD_{max} \sum_{k=0}^{n-1} a_{2k+1} \theta^{2k+1} \right) \sin(2\theta) d\theta = \\
& = -\frac{1}{2\Delta\theta} COD_{avg} [\cos(2\theta)] \Big|_0^{\Delta\theta} + \\
& + \frac{1}{\Delta\theta} \left[COD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2} \right)^{i+1} \sin\left(\frac{1+\text{mod}(i,2)}{2} \pi - 2\theta \right) \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \theta^{k-i} \right) \right] \Big|_0^{\Delta\Psi} = \\
& = \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} COD_{avg} + \\
& + \frac{1}{\Delta\theta} COD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2} \right)^{i+1} \sin\left(\frac{1+\text{mod}(i,2)}{2} \pi - 2\Delta\Psi \right) \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i} \right)
\end{aligned} \tag{42}$$

4.

$$\begin{aligned}
& \frac{1}{\Delta\theta} \int_0^{\Delta\theta} CSD(\theta) \sin(2\theta) d\theta = \\
& = \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left(CSD_{avg} + CSD_{max} \sum_{k=0}^{n-1} b_{2k+1} \theta^{2k+1} \right) \sin(2\theta) d\theta = \\
& = -\frac{1}{2\Delta\theta} CSD_{avg} [\cos(2\theta)] \Big|_0^{\Delta\theta} + \\
& + \frac{1}{\Delta\theta} \left[CSD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2} \right)^{i+1} \sin\left(\frac{1+\text{mod}(i,2)}{2}\pi - 2\theta\right) \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \theta^{k-i} \right) \right] \Big|_0^{\Delta\theta} = \\
& = \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} CSD_{avg} + \\
& + \frac{1}{\Delta\theta} CSD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2} \right)^{i+1} \sin\left(\frac{1+\text{mod}(i,2)}{2}\pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i} \right)
\end{aligned} \tag{43}$$

5.

$$\begin{aligned}
& \frac{1}{\Delta\theta} \int_0^{\Delta\theta} COD(\theta) \cos(2\theta) d\theta = \\
& = \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left(COD_{avg} + COD_{max} \sum_{k=0}^{n-1} a_{2k+1} \theta^{2k+1} \right) \cos(2\theta) d\theta = \\
& = \frac{1}{2\Delta\theta} COD_{avg} [\sin(2\theta)] \Big|_0^{\Delta\theta} + \\
& + \frac{1}{\Delta\theta} \left[COD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2} \right)^i \sin\left(\frac{1+\text{mod}(i+1,2)}{2}\pi - 2\theta\right) \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \theta^{k-i} \right) \right] \Big|_0^{\Delta\theta} = \\
& = \frac{\sin(2\Delta\theta)}{2\Delta\theta} COD_{avg} + \\
& + \frac{1}{\Delta\theta} COD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2} \right)^i \sin\left(\frac{1+\text{mod}(i+1,2)}{2}\pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i} \right)
\end{aligned} \tag{44}$$

6.

$$\begin{aligned}
& \frac{1}{\Delta\theta} \int_0^{\Delta\theta} CSD(\theta) \cos(2\theta) d\theta = \\
& = \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left(CSD_{avg} + CSD_{max} \sum_{k=0}^{n-1} b_{2k+1} \theta^{2k+1} \right) \cos(2\theta) d\theta = \\
& = -\frac{1}{2\Delta\theta} CSD_{avg} [\cos(2\theta)] \Big|_0^{\Delta\theta} + \\
& + \frac{1}{\Delta\theta} \left[CSD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2} \right)^i \sin\left(\frac{1 + \text{mod}(i+1, 2)}{2} \pi - 2\theta \right) \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \theta^{k-i} \right) \right] \Big|_0^{\Delta\theta} = \\
& = \frac{\sin(2\Delta\theta)}{2\Delta\theta} CSD_{avg} + \\
& + \frac{1}{\Delta\theta} CSD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2} \right)^i \sin\left(\frac{1 + \text{mod}(i+1, 2)}{2} \pi - 2\Delta\theta \right) \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\theta^{k-i} \right) \\
& \hspace{15em} (45)
\end{aligned}$$

Finally we can compute the expressions of the components of the Vakulenko-

65 Kachanov tensor:

1. β_{22}

$$\begin{aligned}
\beta_{22} &= \\
&= \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left[\frac{COD(\theta) + CSD(\theta)}{2} (1 - \sin(2\theta)) + \frac{COD(\theta) - CSD(\theta)}{2} \cos(2\theta) \right] d\theta \\
&= \frac{\rho_D}{2} (COD_{avg} + CSD_{avg}) + \\
&\quad - \frac{\rho_D}{2} \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} COD_{avg} - \frac{\rho_D}{2} \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} CSD_{avg} + \\
&\quad - \frac{\rho_D}{2} \frac{1}{\Delta\theta} COD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1 + \text{mod}(i, 2)}{2} \pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&\quad - \frac{\rho_D}{2} \frac{1}{\Delta\theta} CSD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1 + \text{mod}(i, 2)}{2} \pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&\quad + \frac{\rho_D}{2} \frac{\sin(2\Delta\theta)}{2\Delta\theta} COD_{avg} + \\
&\quad + \frac{\rho_D}{2} \frac{1}{\Delta\theta} COD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^i \sin\left(\frac{1 + \text{mod}(i+1, 2)}{2} \pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&\quad - \frac{\rho_D}{2} \frac{\sin(2\Delta\theta)}{2\Delta\theta} CSD_{avg} + \\
&\quad - \frac{\rho_D}{2} \frac{1}{\Delta\theta} CSD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^i \sin\left(\frac{1 + \text{mod}(i+1, 2)}{2} \pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) = \\
&= \frac{\rho_D}{2} COD_{avg} \left(1 - \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} + \frac{\sin(2\Delta\theta)}{2\Delta\theta}\right) + \\
&\quad + \frac{\rho_D}{2} CSD_{avg} \left(1 - \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} - \frac{\sin(2\Delta\theta)}{2\Delta\theta}\right) + \\
&\quad + \frac{\rho_D}{2} COD_{max} \frac{1}{\Delta\theta} \sum_{i=0}^{2n-1} \left(\left(-\frac{1}{2}\right)^i \sin\left(\frac{1 + \text{mod}(i+1, 2)}{2} \pi - 2\Delta\Psi\right) - \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1 + \text{mod}(i, 2)}{2} \pi - 2\Delta\Psi\right) \right) \cdot \\
&\quad \cdot \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&\quad - \frac{\rho_D}{2} CSD_{max} \frac{1}{\Delta\theta} \sum_{i=0}^{2n-1} \left(\left(-\frac{1}{2}\right)^i \sin\left(\frac{1 + \text{mod}(i+1, 2)}{2} \pi - 2\Delta\Psi\right) + \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1 + \text{mod}(i, 2)}{2} \pi - 2\Delta\Psi\right) \right) \cdot \\
&\quad \cdot \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right)
\end{aligned} \tag{46}$$

2. β_{33}

$$\begin{aligned}
\beta_{33} &= \\
&= \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} \left[\frac{COD(\theta) + CSD(\theta)}{2} (1 + \sin(2\theta)) - \frac{COD(\theta) - CSD(\theta)}{2} \cos(2\theta) \right] d\theta = \\
&= \frac{\rho_D}{2} (COD_{avg} + CSD_{avg}) + \\
&+ \frac{\rho_D}{2} \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} COD_{avg} + \frac{\rho_D}{2} \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} CSD_{avg} + \\
&+ \frac{\rho_D}{2} \frac{1}{\Delta\theta} COD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1 + \text{mod}(i, 2)}{2} \pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&+ \frac{\rho_D}{2} \frac{1}{\Delta\theta} CSD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1 + \text{mod}(i, 2)}{2} \pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&- \frac{\rho_D}{2} \frac{\sin(2\Delta\theta)}{2\Delta\theta} COD_{avg} + \\
&- \frac{\rho_D}{2} \frac{1}{\Delta\theta} COD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^i \sin\left(\frac{1 + \text{mod}(i+1, 2)}{2} \pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&+ \frac{\rho_D}{2} \frac{\sin(2\Delta\theta)}{2\Delta\theta} CSD_{avg} + \\
&+ \frac{\rho_D}{2} \frac{1}{\Delta\theta} CSD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^i \sin\left(\frac{1 + \text{mod}(i+1, 2)}{2} \pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) = \\
&= \frac{\rho_D}{2} COD_{avg} \left(1 + \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} - \frac{\sin(2\Delta\theta)}{2\Delta\theta}\right) + \\
&+ \frac{\rho_D}{2} CSD_{avg} \left(1 - \frac{1 + \cos(2\Delta\theta)}{2\Delta\theta} + \frac{\sin(2\Delta\theta)}{2\Delta\theta}\right) + \\
&+ \frac{\rho_D}{2} COD_{max} \frac{1}{\Delta\theta} \sum_{i=0}^{2n-1} \left(\left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1 + \text{mod}(i, 2)}{2} \pi - 2\Delta\Psi\right) - \left(-\frac{1}{2}\right)^i \sin\left(\frac{1 + \text{mod}(i+1, 2)}{2} \pi - 2\Delta\Psi\right) \right) \cdot \\
&\quad \cdot \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i} \right) + \\
&+ \frac{\rho_D}{2} CSD_{max} \frac{1}{\Delta\theta} \sum_{i=0}^{2n-1} \left(\left(-\frac{1}{2}\right)^i \sin\left(\frac{1 + \text{mod}(i+1, 2)}{2} \pi - 2\Delta\Psi\right) + \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1 + \text{mod}(i, 2)}{2} \pi - 2\Delta\Psi\right) \right) \cdot \\
&\quad \cdot \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i} \right)
\end{aligned} \tag{47}$$

3. β_{23}

$$\begin{aligned}
\beta_{23} &= \\
&= \rho_D \frac{1}{\Delta\theta} \int_0^{\Delta\theta} 2 \left[\frac{COD(\theta) + CSD(\theta)}{2} \cos(2\theta) + \frac{COD(\theta) - CSD(\theta)}{2} \sin(2\theta) \right] d\theta = \\
&= \frac{\rho_D}{2} \frac{\sin(2\Delta\theta)}{2\Delta\theta} COD_{avg} + \\
&+ \frac{\rho_D}{2} \frac{1}{\Delta\theta} COD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^i \sin\left(\frac{1+mod(i+1,2)}{2}\pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&+ \frac{\rho_D}{2} \frac{\sin(2\Delta\theta)}{2\Delta\theta} CSD_{avg} + \\
&+ \frac{\rho_D}{2} \frac{1}{\Delta\theta} CSD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^i \sin\left(\frac{1+mod(i+1,2)}{2}\pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&+ \frac{\rho_D}{2} \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} COD_{avg} - \frac{\rho_D}{2} \frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} CSD_{avg} + \\
&+ \frac{\rho_D}{2} \frac{1}{\Delta\theta} COD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1+mod(i,2)}{2}\pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&- \frac{\rho_D}{2} \frac{1}{\Delta\theta} CSD_{max} \sum_{i=0}^{2n-1} \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1+mod(i,2)}{2}\pi - 2\Delta\Psi\right) \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) = \\
&= \frac{\rho_D}{2} COD_{avg} \left(\frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} + \frac{\sin(2\Delta\theta)}{2\Delta\theta}\right) + \\
&- \frac{\rho_D}{2} CSD_{avg} \left(\frac{1 - \cos(2\Delta\theta)}{2\Delta\theta} - \frac{\sin(2\Delta\theta)}{2\Delta\theta}\right) + \\
&+ \frac{\rho_D}{2} COD_{max} \frac{1}{\Delta\theta} \sum_{i=0}^{2n-1} \left(\left(-\frac{1}{2}\right)^i \sin\left(\frac{1+mod(i+1,2)}{2}\pi - 2\Delta\Psi\right) + \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1+mod(i,2)}{2}\pi - 2\Delta\Psi\right)\right) \cdot \\
&\quad \cdot \left(\sum_{k=i}^{2n-1} a_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right) + \\
&+ \frac{\rho_D}{2} CSD_{max} \frac{1}{\Delta\theta} \sum_{i=0}^{2n-1} \left(\left(-\frac{1}{2}\right)^i \sin\left(\frac{1+mod(i+1,2)}{2}\pi - 2\Delta\Psi\right) - \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1+mod(i,2)}{2}\pi - 2\Delta\Psi\right)\right) \cdot \\
&\quad \cdot \left(\sum_{k=i}^{2n-1} b_k \frac{k!}{(k-i)!} \Delta\Psi^{k-i}\right)
\end{aligned} \tag{48}$$

2.6. *Application to UD composite*

70 2.7. *Application to $[0_{mk}^\circ, 90_k^\circ, 0_{mk}^\circ]$ laminate*

3. Computations with the Finite Element Method (FEM)

3.1. *Models of Representative Volume Element (RVE)*

3.2. *Details of FEM implementation*

4. Results and discussion

75 5. Conclusions

References

- [1] P. Lundmark, J. Varna, Modeling thermo-mechanical properties of damaged laminates, *Key Engineering Materials* 251-252 (2003) 381–388. doi:10.4028/www.scientific.net/kem.251-252.381.
- 80 [2] P. Lundmark, J. Varna, Crack face sliding effect on stiffness of laminates with ply cracks, *Composites Science and Technology* 66 (10) (2006) 1444–1454. doi:10.1016/j.compscitech.2005.08.016.
- [3] J. Varna, Modelling mechanical performance of damaged laminates, *Journal of Composite Materials* 47 (20-21) (2012) 2443–2474. doi:10.1177/0021998312469241.
- 85 [4] M. S. Loukil, J. Varna, Z. Ayadi, Applicability of solutions for periodic intralaminar crack distributions to non-uniformly damaged laminates, *Journal of Composite Materials* 47 (3) (2012) 287–301. doi:10.1177/0021998312440126.
- 90 [5] M. S. Loukil, W. Hussain, A. Kirti, A. Pupurs, J. Varna, Thermoelastic constants of symmetric laminates with cracks in 90-layer: application of simple models, *Plastics, Rubber and Composites* 42 (4) (2013) 157–166. doi:10.1179/1743289811y.00000000064.

- [6] M. S. Loukil, J. Varna, Z. Ayadi, Engineering expressions for thermo-elastic constants of laminates with high density of transverse cracks, *Composites Part A: Applied Science and Manufacturing* 48 (2013) 37–46. doi:10.1016/j.compositesa.2012.12.012.
- [7] J. Varna, M. S. Loukil, Effective transverse modulus of a damaged layer: Potential for predicting symmetric laminate stiffness degradation, *Journal of Composite Materials* 51 (14) (2016) 1945–1959. doi:10.1177/0021998316658965.
- [8] A. Pupurs, J. Varna, M. Loukil, H. B. Kahla, D. Mattsson, Effective stiffness concept in bending modeling of laminates with damage in surface layers, *Composites Part A: Applied Science and Manufacturing* 82 (2016) 244–252. doi:10.1016/j.compositesa.2015.11.012.
- [9] J. Varna, 2.10 crack separation based models for microcracking, in: P. W. Beaumont, C. H. Zweben (Eds.), *Comprehensive Composite Materials II*, Elsevier, Oxford, 2018, pp. 192 – 220. doi:10.1016/B978-0-12-803581-8.09910-0.
- [10] M. S. Loukil, J. Varna, Effective shear modulus of a damaged ply in laminate stiffness analysis: Determination and validation, *Journal of Composite Materials* (2019) 002199831987436doi:10.1177/0021998319874369.
- [11] M. S. Loukil, J. Varna, Crack face sliding displacement (CSD) as an input in exact GLOB-LOC expressions for in-plane elastic constants of symmetric damaged laminates, *International Journal of Damage Mechanics* (2019) 105678951986600doi:10.1177/1056789519866000.

Appendix A. Explicit expressions for $f(\theta)$ and $g(\theta)$

In the following, recall that

$$\Delta\Psi = \min(\Delta\theta, \Delta\Phi). \quad (\text{A.1})$$

$$\mathbf{n} = \mathbf{1}$$

$$\begin{aligned} f\left(\theta - \frac{\Delta\Psi}{2}\right) &= \sum_{k=0}^0 a_{2k+1} \left(\theta - \frac{\Delta\Psi}{2}\right)^{2k+1} = a_1 \left(\theta - \frac{\Delta\Psi}{2}\right) \\ g\left(\theta - \frac{\Delta\theta}{2}\right) &= \sum_{k=0}^0 b_{2k+1} \left(\theta - \frac{\Delta\theta}{2}\right)^{2k+1} = b_1 \left(\theta - \frac{\Delta\theta}{2}\right) \end{aligned} \quad (\text{A.2})$$

$$\begin{aligned} \int_0^{\Delta\Psi} f\left(\theta - \frac{\Delta\Psi}{2}\right) d\theta &= \int_0^{\Delta\Psi} a_1 \left(\theta - \frac{\Delta\Psi}{2}\right) d\theta = \left[\frac{a_1}{2} \theta^2 - a_1 \frac{\Delta\Psi}{2} \theta \right]_0^{\Delta\Psi} = 0 \quad \forall a_1 \\ \int_0^{\Delta\theta} g\left(\theta - \frac{\Delta\theta}{2}\right) d\theta &= \int_0^{\Delta\theta} b_1 \left(\theta - \frac{\Delta\theta}{2}\right) d\theta = \left[\frac{b_1}{2} \theta^2 - b_1 \frac{\Delta\theta}{2} \theta \right]_0^{\Delta\theta} = 0 \quad \forall b_1 \end{aligned} \quad (\text{A.3})$$

$$\begin{aligned} COD_{avg} + COD_{max} a_1 \left(\Delta\Psi - \frac{\Delta\Psi}{2}\right) &= 0 \rightarrow a_1 = -\frac{2}{\Delta\Psi} \frac{COD_{avg}}{COD_{max}} \\ CSD_{avg} + CSD_{max} b_1 \left(\Delta\theta - \frac{\Delta\theta}{2}\right) &= 0 \rightarrow b_1 = -\frac{2}{\Delta\theta} \frac{CSD_{avg}}{CSD_{max}} \end{aligned} \quad (\text{A.4})$$

$$\begin{aligned} \sum_{i=0}^1 \left(-\frac{1}{2}\right)^{i+1} \sin\left(\frac{1+\text{mod}(i,2)}{2}\pi - 2\Delta\Psi\right) &\left(\sum_{k=0}^{1-i} a_k (1-(k+1))! \Delta\Psi^k\right) = \\ &= \left(-\frac{1}{2}\right)^1 \sin\left(\frac{1+\text{mod}(0,2)}{2}\pi - 2\Delta\Psi\right) \left(\sum_{k=0}^1 a_k (1-(k+1))! \Delta\Psi^k\right) + \\ &+ \left(-\frac{1}{2}\right)^2 \sin\left(\frac{1+\text{mod}(1,2)}{2}\pi - 2\Delta\Psi\right) \left(\sum_{k=0}^0 a_k (1-(k+1))! \Delta\Psi^k\right) = \\ &= -\frac{1}{2} \cos(2\Delta\Psi) \left(\sum_{k=0}^1 a_k (1-(k+1))! \Delta\Psi^k\right) + \\ &+ \frac{1}{4} \sin(2\Delta\Psi) \left(\sum_{k=0}^0 a_k (1-(k+1))! \Delta\Psi^k\right) = \\ &= -\frac{1}{2} \cos(2\Delta\Psi) (a_0 + a_1 (n-(k+1))! \Delta\Psi^k) + \\ &+ \frac{1}{4} \sin(2\Delta\Psi) \left(\sum_{k=0}^0 a_k (n-(k+1))! \Delta\Psi^k\right) = \end{aligned} \quad (\text{A.5})$$

n = 2

$$\begin{aligned}
f\left(\theta - \frac{\Delta\Psi}{2}\right) &= \sum_{k=0}^1 a_{2k+1} \left(\theta - \frac{\Delta\Psi}{2}\right)^{2k+1} = a_1 \left(\theta - \frac{\Delta\Psi}{2}\right) + a_3 \left(\theta - \frac{\Delta\Psi}{2}\right)^3 \\
g\left(\theta - \frac{\Delta\theta}{2}\right) &= \sum_{k=0}^1 b_{2k+1} \left(\theta - \frac{\Delta\theta}{2}\right)^{2k+1} = b_1 \left(\theta - \frac{\Delta\theta}{2}\right) + b_3 \left(\theta - \frac{\Delta\theta}{2}\right)^3
\end{aligned}
\tag{A.6}$$

n = 3

$$\begin{aligned}
f\left(\theta - \frac{\Delta\Psi}{2}\right) &= \sum_{k=0}^2 a_{2k+1} \left(\theta - \frac{\Delta\Psi}{2}\right)^{2k+1} = \\
&= a_1 \left(\theta - \frac{\Delta\Psi}{2}\right) + a_3 \left(\theta - \frac{\Delta\Psi}{2}\right)^3 + a_5 \left(\theta - \frac{\Delta\Psi}{2}\right)^5 \\
g\left(\theta - \frac{\Delta\theta}{2}\right) &= \sum_{k=0}^1 b_{2k+1} \left(\theta - \frac{\Delta\theta}{2}\right)^{2k+1} = \\
&= b_1 \left(\theta - \frac{\Delta\theta}{2}\right) + b_3 \left(\theta - \frac{\Delta\theta}{2}\right)^3 + b_5 \left(\theta - \frac{\Delta\theta}{2}\right)^5
\end{aligned}
\tag{A.7}$$