

Similarity laws of the fiber-matrix interface crack in polymer composites

Luca Di Stasio^{a,b}, Janis Varna^a and Zoubir Ayadi^b

^aLuleå University of Technology, University Campus, SE-97187 Luleå, Sweden

^bUniversité de Lorraine, EEIGM, IJL, 6 Rue Bastien Lepage, F-54010 Nancy, France

ARTICLE INFO

Keywords:

Fiber Reinforced Polymer Composite (FRPC)
Debonding
Similarity
Dimensional analysis

ABSTRACT

This template helps you to create a properly formatted L^AT_EX manuscript.

\beginabstract ... \endabstract and \begin{keyword} ... \end{keyword} which contain the abstract and keywords respectively.

Each keyword shall be separated by a \sep command.

1. Introduction

One of the most promising developments in Fiber Reinforced Polymer Composites (FRPCs) for advanced structural applications is currently represented by *thin-ply* laminates [1]. Constituted by extremely thin plies, with t_{90° as small as just $\sim 4-5$ fiber diameters, this family of laminates is characterized by its damage tolerance, in particular the capability of delaying to higher strains and even suppressing the onset and propagation of transverse cracks [2]. The recent experimental assessment of transverse cracks suppression in *thin-ply* laminates [3, 4, 5] validates the existence of a *ply-thickness* effect [5] at scales $10\times$ smaller than those at which it was originally observed at the end of the 1970's [6]. Onset of transverse cracks coincides at the microscopic level with the formation of fiber/matrix interface cracks [7], or debonds. After the inter-fiber stress [8] and strain concentration [9] causes the matrix to fail at or close the fiber interface, debonds grow along the fiber arc direction until a maximum or critical size is reached. If the applied load is increased, debonds move into the matrix or “kink” out of the fiber/matrix interface [10, 11]. Coalescence of debonds then occurs, which corresponds macroscopically to through-the-thickness transverse crack propagation [10, 12]. Finally, propagation through the specimen width occurs [10].

Given that *thin-ply*s, as previously noted, can reach nowadays thicknesses of just $\sim 4-5$ fiber diameters, the characteristic size of the ply, i.e. the thickness t_{90° , is now comparable in magnitude to the characteristic size of debonds, i.e. the fiber diameter $2R_f$, such that $t_{90^\circ}/(2R_f) \sim \mathcal{O}(1)$. This has motivated in recent years a renewed interest in debond growth modeling [12, 13, 14, 15]. Since the elastic solution to the interface crack implies an oscillating solution at the crack tip [16] in the *open* case (crack faces not in contact), Stress Intensify Factors (SIFs) are not defined and debond growth characterization has focused on the determination of Mode I, Mode II and total Energy Release Rate (ERR). Many authors have reported their results in normalized form [11, 17, 18], by defining a reference ERR G_0 . The definition of such reference ERR would be useful to establish similarity laws and thus to allow comparisons between different

material systems, scales, loads and microstructural arrangement. However, no agreement can be found in the literature on the very definition of G_0 and expressions vary between authors. Furthermore, no clear derivation of G_0 has been proposed. In this brief contribution, we provide a derivation of G_0 based on arguments of dimensional analysis, material homogenization and fracture mechanics; we then apply the derived expression of reference ERR to the analysis of debond growth in Representative Volume Elements (RVEs) of UD composites and cross-ply laminates.

2. Dimensional analysis

3. Representative Volume Elements (RVEs)

4. Similarity laws

5. Conclusions

References

- [1] A. Kopp, S. Stappert, D. Mattsson, K. Olofsson, E. Marklund, G. Kurth, E. Mooij, E. Roorda, The aurora space launcher concept, CEAS Space Journal 10 (2017) 167–187.
- [2] J. Cugnoni, R. Amacher, S. Kohler, J. Brunner, E. Kramer, C. Dransfeld, W. Smith, K. Scobbie, L. Sorensen, J. Botsis, Towards aerospace grade thin-ply composites: Effect of ply thickness, fibre, matrix and interlayer toughening on strength and damage tolerance, Composites Science and Technology 168 (2018) 467–477.
- [3] H. Sasayama, K. Kawabe, S. Tomoda, I. Ohsawa, K. Kageyama, N. Ogata, Effect of lamina thickness on first ply failure in multidirectionally laminated composites, in: Proceedings of the 8th Japan SAMPE Symposium, SAMPE, 2003.
- [4] H. Saito, H. Takeuchi, I. Kimpara, Experimental evaluation of the damage growth restraining in 90° layer of thin-ply cfrp cross-ply laminates, Advanced Composite Materials 21 (2012) 57–66.
- [5] R. Amacher, J. Cugnoni, J. Botsis, L. Sorensen, W. Smith, C. Dransfeld, Thin ply composites: Experimental characterization and modeling of size-effects, Composites Science and Technology 101 (2014) 121–132.
- [6] J. E. Bailey, P. T. Curtis, A. Parvizi, On the transverse cracking and longitudinal splitting behaviour of glass and carbon fibre reinforced epoxy cross ply laminates and the effect of poisson and thermally generated strain, Proceedings of the Royal Society A: Mathematical, Physical and Engineering Sciences 366 (1979) 599–623.
- [7] J. E. Bailey, A. Parvizi, On fibre debonding effects and the mechanism of transverse-ply failure in cross-ply laminates of glass fi-

ORCID(s):

- bre/thermoset composites, *Journal of Materials Science* 16 (1981) 649–659.
- [8] L. Asp, L. Berglund, R. Talreja, Prediction of matrix-initiated transverse failure in polymer composites, *Composites Science and Technology* 56 (1996) 1089–1097.
 - [9] J. A. Kies, Maximum strains in the resin of fibreglass composites, *NRL Report 5752, AD-274560*, Washington (DC): U.S. Naval Research Laboratory, 1962.
 - [10] H. Zhang, M. Ericson, J. Varna, L. Berglund, Transverse single-fibre test for interfacial debonding in composites: 1. experimental observations, *Composites Part A: Applied Science and Manufacturing* 28 (1997) 309–315.
 - [11] F. París, E. Correa, V. Mantič, Kinking of transversal interface cracks between fiber and matrix, *Journal of Applied Mechanics* 74 (2007) 703.
 - [12] L. Zhuang, A. Pupurs, J. Varna, R. Talreja, Z. Ayadi, Effects of inter-fiber spacing on fiber-matrix debond crack growth in unidirectional composites under transverse loading, *Composites Part A: Applied Science and Manufacturing* 109 (2018) 463–471.
 - [13] C. Sandino, E. Correa, F. París, Numerical analysis of the influence of a nearby fibre on the interface crack growth in composites under transverse tensile load, *Engineering Fracture Mechanics* 168 (2016) 58–75.
 - [14] J. Varna, L. Q. Zhuang, A. Pupurs, Z. Ayadi, Growth and interaction of debonds in local clusters of fibers in unidirectional composites during transverse loading, *Key Engineering Materials* 754 (2017) 63–66.
 - [15] C. Sandino, E. Correa, F. París, Interface crack growth under transverse compression: nearby fibre effect, in: *Proceeding of the 18th European Conference on Composite Materials (ECCM-18)*, 2018.
 - [16] M. Comninou, The interface crack, *Journal of Applied Mechanics* 44 (1977) 631.
 - [17] M. Toya, A crack along the interface of a circular inclusion embedded in an infinite solid, *Journal of the Mechanics and Physics of Solids* 22 (1974) 325–348.
 - [18] F. París, J. C. Caño, J. Varna, The fiber-matrix interface crack — a numerical analysis using boundary elements, *International Journal of Fracture* 82 (1996) 11–29.