3293 Midland Dr. Suite 106.
Ogden, UT 84401
(801) 643-5705
www.limelinepaintsupply.com

TECHNICAL DATA SHEET

UC4:1

URETHANE CLEARCOAT

03012023

UC4:1 is a premium automotive National Rule Clear. Its distinct "water white" property eliminates concerns of color change, especially over white. It has an outstanding buffing capabilities and a superior gloss for a kick ass appearance

COMPONENTS

• UC4:1	LiME LiNE Urethane Clearcoat
• GH60/GH70/GH80	Fast/Medium/Slow – National Rule Activators
• GH50W	Super Fast - Winterized Activators

MIXING RATIO

Mix four (4) parts Urethane Clearcoat with one (1) part selected activator.

POT LIFE

2 hours @ 77° F/25° C

CLEAN UP

Use LiME LiNE Thinner or zero VOC solvents. (Check local regulation)

PHYSICAL DATA

Solids wt.	34.4% (39.0% as mixed)
VOC as mixed (restricted areas)	4.8 lbs/gl
Color	Water white

DRY / FLASH TIMES

Air Dry at 77° F/25°C

Flash between coats	8-10 minutes
Dust free	30 minutes
Tack free	15-20 minutes
Sand & Bu	12-24 hours (air dry) @77° F/25° C

Force Dry

Flash before force dry 15 minute ash
Force dry time 40 minutes @140° F/60°C
Sand & Bu 1 hour after cooldown at minimum 77° F/25°C

COLOR SANDING

Wet sand with 1500 to 2000 wet or dry paper, then bu with appropriate compounds and glazes to achieve a high gloss nish.

GUN SETUPS

Compliant

Gravity Feed	1.3 mm – 1.5 mm
Siphon Feed	1.3 mm – 1.5 mm

AIR PRESSURES

Conventional at Gun

Gravity Feed	30 – 40 psi
Siphon Feed	35 – 45 psi
HVLP at cap	8 – 10 psi

SURFACE PREPARATION

Use LiME LiNE Clean Wipe to clean substrate free of grease, dirt, and foreign contaminants.

APPLICATION AT 77° F/25°C

- Apply 2 medium wet coats over substrate to desired lm thickness
- Allow 10 – 15 minutes between coats
- Scu after 24 hours before recoating
- Clean gun after spraying is completed

SAFETY

Refer to Material Safety Data Sheet (MSDS) for complete safety instructions. The technical data sheet listed has been compiled in good faith for your convenience and guidance. No warranty, expressed or implied, is intended or given by the information on this sheet.