Technical Datasheet

ML3

Multi-Layer Infusion Media

Key Features

- Speeds up tear down
- Allows for ovelapping
- Best for flatter mould shapes

Description

ML3 is a multi-layer infusion media which combines the functions of the infusion flow media (mesh) with peel-ply/ perforated release film to offer a reliable and fast layup along with incredibly easy removal. By combining the flow mesh and peel ply ML3 offers a much faster and simpler workflow to reduce production times.

The full permeability of the material means that it can be overlapped in tricky areas without the risk of it binding, as can be the case with use of a perforated release film.

The biggest advantage comes when demoulding, as the multiple layers stay in one piece meaning that quite often the membrane can be removed in one.

Typical Uses

ML3 is used as a combined flow media and peel ply to distribute resin through the laminate during vacuum resin infusion. Its unique construction makes laying up and removing a simpler and faster process. It is typically used in:

- Wind turbine blades.
- Marine hulls and mouldings
- Automotive/motorsport panels
- Kayak/Dinghy mouldings

It would be recommended for use in resin infusion of flatter or less complex mouldings and it is compatible with Epoxy, polyester and vinylester infusions.

Specification

Property	Unit	Value
Material	-	Polyester
Width	mm	1520
Format	-	Multi-Layer
Areal Weight	g/m²	335
Maximum Use Temp	°C	210
Appearance	-	Yellow / White

Handling & Storage

ML3 is a stable material with no special handling or storage requirements.

Disclaimer

This data is not to be used for specifications. Values listed are for typical properties and should not be considered minimum or maximum. Our technical advice, whether verbal or in writing, is given in good faith but Easy Composites Ltd gives no warranty; express or implied, and all products are sold upon condition that purchasers will make their own tests to determine the quality and suitability of the product for their particular application and circumstances.

Easy Composites Ltd shall be in no way responsible for the proper use and service of the product, nor for the safeguarding of personnel or property, all of which is the duty of the user. Any information or suggestions are without warranty of any kind and purchasers are solely responsible for any loss arising from the use of such information or suggestions. No information or suggestions given by us shall be deemed to be a recommendation to use any product in conflict with any existing patent rights. Before using any of our products, users should familiarise themselves with the relevant technical and safety datasheets provided by Easy Composites Ltd.

ML3 is a trademark of Easy Composites Ltd.

Easy Composites Ltd
Unit 39, Park Hall Business Village
Stoke-on-Trent, ST3 5XA
United Kingdom

Easy Composites EU B.V.
Beneluxbaan 16
Rijen, 5121 DC
Netherlands

W: **www.easycomposites.com**
E: **sales@easycomposites.com**
T: **+44 (0) 1782 454499**

Version 1.0
Revised 04/09/2025