

GRX-810 NASA Developed Data Sheet

Principal Features

GRX-810 alloy is a nickel-Cobalt-Chromium-Tungsten oxide dispersion strengthened (ODS) alloy that combines excellent high-temperature strength, outstanding resistance to oxidizing environments up to 2400°F (1316°C). At 2000°F (1093°C) GRX-810 provides a 2x improvement in strength compared to superalloy 718 and 625. Most notably, GRX-810 provides over 1000x longer creep rupture lives in the build direction compared to 718 and 625. It is amenable to the additive manufacturing, specifically laser-powder bed fusion. Other attractive features include its stable microstructure up to its melting temperature.

Easily Fabricated

GRX-810 can be easily printed at similar build speeds compared to superalloy 718.

Heat Treatment

GRX-810 can be used in both the as-built and post HIP states. No aging or solution treatment is required.

Applications

The GRX-810 alloy was specifically designed for aerospace applications, including liquid rocket engine injectors, preburners, turbines, and hot-section components, capable of withstanding temperatures up to 1,100 °C. The objective of this alloy was to bridge the temperature gap between traditional Nickel-based superalloys and refractory alloys.

Composition and Processing

Table 1: Nominal composition for base powder GRX-810.

| Element | Nominal |
|---------|---------|
| Al | 0.3% |
| C | 0.055% |
| Cr | 30% |
| Co | 32% |
| Nb | 0.8% |
| Ni | Balance |
| Re | 1.5% |
| Ti | 0.3% |
| W | 3.0% |

Table 2: Heat treatment used performed on GRX-810 samples used for material test data.

| Heat Treatment | Temperature | Time | Stress |
|-----------------|-------------|-----------|---------|
| HIP – ASTM 3301 | 1163°C | 3-4 hours | 103 MPa |

Table 3: L-PBF core process parameters for GRX-810.

| Laser Power (W) | Scan Speed (mm/s) | Layer Thickness (mm) |
|-----------------|-------------------|----------------------|
| 275 | 1000 | 0.04 |

Physical Properties

Room Temperature Overview

All Thermal properties were measured from room temperature to 1300°C. Due to system limitations, thermal diffusivity could not be determined above 1200C, therefore, thermal diffusivity and thermal conductivity were reported to 1200C. Density was measured per ASTM B3311-22 on a Mettler-Toledo XS-205 Density Determinator. Specific heat was measured per ASTM E1269-24 using a Netzsch DSC 404 F1 Pegasus. Thermal Diffusivity was measured per ASTM E1461-13 (2022) using a TA Instruments DLF1200 laser flash. Thermal Expansion was performed per ASTM E288-22 using a Netzsch DIL402SE dilatometer.

Table 4: Room Temperature Properties for HIP GRX-810

| | |
|--|--------|
| Density (g/cm ³) | 8.44 |
| Specific Heat (J/g*K) | 0.434 |
| Coefficient of Thermal Expansion (10 ⁻⁶ /K) | 10.6 |
| Thermal Conductivity (W/m*K) | 11.0 |
| Thermal Diffusivity (Cm ² /s) | 0.0299 |
| Poisson's Ratio | 0.234 |
| Young's Modulus (GPa) | 188.2 |

Table 5: Room Temperature Properties for As-built GRX-810

| | |
|--|--------|
| Density (g/cm ³) | 8.44 |
| Specific Heat (J/g*K) | 0.434 |
| Coefficient of Thermal Expansion (10 ⁻⁶ /K) | 11.8 |
| Thermal Conductivity (W/m*K) | 10.55 |
| Thermal Diffusivity (Cm ² /s) | 0.0295 |
| Poisson's Ratio | 0.24 |
| Young's Modulus (GPa) | 190.6 |

Specific Heat




Figure 1: Specific heat as a function of temperature for AM GRX-810 in the as-built and HIP condition.

Thermal Conductivity





Figure 2: Thermal conductivity vs temperature curve for AM GRX-810 in the as-built and HIP condition.

Thermal Diffusivity**Figure 3:** Thermal Diffusivity vs temperature curve for AM GRX-810 in the as-built and HIP conditions.**Table 6:** Tabulated data for specific heat, thermal diffusivity, and thermal conductivity vs temperature in As-built GRX-810.

| Temperature (C) | AB Specific Heat (J/g/K) | AB Thermal Diffusivity (Cm ⁻² /s) | AB Thermal Conductivity (W/m/K) |
|-----------------|--------------------------|--|---------------------------------|
| 25 | 0.420 | 0.0295 | 10.7 |
| 100 | 0.428 | 0.0322 | 12.0 |
| 200 | 0.444 | 0.0357 | 13.9 |
| 300 | 0.454 | 0.0388 | 15.6 |
| 400 | 0.467 | 0.0417 | 17.3 |
| 500 | 0.471 | 0.0443 | 18.6 |
| 600 | 0.440 | 0.0467 | 18.8 |
| 700 | 0.559 | 0.0487 | 24.1 |
| 800 | 0.570 | 0.0505 | 25.3 |
| 900 | 0.587 | 0.0520 | 26.7 |
| 1000 | 0.650 | 0.0532 | 30.0 |
| 1100 | 0.694 | 0.0541 | 32.6 |
| 1200 | 0.635 | 0.0547 | 28.7 |
| 1300 | 0.646 | --- | --- |

Table 7: Tabulated data for specific heat, thermal diffusivity, and thermal conductivity vs temperature in HIP GRX-810

| Temperature (C) | HIP Specific Heat (J/g/K) | HIP Thermal Diffusivity (Cm ² /s) | HIP Thermal Conductivity (W/m/K) |
|-----------------|---------------------------|--|----------------------------------|
| 25 | 0.434 | 0.0299 | 11.0 |
| 100 | 0.446 | 0.0327 | 12.3 |
| 200 | 0.464 | 0.0361 | 14.1 |
| 300 | 0.479 | 0.0392 | 15.8 |
| 400 | 0.495 | 0.0421 | 17.6 |
| 500 | 0.511 | 0.0447 | 19.3 |
| 600 | 0.547 | 0.0470 | 21.7 |
| 700 | 0.598 | 0.0491 | 24.7 |
| 800 | 0.617 | 0.0509 | 26.5 |
| 900 | 0.638 | 0.0524 | 28.2 |
| 1000 | 0.693 | 0.0537 | 31.4 |
| 1100 | 0.750 | 0.0547 | 34.6 |
| 1200 | 0.683 | 0.0554 | 32.0 |
| 1300 | 0.666 | --- | --- |

Thermal Expansion




Figure 4: Thermal displacement as a function of temperature for AM HIP GRX-810




Figure 5: Thermal displacement as a function of temperature for AM As-built GRX-810

Table 8: Tabulated thermal expansion data vs. Temperature in HIP and as-built AM GRX-810

| Temperature (C) | HIP CTE (10 ⁻⁶ m/m/°C) | AB CTE (10 ⁻⁶ m/m/°C) |
|-----------------|-----------------------------------|----------------------------------|
| 100 | 11.8 | 10.6 |
| 200 | 12.9 | 12.3 |
| 300 | 13.5 | 13 |
| 400 | 13.9 | 13.5 |
| 500 | 14.3 | 13.9 |
| 600 | 14.7 | 13.9 |
| 700 | 15.4 | 14.4 |
| 800 | 16 | 15 |
| 900 | 16.5 | 15.5 |
| 1000 | 17.2 | 16.1 |
| 1100 | 17.9 | 16.8 |
| 1200 | 18.5 | 17.4 |
| 1300 | 19 | 17.9 |

Elastic Modulus:

Table 9: Elastic modulus for AM GRX-810 produced using a single-laser AM printer (1) measured from tensile tests.

| Temp (C) | Modulus (Gpa) |
|-----------------|----------------------|
| -196 | 182.0 |
| 21 | 158.6 |
| 427 | 115.8 |
| 649 | 106.2 |
| 871 | 82.1 |
| 1093 | 42.7 |

Microstructure and Characterization

Polish Procedure:

Table 10: GRX-810 polishing procedure.

| Polishing Step | Grit Size | Lubricant | Time (min) | Load (N) | RPM |
|----------------|-------------------------|---|------------|----------|-----|
| 1 | 220 | H ₂ O | 1-2 | 150 | 300 |
| 2 | 9um Diamond suspension | 60% HUDOIL Extender + 40% ethanol | 7 | 150 | 150 |
| 3 | 6 um Diamond suspension | 60% HUDOIL Extender + 40% ethanol | 7 | 150 | 150 |
| 4 | 3 um Diamond suspension | 60% HUDOIL Extender + 40% ethanol | 3.5 | 150 | 150 |
| 5 | 3 um Diamond suspension | 60% HUDOIL Extender + 40% ethanol | 3.5 | 150 | 150 |
| 6 | 1 um Diamond suspension | 60% HUDOIL Extender + 40% ethanol | 3.5 | 150 | 150 |
| 7 | 1 um Diamond suspension | 60% HUDOIL Extender + 40% ethanol | 15 | 150 | 150 |
| 8 | .05 | 60% Colloidal Silica + 40% H ₂ O | 120-240 | N/A | N/A |

Etchant

Electrolytic etching in 5g Oxalic, 95mL HCl at 25C. Stainless steel cathode, carbon cathode at 6V with 1-2s contact. (Etch until blue film covers specimen surface evenly)




Figure 6: Typical as-built microstructure of AM GRX-810 in the XZ plane for (a) as-built and (b) HIP after etching.

Grain Structure




Figure 7: Typical grain structure of HIPed AM GRX-810 in the XY plane (left) and XZ plane (right).




Figure 8: Typical SEM microstructure of (a) as-built and (b) HIP AM GRX-810.

Mechanical Properties

Multiple printers were employed to print and test GRX-810 specimen. The data from each AM printer has been separated to convey printer-to-printer variation typical for GRX-810.

Tensile

Table 11: Average tensile behavior vs temperature for as-built AM GRX-810 loading in Z direction with respect to AM machine.

| Machine | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
|------------------------------|------------------|------|--------------------------|-------|--------------------------------|--------|-----------------|----------------|
| Single-Laser AM Printer 1 | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | -320 | -196 | 118.3 | 815.3 | 183.5 | 1265.2 | 49.0 | 4 |
| | 75 | 24 | 83.1 | 573.3 | 127.9 | 881.5 | 44.6 | 7 |
| | 800 | 427 | 68.0 | 468.8 | 99.0 | 682.6 | 40.0 | 2 |
| | 1200 | 649 | 61.5 | 424.0 | 94.8 | 653.3 | 43.0 | 2 |
| | 1600 | 871 | 33.1 | 227.9 | 40.3 | 277.5 | 62.0 | 2 |
| | 1832 | 1000 | 21.8 | 150.3 | 23.2 | 159.6 | 45.5 | 2 |
| | 2000 | 1093 | 15.9 | 109.9 | 16.7 | 115.0 | 21.6 | 9 |
| | | | | | | | | |
| Machine | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
| Single-Laser AM Printer 2 | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | 75 | 24 | 76.0 | 524.0 | 115.2 | 794.0 | 45.5 | 18 |
| | 400 | 204 | 55.1 | 380.1 | 95.3 | 656.7 | | 4 |
| | 800 | 427 | 52.0 | 358.5 | 87.4 | 602.4 | | 4 |
| | 1000 | 538 | 59.0 | 406.7 | 88.1 | 607.2 | 41.9 | 8 |
| | 1200 | 649 | 46.4 | 319.9 | 82.9 | 571.4 | | 4 |
| | 1600 | 871 | 27.2 | 187.2 | 36.4 | 250.6 | | 4 |
| | 1800 | 982 | 19.2 | 132.2 | 22.8 | 157.0 | | 4 |
| | 1900 | 1038 | 19.0 | 131.0 | 19.3 | 133.1 | | 4 |
| | 2000 | 1093 | 14.9 | 103.0 | 15.6 | 107.7 | 39.6 | 17 |
| | 2100 | 1149 | 13.0 | 89.8 | 13.2 | 91.3 | 23.9 | 10 |
| | 2200 | 1204 | 10.7 | 73.6 | 11.1 | 76.3 | 13.2 | 6 |
| | 2300 | 1260 | 8.7 | 59.9 | 9.4 | 64.5 | 13.0 | 6 |
| | 2400 | 1316 | 6.1 | 41.8 | 7.1 | 49.1 | 6.6 | 6 |
| | | | | | | | | |
| Machine | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
| Single-Laser AM Printer 3 | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | 75 | 24 | 90.0 | 620.5 | 114.0 | 786.0 | 56.5 | 3 |
| | 1000 | 538 | 67.2 | 463.3 | 90.5 | 624.2 | 55.8 | 3 |
| | 2000 | 1093 | 13.4 | 92.2 | 14.9 | 103.0 | 40.8 | 3 |
| | | | | | | | | |
| Machine | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
| Multi-Laser AM Printer 1 | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | 75 | 24 | 75.5 | 520.7 | 115.5 | 796.3 | 48.0 | 16 |
| | 400 | 204 | 62.7 | 432.3 | 96.2 | 663.5 | 47.9 | 16 |
| | 800 | 427 | 58.4 | 402.4 | 89.6 | 618.0 | 48.7 | 16 |
| | 1000 | 538 | 56.5 | 389.6 | 84.8 | 584.3 | 48.5 | 6 |
| | 1200 | 649 | 53.1 | 365.9 | 84.8 | 584.9 | 50.2 | 16 |
| | 1400 | 760 | 48.3 | 332.7 | 61.3 | 422.9 | 102.2 | 6 |
| | 1600 | 871 | 30.1 | 207.7 | 37.3 | 257.0 | 98.8 | 16 |
| | 1800 | 982 | 20.3 | 140.0 | 22.4 | 154.2 | 81.4 | 16 |
| | 1900 | 1038 | 16.6 | 114.5 | 17.8 | 122.7 | 68.0 | 10 |
| | 2000 | 1093 | 13.7 | 94.7 | 14.5 | 100.0 | 53.5 | 19 |
| | 2100 | 1149 | 12.1 | 83.1 | 12.3 | 84.9 | | 6 |
| | 2200 | 1204 | 9.3 | 64.3 | 9.5 | 65.7 | | 6 |
| | 2300 | 1260 | 7.4 | 50.9 | 7.7 | 52.9 | | 7 |

Table 12: Average tensile behavior vs temperature for HIP AM GRX-810 loading in Z direction with respect to AM machine.

| Machine | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
|------------------------------|------------------|------|--------------------------|-------|--------------------------------|--------|-----------------|----------------|
| Single-Laser AM Printer 1 | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | -320 | -196 | 105.0 | 723.9 | 178.0 | 1227.3 | 49.0 | 2 |
| | 75 | 24 | 69.7 | 480.3 | 129.3 | 891.7 | 51.5 | 3 |
| | 800 | 427 | 59.5 | 410.2 | 95.0 | 655.0 | 40.0 | 1 |
| | 1200 | 649 | 53.5 | 368.9 | 91.5 | 630.9 | 43.0 | 1 |
| | 1600 | 871 | 29.9 | 206.2 | 38.1 | 262.7 | 62.0 | 1 |
| | 1832 | 1000 | 21.8 | 150.3 | 23.2 | 159.6 | 45.5 | 2 |
| | 2000 | 1093 | 15.8 | 108.9 | 16.9 | 116.3 | 32.5 | 3 |
| | | | | | | | | |
| Machine | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
| Single-Laser AM Printer 2 | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | 75 | 24 | 69.7 | 480.7 | 114.5 | 789.4 | 48.2 | 12 |
| | 400 | 204 | 55.1 | 380.1 | 95.3 | 656.7 | | 4 |
| | 800 | 427 | 52.0 | 358.5 | 87.4 | 602.4 | | 4 |
| | 1000 | 538 | 51.6 | 355.9 | 85.5 | 589.3 | 46.1 | 4 |
| | 1200 | 649 | 46.4 | 319.9 | 82.9 | 571.4 | | 4 |
| | 1600 | 871 | 27.2 | 187.2 | 36.4 | 250.6 | | 4 |
| | 1800 | 982 | 19.2 | 132.2 | 22.8 | 157.0 | | 4 |
| | 1900 | 1038 | 19.0 | 131.0 | 19.3 | 133.1 | | 4 |
| | 2000 | 1093 | 14.9 | 102.8 | 15.5 | 107.0 | 37.1 | 10 |
| | 2100 | 1149 | 13.0 | 89.6 | 13.3 | 91.7 | 21.8 | 7 |
| | 2200 | 1204 | 10.2 | 70.4 | 11.0 | 76.0 | 13.2 | 3 |
| | 2300 | 1260 | 8.6 | 59.5 | 9.6 | 66.1 | 15.0 | 3 |
| | 2400 | 1316 | 5.5 | 37.8 | 6.6 | 45.8 | 4.3 | 3 |
| | | | | | | | | |
| Machine | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
| Single-Laser AM Printer 3 | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | 75 | 24 | 67.6 | 466.3 | 107.4 | 740.7 | 62.8 | 3 |
| | 1000 | 538 | 49.3 | 339.9 | 84.2 | 580.5 | 59.2 | 3 |
| | 2000 | 1093 | 13.2 | 90.8 | 14.6 | 100.4 | 40.6 | 3 |
| | | | | | | | | |
| Machine | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
| Multi-Laser AM Printer 1 | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | 75 | 24 | 65.9 | 454.4 | 111.9 | 771.7 | 51.0 | 8 |
| | 400 | 204 | 54.1 | 373.1 | 92.5 | 637.5 | 51.4 | 8 |
| | 800 | 427 | 50.9 | 351.0 | 86.5 | 596.5 | 52.7 | 8 |
| | 1000 | 538 | 48.5 | 334.4 | 81.8 | 564.2 | 52.7 | 3 |
| | 1200 | 649 | 45.4 | 312.8 | 81.4 | 561.3 | 58.2 | 8 |
| | 1400 | 760 | 43.5 | 299.9 | 58.8 | 405.6 | 109.0 | 3 |
| | 1600 | 871 | 27.7 | 190.8 | 35.2 | 242.5 | 104.1 | 8 |
| | 1800 | 982 | 19.0 | 131.0 | 21.8 | 150.2 | 88.2 | 8 |
| | 1900 | 1038 | 16.1 | 111.1 | 17.4 | 120.2 | 68.5 | 5 |
| | 2000 | 1093 | 13.6 | 93.9 | 14.4 | 99.0 | 58.5 | 11 |
| | 2100 | 1149 | 11.6 | 80.3 | 11.9 | 82.0 | | 3 |
| | 2200 | 1204 | 9.5 | 65.2 | 9.7 | 66.7 | | 3 |
| | 2300 | 1260 | 7.7 | 52.8 | 7.9 | 54.7 | | 3 |

Table 13: Average tensile behavior vs temperature for as-built AM GRX-810 loading in X direction (horizontal) with respect to AM machine.

| Machine | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
|-----------------------------|------------------|------|--------------------------|-------|--------------------------------|-------|-----------------|----------------|
| Multi-Laser AM Printer 1 | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | 75 | 24 | 85.3 | 587.8 | 129.0 | 889.4 | 37.5 | 10 |
| | 400 | 204 | 70.7 | 487.3 | 109.2 | 753.2 | 37.3 | 10 |
| | 800 | 427 | 65.7 | 452.6 | 99.9 | 688.6 | 36.8 | 10 |
| | 1200 | 649 | 58.8 | 405.2 | 92.8 | 640.0 | 34.2 | 10 |
| | 1600 | 871 | 32.5 | 223.9 | 40.9 | 282.2 | 38.1 | 10 |
| | 1800 | 982 | 21.2 | 146.2 | 24.1 | 165.9 | 23.0 | 10 |
| | 1900 | 1038 | 16.8 | 115.5 | 18.6 | 128.0 | 17.0 | 10 |
| | 2000 | 1093 | 13.3 | 91.8 | 14.3 | 98.7 | 14.3 | 16 |
| | 2100 | 1149 | 11.6 | 80.0 | 11.7 | 80.8 | | 6 |
| | 2200 | 1204 | 8.6 | 59.3 | 8.9 | 61.2 | | 6 |
| | 2300 | 1260 | 6.3 | 43.6 | 6.6 | 45.6 | | 6 |

Table 14: Average tensile behavior vs temperature for HIP AM GRX-810 loading in X direction (horizontal) with respect to AM machine.

| Machine | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
|-----------------------------|------------------|------|--------------------------|-------|--------------------------------|-------|-----------------|----------------|
| Multi-Laser AM Printer 1 | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | 75 | 24 | 74.2 | 511.6 | 127.0 | 875.6 | 42.6 | 3 |
| | 400 | 204 | 58.4 | 402.8 | 105.9 | 730.2 | 41.5 | 5 |
| | 800 | 427 | 54.3 | 374.4 | 96.9 | 668.0 | 40.5 | 5 |
| | 1200 | 649 | 49.4 | 340.7 | 89.8 | 619.0 | 38.0 | 5 |
| | 1600 | 871 | 28.8 | 198.3 | 39.3 | 270.7 | 41.5 | 5 |
| | 1800 | 982 | 19.6 | 134.9 | 23.5 | 162.2 | 25.8 | 5 |
| | 1900 | 1038 | 16.2 | 111.6 | 18.6 | 128.2 | 16.1 | 5 |
| | 2000 | 1093 | 13.1 | 90.4 | 14.3 | 98.4 | 14.1 | 8 |
| | 2100 | 1149 | 10.6 | 73.0 | 10.7 | 74.0 | | 3 |
| | 2200 | 1204 | 8.9 | 61.3 | 9.1 | 62.7 | | 3 |
| | 2300 | 1260 | 6.4 | 44.2 | 6.7 | 46.0 | | 3 |

Table 15: Average tensile behavior vs temperature for AM GRX-810 loading in 45° from the build direction (Z)

| Machine | Condition | Test Temperature | | Avg. 0.2% Yield Strength | | Avg. Ultimate Tensile Strength | | Avg. Elongation | Tested Samples |
|------------------------------|-----------|------------------|-----|--------------------------|-------|--------------------------------|-------|-----------------|----------------|
| Single-Laser AM Printer 3 | N/A | °F | °C | ksi | Mpa | ksi | Mpa | % | # |
| | As-built | 75 | 24 | 98.8 | 681.0 | 132.6 | 914.2 | 34.2 | 3 |
| | HIP | 75 | 24 | 74.2 | 511.6 | 127.0 | 875.6 | 42.6 | 3 |
| | As-built | 800 | 427 | 77.4 | 533.4 | 105.1 | 724.4 | 33.6 | 3 |
| | HIP | 800 | 427 | 55.6 | 383.3 | 99.7 | 687.4 | 38.2 | 3 |
| | As-built | 1200 | 649 | 70.2 | 484.0 | 100.0 | 689.2 | 29.9 | 3 |
| | HIP | 1200 | 649 | 50.6 | 349.1 | 94.5 | 651.6 | 38.8 | 3 |




Figure 9: Ultimate Tensile Strength vs. temperature for AM GRX-810




Figure 10: Ultimate Tensile Strength vs. temperature for AM GRX-810 at elevated temperatures

Low Cycle Fatigue




Figure 11: Low cycle fatigue life vs strain amplitude ($R=-1$) at room temperature for AM GRX-810 loading in the Z direction




Figure 12: Low cycle fatigue life vs strain amplitude ($R=-1$) at 1000°F (537.8°C) for AM GRX-810 loading in the Z direction




Figure 13: Low cycle fatigue life vs strain amplitude ($R=-1$) at 2000°F (1093°C) for AM GRX-810 loading in the Z direction

High Cycle Fatigue




Figure 14: Stress controlled high cycle fatigue life vs stress amplitude ($R=-1$) for GRX-810 loading in the Z direction at room temperature.




Figure 15: Stress controlled high cycle fatigue life vs stress amplitude (R=-1) for GRX-810 loading in the Z direction at 1000°F (537.8°C).




Figure 16: Stress controlled high cycle fatigue life vs stress amplitude (R=-1) for GRX-810 loading in the Z direction at 1600°F (871.1°C).




Figure 17: Stress controlled high cycle fatigue life vs stress amplitude (R=-1) for GRX-810 loading in the Z direction at 2200°F (1204°C).

Creep




Figure 18: Creep overview at 2000°F (1093°C) for AM GRX-810.




Figure 19: The Larson Miller Parameter vs. stress for creep rupture in GRX-810 in the horizontal (H) and vertical (V) build directions compared to plate Haynes 230 and sheet Superalloy 625.

Oxidation Resistance

Cyclic Oxidation




Figure 20: Cyclic Oxidation Results at 1100°C, 1200°C, and 1300°C. Cyclic oxidation results for (a) GRX-810, 718, and single crystal B1900 at 1100°C, (b) GRX-810, 718, ME3 (powder metallurgy (PM) disk alloy), 625, and B1900 at 1200C, and (c) GRX-810, 625, 718, single crystals B1900+Hf, B1900, and SC180 at 1300°C. Images of the samples were taken after the final cycle measured to highlight the state of the alloy at that point. Note: the 718 sample produced runaway oxidation gain after cycle 3 which has been denoted with the dashed arrow. “x” denotes a test ending due to catastrophic oxidation (sample weight < 1 gram or severe microstructure degradation).




Figure 21: Microstructural stability at 1300°C. metallography cross-sections of (a) superalloy 718 after 7 cycles and (b) GRX-810 after 10 cycles. SEM micrographs of the oxide (fine dark circular features) size and morphology of (c) as-printed GRX-810 and (d) GRX-810 after ten 1300°C 1-hour cycles.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Acknowledgements: Funding for this data sheet was provided by NASA's Aeronautics Research Mission Directorate (ARMD) – Transformational Tools and Technologies (TTT) Project Office, NASA's Space Technology Mission Directorate (STMD) Game Changing Development (GCD) Program under the optimized and Repeatable Components in Additive Manufacturing (ORCA) project and the Air Force Research Laboratory.