

Percolation Weight and Thermodynamic Stability Across a 186-Compound Dataset

Campaign 2: Dataset Construction, VASP+LOBSTER Computation, and Statistical Analysis

Gilles Frapper
Professor, Theoretical Chemistry
IC2MP UMR 7285 CNRS, Université de Poitiers
gilles.frapper@univ-poitiers.fr

Report generated as part of the `viability` project

August 14, 2026

Update, August 15, 2026: missions #3–#5 added (dimensionality/min-cut, antibonding population, reaction ICOHP), see §11. The body of this report below (through the conclusion and appendices) documents the original campaign 2 (186 compounds, percolation weight only) unmodified.

Contents

1	Objective and Problem Statement	2
2	Methodology	2
2.1	Dataset Selection	2
2.2	Bonding-Type Classification	2
2.3	VASP + LOBSTER Computation	2
2.4	Statistics	3
3	Workflow Diagram	3
4	Environment	3
5	Dataset	3
6	Results	4
6.1	Correlations (Spearman)	4
6.2	Reference Logistic Regression	4
6.3	Figures	5
7	Failures Found and Fixed	5
8	Compute Cost	6
9	Limits and Next Steps	6
10	Conclusion	6

11 Campaign 2 follow-ups (missions #3 to #5)	7
11.1 Mission #3: network dimensionality and periodic min-cut	7
11.2 Mission #4: antibonding population near the Fermi level	7
11.3 Mission #5: reaction ICOHP	8
11.4 Comparative summary	9
A Compound List	9
B VASP Calculation Parameters	13
C PAW-PBE Potentials	13
D k-point Grid and NBANDS per Compound	15

1 Objective and Problem Statement

The first report (6 toy compounds) established that the percolation descriptor computed by `percolation_path.py` diverges sharply from classic ICOHP aggregates (sum, mean, min, max), but without a sample large enough to statistically test whether that difference is *useful*: does the percolation descriptor carry predictive information about thermodynamic stability (`energy_above_hull`) that the classic aggregates don't already carry?

This second campaign builds a 186-compound dataset (180 new + the 6 pilot compounds) split into three families:

- **exp_stable**: experimental (ICSD-referenced) compounds on the Materials Project thermodynamic convex hull;
- **exp_metastable**: experimental metastable compounds ($0 < E_{\text{hull}} \leq 100$ meV/atom);
- **theo_metastable**: theoretical (never experimentally observed) metastable compounds ($0 < \bar{E}_{\text{hull}} \leq 200$ meV/atom).

The `exp_metastable` / `theo_metastable` split serves as a proxy for kinetic persistence: an experimentally observed metastable compound has, by definition, survived long enough to be synthesized and characterized, unlike a theoretical compound of comparable thermodynamic metastability.

2 Methodology

2.1 Dataset Selection

Materials Project query (`mp_dataset/select_campaign.py`): unary and binary chemical systems, non-magnetic ($|\text{total magnetization}| \leq 0.01 \mu_B/\text{formula unit}$ — MP's categorical `magnetic_ordering` field is "Unknown" for ~98% of entries and would have excluded nearly every genuinely non-magnetic compound), no f-block elements, ≤ 20 atoms/cell, 60 compounds per family with a 2-entries-per-chemical-system cap to ensure elemental diversity rather than many polymorphs of the same system.

2.2 Bonding-Type Classification

Bond type (ionic / covalent / metallic) is computed by `fetch_candidates.py`'s `classify()` function (**reused unchanged**, per the campaign's instructions), from `is_metal` and elemental composition. This is a secondary analysis axis here, not the primary sampling axis (unlike the campaign's originally proposed plan, replaced at the user's request with the stable/metastable scheme above).


2.3 VASP + LOBSTER Computation

Same template as the pilot campaign (static run, `ISYM=-1`, `LASPH=.TRUE.`, PAW-PBE potentials recommended by `pymatgen.io.vasp.sets.MPRelaxSet`), with two improvements: `NBANDS` is no longer a fixed value but derived per compound from the number of local orbitals in the LOBSTER basis (`Lobsterin.write_INCAR`), and basis-function determination goes through `Lobsterin.get_basis(potcar_symbols=...)` rather than direct POTCAR-file parsing (whose internal pymatgen validity check fails on several POTCARs unrecognized by hash in the local mirror).

2.4 Statistics

Spearman correlation (no reason to expect a linear relationship) between percolation weight (raw and normalized by $|\text{ICOHP}_{\min}|$) and `energy_above_hull`, overall and per bond type; same for the classic ICOHP aggregates, for direct comparison; a reference logistic regression (stable vs. metastable, 2–3 features, 5-fold cross-validation) for a reference AUC. **No SISSO, no symbolic regression**: premature with a single candidate descriptor at this sample size (see §9).

3 Workflow Diagram



4 Environment

Same as the pilot campaign (Yargla, VASP 6.5.0, LOBSTER 5.1.1, Python 3.11 `.venv`), extended with: `mp-api`, `pandas`, `scipy`, `scikit-learn`, `matplotlib` (see `requirements.txt`).

5 Dataset

Family	n	E_{hull} range (eV/atom)
exp_stable	63	0.0000 (by construction)
exp_metastable	63	0.0005 – 0.0907
theo_metastable	60	0.0013 – 0.1991

Bond type (<code>classify()</code>)	<i>n</i>
metallic	88
covalent	23
ionic	9
unclassified	66

35% of compounds (66/186) fall outside `classify()`'s three categories — mostly transition-metal pnictides/chalcogenides and hydrogen-containing compounds, a real limitation of the reused heuristic, documented but not fixed here.

6 Results

6.1 Correlations (Spearman)

Group	Metric	<i>n</i>	ρ	<i>p</i>
all	percolation weight (raw)	186	0.064	0.383
all	percolation weight (normalized)	186	0.071	0.339
metallic	percolation weight (raw)	88	0.191	0.075
metallic	percolation weight (normalized)	88	0.222	0.038
ionic*	percolation weight (raw)	9	−0.402	0.284
covalent	percolation weight (raw)	23	0.165	0.453
all	ICOHP sum	186	0.032	0.670
all	ICOHP min	186	0.093	0.209
metallic	ICOHP sum	88	0.223	0.037
metallic	ICOHP min	88	0.198	0.065

* *n* < 15: do not over-interpret.

In the one subgroup where any result reaches nominal significance (metallic, *n* = 88), the normalized percolation weight (ρ = 0.222, *p* = 0.038) and the ICOHP sum (ρ = 0.223, *p* = 0.037) are statistically indistinguishable in strength. **The percolation descriptor does not demonstrate additional predictive power over the classic aggregates on this dataset** — a more precise answer than the previous (6-compound) report's "qualitatively different" framing, and a more directly actionable one.



6.2 Reference Logistic Regression

Stable (on-hull) vs. metastable, features: normalized percolation weight, mean ICOHP, bond-type dummies (*n* = 120 after dropping unclassified compounds).

AUC (5-fold cross-validation)	0.496 ± 0.141
per-fold AUC	0.556, 0.430, 0.252, 0.637, 0.607

AUC $\approx$ 0.5: chance level. The wide spread across folds (0.25–0.64) is itself informative: it indicates the absence of a stable, learnable signal at this sample size, not merely a "weak but real" one.

6.3 Figures



7 Failures Found and Fixed

Per the instruction ("every job failure must be logged with its probable cause"), 5 of the 178 SLURM-array-submitted jobs failed on the first pass, all diagnosed and fixed at the source:

- **Al12W, BW, WO2, TeW, TiW** (all tungsten-containing): the local mirror's `W_sv` POTCAR is missing its `LEXCH` field entirely (confirmed by direct inspection — present in every other variant checked, including plain `W`), which VASP reads as an incompatible exchange-correlation functional and refuses to run. Fixed by replacing the `W_sv` override with plain `W` (valid PBE, verified).

- **A112W** failed again after that fix, this time with a VASP SIGSEGV — exactly the known issue flagged in the mission brief (`ulimit -s unlimited` before `vasp_std`), present in `submit_array.sh` but forgotten in `prepare_vasp_lobster.py`'s per-compound SLURM template. Fixed; recovered on retry.

Final success rate: **186/186**.

8 Compute Cost

	VASP	LOBSTER
Mean (s)	124	397
Median (s)	72	145
Max (s)	1440	6675
Sequential total	6.4 h	19.1 h

Actual elapsed wall-clock time (8-way concurrency): ~ 3.5 h, within the 6 h overnight budget.

9 Limits and Next Steps

- **Sample size:** 186 overall, but 88/23/9 once split by bond type — the "ionic" correlations ($n = 9$) are not interpretable.
- **Primitive vs. conventional cell** (carried over from the pilot report): not addressed here. Most likely explanation for the weak observed correlations — the strongest bond can sit entirely inside the primitive cell and contribute to no non-contractile cycle at all, biasing the measured "weakest link."
- **No true dynamical "unstable" class:** `theo_metastable` is a proxy (never synthesized), not a phonon-calculation result.
- **classify() coverage:** 35% of compounds unclassified.
- **Why not SISSO yet:** a single candidate descriptor (the percolation weight, in two algebraically related variants), compared against aggregates that are themselves functions of the same underlying ICOHP values — no meaningful combinatorial search space yet. Justifying SISSO would require: (a) several conceptually novel candidate descriptors, (b) per-stratum $n \geq 50$ –100, (c) a clearer signal than $AUC \approx 0.5$.

10 Conclusion

The 186-compound dataset was built, computed (VASP+LOBSTER), and analyzed end to end, with two compute failures diagnosed and fixed at the source. The headline result is a *negative* but quantified and honest one: at this sample size, the percolation descriptor shows no significant correlation with thermodynamic stability, and demonstrates no advantage over classic ICOHP aggregates. The priority actions (§9) — especially conventional-cell reprocessing and a targeted extension of the metallic subsample — are likely to move this result before a SISSO-class tool is warranted.

Source code: <https://github.com/John-Akapulco/viability>

Data: `analysis/percolation_vs_hull.csv`

Detailed report: `analysis/REPORT.md`


11 Campaign 2 follow-ups (missions #3 to #5)

Three further descriptors were built in later sessions, all tested against `formation_energy_per_atom` (introduced in mission #3 as an alternative target to `energy_above_hull`, generally more correlatable) rather than the hull. Missions #3 and #4 reuse the 186-compound dataset above unmodified; mission #5 draws in part on a **74-compound extension campaign** (`extension_*`: elemental references, ionic compounds and polymorphs outside the main set), not reprocessed into this report’s appendices — see the repository’s `README.md` for its full detail.

A pattern repeats across all three missions: each new descriptor reaches a statistically significant *global* correlation, stronger than anything the percolation weight ever achieved (§9) — but in all three cases that global correlation turns out to be substantially, or entirely, a clustering effect between bond types or between metals and gapped compounds, rather than a robust relationship *within* a homogeneous group.

11.1 Mission #3: network dimensionality and periodic min-cut


Two new descriptors, `percolation_path.py` left unchanged: `network_dimensionality.py` (0D–3D classification via a relative bond-strength threshold + breadth-first search) and `periodic_mincut.py` (minimum cut via `networkx` max-flow, separability rather than traversability). Headline: the normalized min-cut is the **first descriptor in the project to reach a significant global correlation** ($\rho = 0.285$, $p = 1.0 \times 10^{-4}$, $n = 186$), likely driven in part by between-bond-type clustering; dimensionality alone does not separate `formation_energy_per_atom` (Kruskal–Wallis $p = 0.19$).



11.2 Mission #4: antibonding population near the Fermi level


A distinct question: not the integrated ICOHP (one number per bond), but *how* COHP is distributed in energy — the occupied antibonding fraction just below the Fermi level/VBM, by analogy with Peierls/Jahn–Teller electronic instabilities (new module `cohp_extraction.py`, validated by exact cross-check against `ICOHPLIST.lobster` on the 6 pilot compounds). Headline: $\rho = -0.328$, $p = 5.0 \times 10^{-6}$ ($n = 186$) — the strongest global correlation in the project at the time. The sign is *opposite* the naive Peierls/Jahn–Teller reading. Diagnostics: the effect is substantially driven by metal/gapped clustering, but the `bond_type=covalent` subgroup ($n = 23$) survives

stratification ($p = 0.018$ – 0.029) — the only subgroup in the project, to date, to hold up under such a test.



11.3 Mission #5: reaction ICOHP

An ICOHP analog of `formation_energy_per_atom`: is a compound’s total ICOHP “cheaper” than the same atoms in elemental reference form (new module `reaction_icohp.py`, reaction balanced via `pymatgen.analysis.reaction_calculator`)? Extended to 192 compounds using the 74-compound extension campaign (62 elemental references computed). Headline: $\rho = 0.370$, $p = 3.9 \times 10^{-7}$ ($n = 177$) — numerically the strongest global correlation in the project to date, this time with an intuitive sign (less bonding than the elemental state $\Rightarrow$ less stable formation). But **no bond_type subgroup survives stratification** (Kruskal–Wallis $p = 2.1 \times 10^{-6}$ for the descriptor, $p = 5.0 \times 10^{-8}$ for the target, across the three strata) — unlike mission #4, the clustering effect here explains the entire observed signal. Against `energy_above_hull` the correlation is absent ($\rho = 0.09$, $p = 0.20$).



11.4 Comparative summary

All four descriptors tested against `formation_energy_per_atom`, on the same common subsample ($n = 177$, the intersection of campaign 2’s 186 compounds and mission #5’s 192 computable rows):

Descriptor	n	ρ	p
Reaction ICOHP (mission #5)	177	0.370	3.9×10^{-7}
Antibonding population, normalized (mission #4)	177	-0.337	4.5×10^{-6}
Periodic min-cut, normalized (mission #3)	177	0.313	2.3×10^{-5}
Percolation weight, normalized (mission #1)	177	0.104	0.170

Ranking by raw correlation strength (ρ) is not the same as ranking by reliability: mission #5 leads numerically but is also the only one where *no* subgroup survives stratification (above), whereas mission #4 keeps a significant covalent subgroup. **Still no SISSO**: four descriptors now show a global signal, but none yet sits in the clean, well-powered-per-stratum situation that would justify a combinatorial symbolic search.

Detailed reports: `analysis/REPORT_dimensionality_mincut.md`, `analysis/REPORT_antibonding.md`, `analysis/REPORT_reaction_icohp.md`.

A Compound List

The 186 compounds in the dataset, grouped by category (family), with their Materials Project identifier, PBE thermodynamic hull distance (`energy_above_hull`), and the minimum ICOHP percolation weight (`icohp_percolation_weight_min`, this work’s main metric). Auto-generated from `analysis/percolation_vs_hull.csv` by `report/gen_appendix.py`.

Table 1: Complete list of the 186 compounds, grouped by category, with their Materials Project identifier, PBE hull distance, and minimum ICOHP percolation weight.

Formula	mp-id	Bonding	E_{hull} (eV/at)	Percolation weight (eV)
Experimental, stable (hull) ($n = 63$)				
As ₂ S ₃	mp-1189572	covalent	0.0000	1.00e-05
AsF ₃	mp-28027	covalent	0.0000	0.00e+00
BI ₃	mp-23189	covalent	0.0000	1.00e-05
BW	mp-7832	—	0.0000	1.90e-04
BaAu ₂	mp-30363	metallic	0.0000	5.19e-02
BaCl ₂	mp-568662	ionic	0.0000	1.31e-02
BaH ₂	mp-23715	—	0.0000	2.40e-04
Be ₂ Cu	mp-2031	metallic	0.0000	1.15e-03
Be ₂ Nb ₃	mp-11272	metallic	0.0000	6.36e-03
Be ₂ V	mp-11281	metallic	0.0000	6.80e-04
CaAl ₄	mp-1749	metallic	0.0000	1.03e-02
CaSn	mp-2450	metallic	0.0000	5.23e-03
CdPd	mp-1696	metallic	0.0000	9.00e-05
CoB	mp-20857	—	0.0000	6.00e-05
Cs ₂ As ₃	mp-15557	—	0.0000	2.02e-02
FeS	mp-505531	—	0.0000	3.05e-03
Ge ₂ O _s	mp-10032	metallic	0.0000	1.21e-02
HfTc ₂	mp-1095669	metallic	0.0000	1.77e-02
Hg ₄ Pt	mp-936	metallic	0.0000	3.36e-03
HgF ₂	mp-8177	—	0.0000	8.95e-03

Table 1 (continued)

Formula	mp-id	Bonding	E_{hull} (eV/at)	Percolation weight (eV)
InBr	mp-22870	covalent	0.0000	1.02e-02
KI	mp-22898	ionic	0.0000	2.26e-02
KN3	mp-827	—	0.0000	2.80e-04
Li2Se	mp-2286	—	0.0000	1.16e-02
LiB	mp-1001835	—	0.0000	2.91e-03
Mg2Ni	mp-2137	metallic	0.0000	1.60e-04
MgP4	mp-384	—	0.0000	0.00e+00
MnAl12	mp-1104165	metallic	0.0000	1.42e-02
MoSe2	mp-1634	covalent	0.0000	1.16e-03
NaS	mp-2400	—	0.0000	0.00e+00
Na	mp-10172	—	0.0000	1.97e-03
Nb3Ir	mp-1458	metallic	0.0000	9.02e-03
NbGa3	mp-1973	metallic	0.0000	8.58e-03
PI2	mp-29443	covalent	0.0000	2.30e-04
PbSe	mp-2201	covalent	0.0000	1.66e-02
RbI	mp-22903	ionic	0.0000	2.00e-02
Sc5Ge3	mp-17190	metallic	0.0000	5.30e-04
ScAg2	mp-1018128	metallic	0.0000	1.70e-04
ScTe	mp-10026	—	0.0000	7.12e-03
SnPt	mp-19856	metallic	0.0000	1.29e-02
SrO2	mp-2697	ionic	0.0000	4.40e-04
SrSi	mp-2661	metallic	0.0000	7.00e-05
Ta5Ge3	mp-17593	metallic	0.0000	3.46e-02
TaP	mp-1067587	—	0.0000	3.14e-02
TaSb2	mp-11697	metallic	0.0000	1.17e-02
Te2Pd	mp-782	—	0.0000	1.44e-02
Te2Ru	mp-267	covalent	0.0000	4.34e-03
TeO2	mp-8377	covalent	0.0000	4.00e-05
Ti3In	mp-866046	metallic	0.0000	5.01e-03
Ti3Pt	mp-2339	metallic	0.0000	1.78e-03
TiBe12	mp-1104067	metallic	0.0000	2.40e-04
TiNi	mp-1048	metallic	0.0000	3.91e-03
TiO	mp-1071163	—	0.0000	6.40e-04
TiSi2	mp-1077503	metallic	0.0000	6.18e-03
TlCl	mp-571079	—	0.0000	7.17e-03
VNi2	mp-11531	metallic	0.0000	3.88e-03
WO2	mp-1524394	—	0.0000	2.20e-04
Zr2Au	mp-2348	metallic	0.0000	3.06e-02
Zr5Pb3	mp-681992	metallic	0.0000	2.00e-05
ZrMo2	mp-2049	metallic	0.0000	1.05e-02
Si	mp-149	covalent	0.0000	3.17e-03
NaCl	mp-22862	ionic	0.0000	3.07e-02
AlNi	mp-1487	metallic	0.0000	4.19e-03
Experimental, metastable ($n = 63$)				
CdI2	mp-567259	—	0.0005	2.38e-02
MgCl2	mp-570259	ionic	0.0006	1.90e-04
C	mp-169	covalent	0.0008	2.50e-04
ZrBr	mp-1065846	—	0.0008	7.88e-03
Li3Hg	mp-1646	metallic	0.0013	1.20e-03
Ta7Co6	mp-1104548	metallic	0.0015	3.10e-04
CaGa4	mp-2461	metallic	0.0016	1.91e-02
InCl	mp-571636	covalent	0.0016	8.50e-03
NiB	mp-14019	—	0.0018	4.10e-04
MgH2	mp-23711	—	0.0019	1.00e-05

Table 1 (continued)

Formula	mp-id	Bonding	E_{hull} (eV/at)	Percolation weight (eV)
Sn7Ir5	mp-20466	metallic	0.0024	1.00e-02
NaN3	mp-1066400	—	0.0029	7.00e-04
ClF3	mp-556767	—	0.0030	0.00e+00
SiS2	mp-1095294	covalent	0.0030	1.00e-04
Sr5Sn3	mp-17720	metallic	0.0030	1.08e-02
Te2Ir	mp-1551	—	0.0030	2.80e-03
Li13Sn5	mp-30769	metallic	0.0033	8.50e-04
H3N	mp-643432	covalent	0.0038	0.00e+00
Cs2Se	mp-1011696	—	0.0042	2.62e-02
In3Ir	mp-630976	metallic	0.0043	2.04e-03
HI	mp-697025	—	0.0044	0.00e+00
Rb2Hg7	mp-31474	metallic	0.0045	3.14e-02
PbAu2	mp-19871	metallic	0.0047	2.01e-03
BeCu	mp-2323	metallic	0.0050	4.80e-04
SiO2	mp-546794	covalent	0.0056	1.50e-04
IF7	mp-27988	—	0.0063	0.00e+00
K	mp-10157	—	0.0069	8.07e-02
Al3Os2	mp-16521	metallic	0.0074	6.23e-03
Nb2O5	mp-1595	—	0.0075	1.00e-04
LiBr	mp-23259	ionic	0.0099	9.88e-02
ZnAg	mp-1912	metallic	0.0112	9.67e-03
MgPd3	mp-7753	metallic	0.0114	2.21e-03
AsPd2	mp-1080831	—	0.0118	3.50e-04
GeSe2	mp-10074	covalent	0.0125	4.00e-05
Re3Ge7	mp-29141	metallic	0.0126	2.42e-03
Cu3Ge	mp-19724	metallic	0.0126	5.30e-04
Ti3Ge	mp-1189044	metallic	0.0130	1.40e-02
ZrGa3	mp-30685	metallic	0.0130	7.64e-03
SrAl2	mp-1638	metallic	0.0136	5.36e-03
NiS	mp-1547	—	0.0142	3.00e-04
Al12W	mp-11227	metallic	0.0152	1.37e-02
CsH	mp-632319	—	0.0161	2.66e-02
CaGa2	mp-992	metallic	0.0170	1.66e-02
NiHg4	mp-570835	metallic	0.0171	1.09e-03
SiRh	mp-2287	metallic	0.0246	1.10e-02
BaSn5	mp-571353	metallic	0.0262	4.58e-03
PS	mp-612	covalent	0.0265	8.00e-05
AsRh	mp-22079	—	0.0269	1.93e-03
Te2Au	mp-567525	—	0.0274	1.62e-02
Be3N2	mp-6977	—	0.0315	2.00e-05
Y2O3	mp-558573	—	0.0342	5.00e-05
AgO	mp-1079720	—	0.0423	4.00e-05
FeTe2	mp-1102002	—	0.0449	5.20e-04
H2O	mp-2739191	—	0.0494	0.00e+00
CdO2	mp-2310	—	0.0562	9.00e-05
Mo3Se4	mp-21021	—	0.0609	1.84e-03
PbSe	mp-22009	covalent	0.0731	1.68e-02
Be12Pd	mp-12666	metallic	0.0795	5.00e-05
Sr2As	mp-15697	—	0.0800	2.06e-03
AsRh2	mp-1102364	—	0.0806	4.63e-03
ZrRh	mp-2808	metallic	0.0839	3.50e-02
K2S	mp-559278	—	0.0873	1.07e-02
Ge4Rh	mp-1104286	metallic	0.0907	2.08e-03

Theoretical, metastable ($n = 60$)

Table 1 (continued)

Formula	mp-id	Bonding	E_{hull} (eV/at)	Percolation weight (eV)
Li3Ag	mp-976408	metallic	0.0013	1.15e-02
Y3Co	mp-1189329	metallic	0.0016	1.50e-02
TiNi	mp-1067248	metallic	0.0020	5.29e-03
TaP	mp-1187244	—	0.0033	3.59e-02
Sr3As4	mp-678007	—	0.0062	4.47e-03
Ga2Se3	mp-1224809	covalent	0.0063	1.14e-02
MnN	mp-1009130	covalent	0.0151	1.85e-03
BeCl2	mp-1190080	ionic	0.0187	2.37e-03
MgSn	mp-1094801	metallic	0.0212	4.26e-03
TiW	mp-1216621	metallic	0.0225	2.25e-03
SrTi3	mp-1206636	metallic	0.0294	3.29e-03
IrCl3	mp-729507	—	0.0301	2.72e-03
Ta4C3	mp-1218000	—	0.0335	1.44e-03
Sc2O3	mp-755313	—	0.0364	5.10e-04
SnBr2	mp-978985	covalent	0.0405	3.40e-04
Sn7Pd5	mp-1219006	metallic	0.0414	2.30e-03
Tl4Sn	mp-1216560	metallic	0.0459	1.00e+00
LiTi3	mp-1185253	metallic	0.0467	3.35e-03
PtCl2	mp-1219748	—	0.0490	5.04e-03
HCl	mp-684609	—	0.0536	2.50e-04
MgSn	mp-1094669	metallic	0.0560	2.60e-04
K5As4	mp-684799	—	0.0564	8.80e-03
KSn3	mp-1185151	metallic	0.0573	2.65e-02
NbS2	mp-774873	—	0.0576	1.20e-04
YAg3	mp-1187811	metallic	0.0594	1.12e-03
B3Ir2	mp-1228647	—	0.0609	2.80e-04
TiMo2	mp-1216675	metallic	0.0613	3.77e-02
Cr2C	mp-1226378	—	0.0625	2.08e-03
ZrO2	mp-775909	—	0.0627	1.20e-04
Zn	mp-2647117	—	0.0717	1.04e-02
IN2	mp-1097011	—	0.0730	4.70e-04
CoSe2	mp-1390196	—	0.0734	8.40e-04
GeS	mp-12910	covalent	0.0762	2.26e-03
ZrTi	mp-1215236	metallic	0.0883	3.15e-02
VCo3	mp-1095057	metallic	0.0942	2.93e-03
Tl3Ga	mp-1187539	metallic	0.0972	5.00e-05
CaGe2	mp-643542	metallic	0.0979	1.30e-02
NbRh2	mp-1220414	metallic	0.1043	1.76e-02
TcW	mp-1217337	metallic	0.1056	4.10e-03
MgF2	mp-560236	ionic	0.1076	2.00e-05
VN	mp-1017532	—	0.1080	4.00e-05
Na2Cl	mp-990084	—	0.1105	3.76e-02
ZnPb3	mp-1187949	metallic	0.1107	4.51e-03
Sr3Sn	mp-1187136	metallic	0.1111	7.94e-03
TaRe	mp-1217894	metallic	0.1113	6.98e-02
Al4Si	mp-1228120	metallic	0.1149	8.54e-02
B6Pb	mp-1096825	covalent	0.1151	2.35e-03
ScTc3	mp-867262	metallic	0.1154	3.31e-02
CrMo	mp-1226200	metallic	0.1163	4.23e-02
BPd5	mp-1228665	—	0.1325	2.42e-02
Zr3Be	mp-1188016	metallic	0.1430	1.05e-03
Na3Cl	mp-1064484	—	0.1456	2.55e-03
SiAu3	mp-1186998	metallic	0.1643	5.68e-03
InSe2	mp-1232036	—	0.1733	1.64e-03
TiSi2	mp-570991	metallic	0.1796	1.35e-02

Table 1 (continued)

Formula	mp-id	Bonding	E_{hull} (eV/at)	Percolation weight (eV)
BeAu3	mp-983539	metallic	0.1818	2.41e-02
Zr3Ge	mp-1188039	metallic	0.1851	6.59e-03
AlSb	mp-1023918	metallic	0.1878	3.60e-04
Mg15B	mp-1023515	—	0.1943	2.80e-04
HfMo	mp-1224314	metallic	0.1991	2.00e-02

B VASP Calculation Parameters

Fixed INCAR parameters, identical across all 186 compounds (static, LOBSTER-compatible run) — only NBANDS (appendix D) and the k-point grid vary by compound.

Parameter	Value	Description
PREC	Accurate	Overall precision (charge grid, projectors)
ENCUT	600.0	Plane-wave cutoff energy (eV)
EDIFF	1e-06	Electronic convergence criterion (eV)
IBRION	-1	Ionic dynamics type (-1 = static, no relaxation)
NSW	0	Number of ionic steps (0 = static run on the MP structure)
ISMear	0	Smearing type (0 = Gaussian)
SIGMA	0.05	Smearing width (eV)
LASPH	True	Non-spherical corrections to the PAW potential
ISYM	-1	Symmetry (-1 = disabled, required by LOBSTER)
LWAVE	True	Write WAVECAR (required by LOBSTER)
LCHARG	True	Write CHGCAR
NPAR	4	Band-level parallelization
KPAR	2	K-point-level parallelization

C PAW-PBE Potentials

One PAW-PBE potential per element present in the dataset (pymatgen’s MPRelaxSet library — the same one Materials Project used to relax the input structures), with one documented exception for tungsten (§7): the recommended `W_pv` variant is absent from the local mirror, and `W_sv` turned out to be corrupted (missing `LEXCH` field) — plain `W` is used instead, verified valid.

Table 2: PAW-PBE potentials used, one per element present in the dataset (pymatgen’s MPRelaxSet library, with one documented exception: `W` substituted for `W_pv`/`W_sv`, see §7).

Element	PAW-PBE potential
Ag	Ag (02Apr2005)
Al	Al (04Jan2001)
As	As (22Sep2009)
Au	Au (04Oct2007)
B	B (06Sep2000)
Ba	Ba_sv (06Sep2000)

Element	PAW-PBE potential
Be	Be_sv (06Sep2000)
Br	Br (06Sep2000)
C	C (08Apr2002)
Ca	Ca_sv (06Sep2000)
Cd	Cd (06Sep2000)
Cl	Cl (06Sep2000)
Co	Co (02Aug2007)
Cr	Cr_pv (02Aug2007)
Cs	Cs_sv (25Jan2019)
Cu	Cu_pv (06Sep2000)
F	F (08Apr2002)
Fe	Fe_pv (02Aug2007)
Ga	Ga_d (06Jul2010)
Ge	Ge_d (03Jul2007)
H	H (15Jun2001)
Hf	Hf_pv (06Sep2000)
Hg	Hg (06Sep2000)
I	I (08Apr2002)
In	In_d (06Sep2000)
Ir	Ir (06Sep2000)
K	K_sv (06Sep2000)
Li	Li_sv (10Sep2004)
Mg	Mg_pv (13Apr2007)
Mn	Mn_pv (02Aug2007)
Mo	Mo_pv (04Feb2005)
N	N (08Apr2002)
Na	Na_pv (19Sep2006)
Nb	Nb_pv (08Apr2002)
Ni	Ni_pv (06Sep2000)
O	O (08Apr2002)
Os	Os_pv (20Jan2003)
P	P (06Sep2000)
Pb	Pb_d (06Sep2000)
Pd	Pd (04Jan2005)
Pt	Pt (04Feb2005)
Rb	Rb_sv (06Sep2000)
Re	Re_pv (06Sep2000)
Rh	Rh_pv (25Jan2005)
Ru	Ru_pv (28Jan2005)
S	S (06Sep2000)
Sb	Sb (06Sep2000)
Sc	Sc_sv (07Sep2000)
Se	Se (06Sep2000)
Si	Si (05Jan2001)
Sn	Sn_d (06Sep2000)
Sr	Sr_sv (07Sep2000)
Ta	Ta_pv (07Sep2000)
Tc	Tc_pv (04Feb2005)
Te	Te (08Apr2002)
Ti	Ti_pv (07Sep2000)
Tl	Tl_d (06Sep2000)
V	V_pv (07Sep2000)
W	W (08Apr2002)
Y	Y_sv (25May2007)
Zn	Zn (06Sep2000)
Zr	Zr_sv (04Jan2005)

D k-point Grid and NBANDS per Compound

k-point grid auto-generated by `pymatgen.io.vasp.Kpoints.automatic_density_by_vol` (density `kppvol=100`, Γ -centered or Monkhorst–Pack mesh depending on cell symmetry) and NBANDS, derived per compound from the number of local orbitals in the LOBSTER basis (`Lobsterin.write_INCAR`) — a strictly sufficient value for the local-basis projection, not a fixed guess.

Table 3: k-point grid (`pymatgen` automatic density, `kppvol=100`) and number of bands (derived from the LOBSTER basis) per compound.

Formula	mp-id	k-point grid	NBANDS
Experimental, stable (hull) ($n = 63$)			
As ₂ S ₃	mp-1189572	5 3 2 (G)	80
AsF ₃	mp-28027	5 4 4 (G)	64
BI ₃	mp-23189	4 4 4 (G)	32
BW	mp-7832	9 9 3 (G)	52
BaAu ₂	mp-30363	6 6 7 (G)	23
BaCl ₂	mp-568662	6 6 6 (G)	13
BaH ₂	mp-23715	6 4 3 (G)	28
Be ₂ Cu	mp-2031	7 7 7 (G)	38
Be ₂ Nb ₃	mp-11272	8 4 4 (M)	74
Be ₂ V	mp-11281	7 7 4 (G)	76
CaAl ₄	mp-1749	7 7 4 (G)	21
CaSn	mp-2450	6 6 4 (M)	28
CdPd	mp-1696	7 6 6 (G)	36
CoB	mp-20857	9 7 5 (G)	52
Cs ₂ As ₃	mp-15557	4 4 3 (G)	44
FeS	mp-505531	8 8 5 (G)	26
Ge ₂ Os	mp-10032	9 6 4 (G)	54
HfTc ₂	mp-1095669	5 5 3 (G)	108
Hg ₄ Pt	mp-936	5 5 5 (G)	45
HgF ₂	mp-8177	8 8 8 (G)	17
InBr	mp-22870	6 6 4 (M)	26
KI	mp-22898	6 6 6 (G)	9
KN ₃	mp-827	5 5 5 (G)	34
Li ₂ Se	mp-2286	7 7 7 (G)	14
LiB	mp-1001835	7 7 9 (G)	18
Mg ₂ Ni	mp-2137	5 5 2 (G)	102
MgP ₄	mp-384	5 5 3 (G)	40
MnAl ₁₂	mp-1104165	4 4 4 (M)	57
MoSe ₂	mp-1634	9 9 2 (G)	34
NaS	mp-2400	6 6 3 (G)	32
Na	mp-10172	8 8 4 (G)	8
Nb ₃ Ir	mp-1458	5 5 5 (G)	72
NbGa ₃	mp-1973	8 8 6 (M)	36
PI ₂	mp-29443	6 4 3 (G)	24
PbSe	mp-2201	7 7 7 (G)	13
RbI	mp-22903	6 6 6 (G)	9
Sc ₅ Ge ₃	mp-17190	3 3 5 (G)	154
ScAg ₂	mp-1018128	8 8 5 (G)	28
ScTe	mp-10026	7 7 4 (G)	28
SnPt	mp-19856	7 7 5 (G)	36
SrO ₂	mp-2697	8 8 7 (G)	13
SrSi	mp-2661	7 6 4 (G)	18
Ta ₅ Ge ₃	mp-17593	4 4 4 (M)	144

Table 3 (continued)

Formula	mp-id	k-point grid	NBANDS
TaP	mp-1067587	9 9 4 (G)	26
TaSb2	mp-11697	8 5 4 (G)	34
Te2Pd	mp-782	7 7 5 (G)	17
Te2Ru	mp-267	7 5 4 (G)	34
TeO2	mp-8377	6 5 3 (G)	48
Ti3In	mp-866046	5 5 6 (G)	72
Ti3Pt	mp-2339	5 5 5 (G)	72
TiBe12	mp-1104067	7 5 5 (G)	69
TiNi	mp-1048	10 7 6 (G)	36
TiO	mp-1071163	10 6 6 (G)	39
TiSi2	mp-1077503	8 8 4 (M)	34
TlCl	mp-571079	6 6 4 (M)	26
VNi2	mp-11531	12 8 7 (G)	27
WO2	mp-1524394	6 5 5 (G)	68
Zr2Au	mp-2348	9 9 4 (G)	29
Zr5Pb3	mp-681992	3 3 5 (G)	154
ZrMo2	mp-2049	6 6 6 (G)	56
Si	mp-149	8 8 8 (G)	100
NaCl	mp-22862	8 8 8 (G)	100
AlNi	mp-1487	10 10 10 (M)	100
Experimental, metastable ($n = 63$)			
CdI2	mp-567259	7 7 4 (G)	17
MgCl2	mp-570259	8 8 5 (G)	12
C	mp-169	12 12 8 (M)	100
ZrBr	mp-1065846	8 8 3 (G)	28
Li3Hg	mp-1646	7 7 7 (G)	24
Ta7Co6	mp-1104548	6 6 3 (G)	117
CaGa4	mp-2461	7 7 5 (G)	41
InCl	mp-571636	6 6 4 (M)	26
NiB	mp-14019	10 10 7 (G)	26
MgH2	mp-23711	6 5 5 (G)	24
Sn7Ir5	mp-20466	4 4 4 (M)	108
NaN3	mp-1066400	7 7 7 (G)	16
ClF3	mp-556767	6 4 3 (G)	64
SiS2	mp-1095294	5 4 3 (G)	48
Sr5Sn3	mp-17720	3 3 3 (G)	104
Te2Ir	mp-1551	7 5 2 (G)	51
Li13Sn5	mp-30769	6 6 1 (G)	110
H3N	mp-643432	8 5 5 (G)	28
Cs2Se	mp-1011696	5 3 2 (G)	56
In3Ir	mp-630976	4 4 4 (M)	144
HI	mp-697025	3 3 3 (G)	40
Rb2Hg7	mp-31474	4 4 4 (G)	73
PbAu2	mp-19871	5 5 5 (G)	54
BeCu	mp-2323	10 10 10 (M)	100
SiO2	mp-546794	6 6 6 (M)	24
IF7	mp-27988	5 5 3 (G)	64
K	mp-10157	6 6 6 (G)	5
Al3Os2	mp-16521	9 9 3 (G)	30
Nb2O5	mp-1595	7 7 4 (G)	38
LiBr	mp-23259	8 8 8 (G)	100
ZnAg	mp-1912	9 9 9 (G)	18
MgPd3	mp-7753	7 7 7 (G)	31
AsPd2	mp-1080831	8 4 4 (G)	66

Table 3 (continued)

Formula	mp-id	k-point grid	NBANDS
GeSe2	mp-10074	5 5 5 (G)	34
Re3Ge7	mp-29141	9 6 1 (G)	180
Cu3Ge	mp-19724	6 6 5 (G)	72
Ti3Ge	mp-1189044	4 4 4 (M)	144
ZrGa3	mp-30685	7 7 5 (G)	37
SrAl2	mp-1638	5 5 5 (G)	26
NiS	mp-1547	6 6 6 (M)	39
Al12W	mp-11227	4 4 4 (M)	57
CsH	mp-632319	7 7 7 (G)	6
CaGa2	mp-992	7 7 6 (G)	23
NiHg4	mp-570835	6 6 6 (M)	45
SiRh	mp-2287	6 6 5 (G)	52
BaSn5	mp-571353	5 5 4 (G)	50
PS	mp-612	4 4 3 (G)	64
AsRh	mp-22079	8 5 4 (G)	52
Te2Au	mp-567525	7 7 5 (G)	17
Be3N2	mp-6977	10 10 3 (G)	46
Y2O3	mp-558573	8 4 3 (G)	96
AgO	mp-1079720	8 5 5 (G)	52
FeTe2	mp-1102002	4 4 4 (M)	68
H2O	mp-2739191	7 7 4 (G)	24
CdO2	mp-2310	5 5 5 (G)	68
Mo3Se4	mp-21021	4 4 4 (M)	86
PbSe	mp-22009	6 6 2 (G)	26
Be12Pd	mp-12666	6 6 6 (M)	69
Sr2As	mp-15697	6 6 3 (G)	28
AsRh2	mp-1102364	7 4 3 (G)	88
ZrRh	mp-2808	8 8 8 (M)	19
K2S	mp-559278	5 5 4 (G)	28
Ge4Rh	mp-1104286	4 4 3 (G)	135
Theoretical, metastable ($n = 60$)			
Li3Ag	mp-976408	7 7 7 (G)	24
Y3Co	mp-1189329	3 4 4 (G)	156
TiNi	mp-1067248	10 7 6 (G)	36
TaP	mp-1187244	9 9 9 (G)	13
Sr3As4	mp-678007	3 3 4 (G)	62
Ga2Se3	mp-1224809	5 5 5 (G)	30
MnN	mp-1009130	10 10 10 (G)	13
BeCl2	mp-1190080	3 3 3 (G)	78
MgSn	mp-1094801	8 8 6 (M)	13
TiW	mp-1216621	10 10 6 (M)	18
SrTi3	mp-1206636	5 5 5 (G)	32
IrCl3	mp-729507	3 3 6 (G)	84
Ta4C3	mp-1218000	6 6 6 (M)	48
Sc2O3	mp-755313	6 5 6 (G)	64
SnBr2	mp-978985	4 4 6 (M)	34
Sn7Pd5	mp-1219006	5 5 3 (G)	108
Tl4Sn	mp-1216560	5 5 5 (G)	45
LiTi3	mp-1185253	6 6 6 (M)	32
PtCl2	mp-1219748	5 5 4 (G)	34
HCl	mp-684609	7 7 7 (G)	5
MgSn	mp-1094669	8 8 8 (M)	13
K5As4	mp-684799	4 4 3 (G)	41
KSn3	mp-1185151	4 4 5 (G)	64

Table 3 (continued)

Formula	mp-id	k-point grid	NBANDS
NbS2	mp-774873	10 6 2 (M)	34
YAg3	mp-1187811	6 6 6 (G)	37
B3Ir2	mp-1228647	9 5 4 (G)	60
TiMo2	mp-1216675	5 6 14 (G)	27
Cr2C	mp-1226378	10 10 7 (G)	22
ZrO2	mp-775909	10 6 4 (M)	36
Zn	mp-2647117	11 11 11 (G)	9
IN2	mp-1097011	5 5 5 (G)	24
CoSe2	mp-1390196	4 4 4 (G)	68
GeS	mp-12910	7 7 5 (G)	26
ZrTi	mp-1215236	9 9 6 (G)	19
VCo3	mp-1095057	7 6 6 (G)	72
Tl3Ga	mp-1187539	5 5 5 (G)	36
CaGe2	mp-643542	7 7 6 (G)	23
NbRh2	mp-1220414	10 6 4 (M)	54
TcW	mp-1217337	10 10 6 (M)	18
MgF2	mp-560236	6 6 5 (G)	24
VN	mp-1017532	11 11 5 (G)	26
Na2Cl	mp-990084	6 6 6 (M)	12
ZnPb3	mp-1187949	5 5 5 (G)	36
Sr3Sn	mp-1187136	5 5 5 (G)	24
TaRe	mp-1217894	10 10 6 (M)	18
Al4Si	mp-1228120	6 6 6 (M)	20
B6Pb	mp-1096825	6 6 6 (M)	33
ScTc3	mp-867262	7 7 7 (G)	37
CrMo	mp-1226200	11 11 7 (G)	18
BPd5	mp-1228665	6 6 6 (M)	49
Zr3Be	mp-1188016	6 6 6 (M)	35
Na3Cl	mp-1064484	8 8 3 (G)	16
SiAu3	mp-1186998	7 7 7 (G)	31
InSe2	mp-1232036	7 7 3 (G)	34
TiSi2	mp-570991	8 8 8 (M)	17
BeAu3	mp-983539	7 7 7 (G)	32
Zr3Ge	mp-1188039	4 4 6 (G)	78
AlSb	mp-1023918	6 6 5 (G)	16
Mg15B	mp-1023515	4 4 3 (G)	64
HfMo	mp-1224314	10 10 6 (M)	18