

SUPPLIER Dalian Steelforce Hi-Tech Co., Ltd.

No. 26 Number 2 Street DD Port.

Dalian Development Zone, Liaoning, China.

TEST CERTIFICATE NUMBER

2021-04-05AGR17021AD1202

28-04-2021

DATE PRINTED PAGE 1 OF 1

CUSTOMER HJ ASMUSS WELLINGTON

CUSTOMER REFERENCE

110333

CUSTOMER ITEM NUMBER

PRODUCT DESCRIPTION

PRODUCT: 100x100x5.0/8m RHS

FINISH: NOPC

MATERIAL. Cold Formed Structural Steel Hollow Sections

SPECIFICATION: AS/NZS 1163:2016

GRADE: C350L0

Basic Oxygen, Continuously Cast, Fine Grained, Fully Killed Coil from Hot Strip Mill STEEL MAKING.

STEEL FEED:

MANUFACTURED DATE: 05-04-2021

CHEMICAL COMPOSITION (% of Elements by Mass)												
SGS Test Report Number	Heat Number	SGS Test Laboratory CNAS Accreditation Number	Analysis Type	С	P	Mn	Si	s	Ni	Cr	Мо	Cu
DLIN2103000612ML	AGR17021AD1202	L3437	L	0.060	0.014	51.300	0, 030	0.005	0.010	0.020	< 0.010	0.010

CHEMICAL COMPOSITION (% of Elements by Mass)												
SGS Test Report Number	Heat Number	SGS Test Laboratory CNAS Accreditation Number	Analysis Type	A1 (t) min = 0.02 max = 0.10	В	Ti	Nb	v	CE	CF2	CF3	
DLIN2103000612ML	AGR17021AD1202	L3437	L	0.034	0.0003	0. 020		< 0.5010	< 2.286	< 0.040	0.065	

Notes: Chemical Composition

Test Laboratory: SGS-CSTC Standards Technical Services Co., Ltd., Dalian Branch Analysis Type: Ladle and Cast Analysis (L); Product Analysis (P)

CF3 = Si+2.5PCE = C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15CF2 = Nh+V+Ti

MECHANICAL PROPERTIES												
		SGS Test						Impact Testing (Joules)			es)	
SGS Test Report		Laboratory CNAS Accreditation		Test	Yield		Elongation					
Number	Heat Number	Number	Test Type	Category	(Mpa)	(Mpa)	(%)	Test 1	Test 2	Test 3	Average	
DLIN2104000653ML	AGR17021AD1202	L3437	LSA	В	44999	4	31					
Only for hollow sections, flats, angles, and with nominal gauge ≥ 6mm									, and channels			

Test Laboratory: SGS-CSTC Standards Technical Services Co., Ltd., Dalian Branch

Test Type: LSA = Longitudinal strip specimen tested in the artificially aged condition

Test Category - B = Batch; S = Statistical Sampling

Gauge Length Method - E = 5.65xSQRT(So)

All Tensile properties are determined using samples from production personnel and tested in accordance with AS 1391:2007 and Amendment 1:2012

Notes: Impact Test

Test Laboratory: SGS-CSTC Standards Technical Services Co., Ltd., Dalian Branch

All Impact properties on gauges ≥ 6mm are determined using samples from production personnel and tested in accordance with AS 1544.2:2003 at 0°

For products complying to AS/NZS1163:2016 with a nominal thickness < 6.0mm LO properties have been derived as per Clause 9.4.2.3

MANAGEMENT SYSTEM CERTIFICATION:

Dalian Steelforce Hi-Tech Co., Ltd. has the following management system certificates:-

Standard ISO 9001:2015 Expiry Date 29/11/2021 Certificate Number

Certification Body British Standards Institution (BSI) FM 641461 ISO 14001:2015 EMS 641462 29/11/2021 British Standards Institution (BSI) British Standards Institution (BSI) ISO 45001:2018 OHS 641463 29/11/2021

JAS-ANZ ACCREDITED CONFORMANCE ASSESSMENT BODY:
Steelforce Australia Pty Ltd has the following product certification for it's Dalian Steelforce Hi-Tech Co., Ltd. manufacturing facility:-

Certification Body

Certificate Number Expiry Date BMP 680293 Expiry Date 20/09/2022 Certification Scheme BSI Benchmark Product Certification AS/NZS1163:2016 BMP 680293 British Standards Institution (BSI)

Australian Tube Mills has the following certification for product manufactured under exclusive agreement by Dalian Steelforce Hi-Tech Co.,Ltd.:-Standard Certificate Number Expiry Date Certification Scheme Certification Body AS/NZS1163 191003 31/12/2021 ACRS Product Certification Australasian Certification Authority for Reinforci Australasian Certification Authority for Reinforcing and Structural Steels

Dalian Steelforce Hi-Tech Co., Ltd., confirms that the information included in this Test Certificate agrees with the records of Dalian Steelforce Hi-Tech Co., Ltd. and the product supplied conforms to the requirements of the Standard.

Authorized Signatory:

Title: Quality Manager