

### PQ, Ferrite Cores (TDK)

| Part No. | W <sub>tcu</sub><br>grams | W <sub>tfe</sub><br>grams | MLT<br>cm | MPL<br>cm | W <sub>a</sub> | A <sub>c</sub><br>cm <sup>2</sup> | W <sub>a</sub><br>cm <sup>2</sup> | A <sub>p</sub><br>cm <sup>4</sup> | K <sub>g</sub><br>cm <sup>5</sup> | A <sub>t</sub><br>cm <sup>2</sup> | *AL<br>mh/1K |
|----------|---------------------------|---------------------------|-----------|-----------|----------------|-----------------------------------|-----------------------------------|-----------------------------------|-----------------------------------|-----------------------------------|--------------|
|          |                           |                           |           |           | A <sub>c</sub> |                                   |                                   |                                   |                                   |                                   |              |
| PQ20/16  | 7.4                       | 13.0                      | 4.4       | 3.74      | 0.765          | 0.620                             | 0.474                             | 0.294                             | 0.0167                            | 16.9                              | 1617         |
| PQ20/20  | 10.4                      | 15.0                      | 4.4       | 4.54      | 1.061          | 0.620                             | 0.658                             | 0.408                             | 0.0227                            | 19.7                              | 1313         |
| PQ26/20  | 31.0                      | 31.0                      | 5.6       | 4.63      | 0.508          | 1.190                             | 0.604                             | 0.718                             | 0.0613                            | 28.4                              | 2571         |
| PQ26/25  | 17.0                      | 36.0                      | 5.7       | 5.55      | 0.716          | 1.180                             | 0.845                             | 0.997                             | 0.0832                            | 32.6                              | 2187         |
| PQ32/20  | 18.9                      | 42.0                      | 6.6       | 5.55      | 0.475          | 1.700                             | 0.808                             | 1.373                             | 0.1417                            | 36.3                              | 3046         |
| PQ32/30  | 35.5                      | 55.0                      | 6.7       | 7.46      | 0.929          | 1.610                             | 1.496                             | 2.409                             | 0.2326                            | 46.9                              | 2142         |
| PQ35/35  | 59.0                      | 73.0                      | 7.5       | 8.79      | 1.126          | 1.960                             | 2.206                             | 4.324                             | 0.4510                            | 60.7                              | 2025         |
| PQ40/40  | 97.2                      | 95.0                      | 8.4       | 10.20     | 1.622          | 2.010                             | 3.260                             | 6.552                             | 0.6280                            | 77.1                              | 1792         |
| PQ50/50  | 158.5                     | 195.0                     | 10.3      | 11.30     | 1.321          | 3.280                             | 4.332                             | 14.209                            | 1.8120                            | 113.9                             | 2800         |

\*This AL value has been normalized for a permeability of 1K. For a close approximation of AL for other values of permeability, multiply this AL value by the new permeability in kilo-perm. If the new permeability is 2500, then use 2.5.