

### ETD, Ferrite Cores (Ferroxcube)

| Part No. | W <sub>tcu</sub><br>grams | W <sub>tfe</sub><br>grams | MLT<br>cm | MPL<br>cm | W <sub>a</sub> | A <sub>c</sub><br>cm <sup>2</sup> | W <sub>a</sub><br>cm <sup>2</sup> | A <sub>p</sub><br>cm <sup>4</sup> | K <sub>g</sub><br>cm <sup>5</sup> | A <sub>t</sub><br>cm <sup>2</sup> | *AL<br>mh/1K |
|----------|---------------------------|---------------------------|-----------|-----------|----------------|-----------------------------------|-----------------------------------|-----------------------------------|-----------------------------------|-----------------------------------|--------------|
|          |                           |                           |           |           | A <sub>c</sub> |                                   |                                   |                                   |                                   |                                   |              |
| ETD-29   | 32.1                      | 28.0                      | 6.4       | 7.20      | 1.865          | 0.761                             | 1.419                             | 1.0800                            | 0.0517                            | 42.5                              | 1000         |
| ETD-34   | 43.4                      | 40.0                      | 7.1       | 7.87      | 1.757          | 0.974                             | 1.711                             | 1.6665                            | 0.0911                            | 53.4                              | 1182         |
| ETD-39   | 69.3                      | 60.0                      | 8.3       | 9.22      | 1.871          | 1.252                             | 2.343                             | 2.9330                            | 0.1766                            | 69.9                              | 1318         |
| ETD-44   | 93.2                      | 94.0                      | 9.4       | 10.30     | 1.599          | 1.742                             | 2.785                             | 4.8520                            | 0.3595                            | 87.9                              | 1682         |
| ETD-49   | 126.2                     | 124.0                     | 10.3      | 11.40     | 1.627          | 2.110                             | 3.434                             | 7.2453                            | 0.5917                            | 107.9                             | 1909         |
| ETD-54   | 186.9                     | 180.0                     | 11.7      | 12.70     | 1.609          | 2.800                             | 4.505                             | 12.6129                           | 1.2104                            | 133.7                             | 2273         |
| ETD-59   | 237.7                     | 260.0                     | 12.9      | 13.90     | 1.410          | 3.677                             | 5.186                             | 19.0698                           | 2.1271                            | 163.1                             | 2727         |

\*This AL value has been normalized for a permeability of 1K. For a close approximation of AL for other values of permeability, multiply this AL value by the new permeability in kilo-perm. If the new permeability is 2500, then use 2.5.