

POR-ROK® HALCO GROUT

Premium Cement Based Non-Shrink Grout

DESCRIPTION

POR-ROK® HALCO GROUT is a premium non-shrink, non-ferrous grout that is easily mixed for grouting at any consistency; dry-pack, plastic, or pourable. It contains no iron particles chlorides or gypsum, and will not corrode, shrink, rust or ravel even under consistently moist conditions. When mixed according to instructions, it produces a high compressive strength due to a technology that reduces the water/cement ratio.

FEATURES/BENEFITS

- Pourable, Pumpable and Dry-Pack Consistency
- Non Shrink
- Non-Metallic - Non Corrosive
- Interior / Exterior Applications
- No heating or two component mixing needed
- Holds several DOT specifications

APPLICATION

Substrate Preparation: First remove all dirt, oil, grease or contaminants from surfaces to be grouted. Then remove all loose material. Metals which will come in contact with grout must be de-rusted, or freed of paints, oils and greases. To avoid entrapment of air, provide air relief openings where required. Prior to placement of grout, thoroughly soak or dampen all concrete areas to be grouted. Then remove excess water from voids and holes.

MIXING AND APPLICATION:

POR-ROK® HALCO GROUT is a one step, ready to use mixture. Just add water, nothing more. For uniform mix, use paddle or drum type mechanical mortar mixers. Do not mix for more than 5 minutes. Place grout immediately after mixing. The temperature of the grout, the environment, and the configuration of the area to be grouted can each or in combination affect the time during which grout can be successfully worked. To be safe, complete grouting within 40 minutes of initial mixing.

FORMING machinery bases and column base plates: Follow standard forming procedures, which permit complete and proper placement of fluid grout, including use of head forms. All support elements should be anchored to prevent movement. Do not remove supports until grout has sufficiently hardened. Wood surfaces, which absorb moisture, should be pretreated with forming oils. When grouting edges of concrete which are less than 1" thick cut edges back to form a uniform butt edge.

PLACEMENT:

Follow the standard grouting procedure and recommendations of ICRI for the placement and curing to concrete. Use chains, rods, or tamping devices to compact grout, taking care to remove all air voids. For optimum results, air temperature should be near 72° F.

APPLICATION CONT.

Pour grout quickly and continuously, striking off exposed areas. Finished POR-ROK HALCO GROUT should be cured for 72 hours before base plate application.

APPLICATIONS DEEPER THAN 3" (EXTENSION)

Mix for a total of five minutes ensuring uniform consistency. For placements greater in depth than 3 inches, up to 25 lbs. of washed 3/8 inch pea gravel must be added to each 57.5 lbs. bag of grout. The approximate working time is 30 minutes. This will vary depending on substrate conditions.

TYPICAL TEST DATA

Compressive Strength (ASTM C109) Plastic Consistency	
1 day	4500 psi
7 days	10250 psi
28 days	11100 psi
Compressive Strength (ASTM C109) Flowable Consistency	
1 day	4200 psi
7 days	9175 psi
28 days	10125 psi
Compressive Strength (ASTM C109) Fluid Consistency	
1 day	400 psi
7 days	7400 psi
28 days	8500 psi
Flexural Strength (ASTM C-293)	
Plastic (28 Day)	1400 psi
Flowable (28 Day)	1200 psi
Fluid (28 Day)	1000 psi
Tensile Strength (ASTM C-496)	
Plastic (28 Day)	1400 psi
Flowable (28 Day)	1200 psi
Fluid (28 Day)	1000 psi

SPECCHEM 
Solution to Service

1511 Baltimore Ave, Suite 600
Kansas City, MO 64108
www.specchemllc.com 866.791.8700

APPLICATION CONT.

CURING:

Exposed grout surfaces must be cured. CGM recommends using a curing compound, cure & seal or a wet cure for 3 days. Maintain the temperature of the grout and contact area at 45°F to 90°F for a minimum of 24 hours.

APPLICATION NOTES:

1. It is the responsibility of the contractor to review the complete technical datasheets of CGM products referenced above as more detailed information may be required. The information provided above acts only as a general guideline and may vary based on jobsite conditions.
2. Apply POR-ROK® HALCO GROUT immediately after mixing.
3. Not for use in moving cracks.
4. Not for use as a surface applied material or coating.
5. Maintain minimum application widths and depths.

SPECIFICATION/COMPLIANCE

- ASTM C-1107, standard specification for packaged dry, hydraulic cement grout (non-shrink)
- CRD-C 621-89, specification for non-shrink grout
- CRD – C 614, method of test for time of setting of grout mixtures
- ASTM C-109, standard test for compressive strength of hydraulic cement mortars
- ASTM C-266, (CRD-C 222), standard test for time of setting of hydraulic cement by Gillmore Needle
- ASTM C-232 (CRD-C 79), standard method of test for bleeding of concrete
- ASTM C-827-82, standard test method for early volume change of cementitious mixtures
- ASTM C-942, test method for compressive strength of grouts for replaced aggregate concrete

PACKAGING

57.5 lb bags
3000 lb. "Super-Sacks"

SHELF LIFE

12 Months — Rotate Stock

WARRANTY

NOTICE-READ CAREFULLY

CONDITIONS OF SALE

SpecChem offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of SpecChem. No other representative of or for SpecChem is authorized to grant any warranty or to waive limitation of liability set forth below.

WARRANTY LIMITATION

SpecChem warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, SpecChem will replace the defective product with new product without charge to the purchaser. SpecChem makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.



1511 Baltimore Ave, Suite 600
Kansas City, MO 64108
www.specchemllc.com 866.791.8700