H62310 | TRUST commercial Satin 245

MICROPOROUS RESIN-COATED PAPER

PRODUCT SPECIFICATION *

Weight DIN EN ISO 536	g/m²	248	± 6
Thickness DIN EN ISO 534	µm mil	242 9.5	± 6 ± 0.2
Gloss BYK (60°) ISO 2813		19	± 5
Colour Elrepho UVO (D65) ISO 2469	L a b delta b	94,2 -0,2 -2,6 <0,7	± 0,5 ± 0,3 ± 0,5
i1 Pro2	L*M0 a*M0 b*M0 L*M1 a*M1 b*M1	95,3 -0,3 -2,7 95,3 -0,3 -3,0	
CIE whiteness (D65/10°) min. ISO 2469		> 94	
Opacity min. ISO 2469	%	> 94	

Printability

Simplex printable

Printing Technology

Inkjet water-based

Compatibility

Compatible with all commercial thermal, piezo water-based printing systems like Epson, Canon, Hewlett-Packard, Kodak, Encad etc.

Certificates

fogra cert
Proof Substrate | 25488-3

Fogra 25488-3

BENEFITS & PROPERTIES

- Reproducibility by outstanding media colour consistency
- Large colour gamut
- Pin-sharp details
- Instant dry
- Universal compatibility for printers and inks

KEY APPLICATIONS

Proof & Prepress

- Proofs for offset, gravure and screen printing
- Dot-proofs
- Contract, design and check proofs
- Mock-ups

Directions for use

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

* Modifications reserved.

Version 10/2026