abezeta
YOUR GLOBAL **PARTNER**

abeplate Galaxy



Plancha CTP Térmica

GALAXY es una plancha térmica positiva de alta resistencia química en máquina de imprimir.
La plancha **GALAXY** está fabricada en modernas líneas de producción totalmente automatizadas.
Con una alta sensibilidad y resolución de copia, puede reproducir hasta 20 µm en trama estocástica - FM.
GALAXY es muy versátil, sea para aplicación en embalaje con o sin tintas UV como para impresión de trabajos comerciales. Muy adecuada para máquinas de pliego y rotativas Heat-set y Cold-set, así como con tintas metálicas.
GALAXY es compatible con los principales reveladores del mercado y tiene una muy buena latitud de revelado.

- Alta sensibilidad y resolución de copia
- Excelente resolución
- Largas tiradas en máquina de imprimir sin post-horneado
- Resistente a tintas UV y solventes
- Compatible con diferentes reveladores

Thermal CTP Plate

GALAXY is a robust positive working thermal plate with high chemical resistance on press.
GALAXY plate has manufactured in modern fully automated production lines.
With high sensitivity and resolution, is suitable to reproduce up to 20 µm FM stochastic screen.
GALAXY is very versatile both for application in packaging with or without UV inks as well as for commercial printing. Suitable for Heat-set and Cold-set webs and sheet-fed presses, as well as metallic ink printing.
GALAXY is compatible with the main developers of the market and has a very good developing latitude.

- High sensitivity and high resolution
- Excellent resolution
- Long runs on press without post-baking
- Resistant to UV inks and solvents
- Compatible with different developers

abeplate Galaxy

Technical specifications

Type	**Positive working thermal**
Substrate	**Electromechanical grained and anodized aluminium**
Coating Color	**Dark blue**
Plate Gauges	**0,15 / 0,15 P / 0,20 / 0,30 / 0,40 mm**
Application	**Sheet-fed and Coldset / Heatset web presses**
Laser Characteristics	**IR - Infrared laser**
Spectral Sensitivity	**800-830 nm**
Energy Required	**120-130 mJ/cm²**
Screen Reproduction	**1 - 99% @ 400 l.p.i.**
Resolution	**Up to 5080 d.p.i. and FM screen 20 µm**
Safelight	**Daylight handling**
Development	**Use Abezeta developers and replenishers**
Processing Conditions	**Temperature: 23 ±1°C** **Dev. Time: 25 ±5 seconds**
Finishing Gum	**Use Abezeta Gum for standard process**
Run Length	**200.000 impressions – UV ink** **500.000 impressions – Conventional ink**
Shelf Life	**18 months**
Storage Conditions	**Temperature: Up to 30°C** **Relative Humidity: Up to 70%**



abezeta
YOUR GLOBAL **PARTNER**

València, 348
08009 Barcelona (Spain)
Tel. +34 934 574 504 / +34 932 075 022
info@abezetagroup.com