

ColorPak®

Precision Engineered Calibrated Press UnderPacking



CHARACTERISTICS/ADVANTAGES



Color-Coded by Gauge ~ *Easy to know how cylinders are packed*
Patented Anti-Corrosion Treated ~ *Protection for Cylinders*
Anti-Creep Formulation ~ *Resists slipping movement*
Anti-Wicking Treatment ~ *Resists moisture at edges, longer lasting*
Broad Caliper Range; 0.05 mm – 0.4 mm ~ *Flexibility in packing*
High-Density ~ *Maintains gauge during the run, sharper dots*
Excellent Formation ~ *Yields uniform solids and quality output*
Narrow Tolerances ~ *Consistent & Dependable performance*

UTILITY

Suitable for use under
√ Plates
√ Blankets ~ Printing Unit or Coating Unit
√ Back Cylinder

DIRECTIONS FOR USE

Follow press manufacturer's specifications

APPLICATIONS / PROCESS

Sheetfed Heatset Web Coldset Web
Commercial Printing Label /Forms Newspaper Packaging

SPECIAL FEATURES

Anti-Corrosive Treatment
Protects Valuable Cylinders from Corrosion Damage





TECHNICAL DATA

Construction	ECF Treated Cellulose Fibers, Starch, Colored Dyes Contains Kaolin, Calcium Carbonate, 5% Water <u>Does Not Contain</u>: Barium Sulfate, Magnesium Silicate, Calcium Sulfate, Zinc Oxide or Metal Powders
Type	Non-Adhesive, Non-Compressible
Surface Finish	Steel Calendared
Color	Various; Fully Dyed (not surface only)
Nominal Thickness	Target +/- 5%
Surfaces	Cobb Sized and Hercules Sized (moisture resistant)
Storage	Store at 70 degrees Fahrenheit, 50% RH

AVAILABILITY

General	Sheets and Rolls; Max sheet size 1600mm x 2133mm
Gauges (")	0.075mm, 0.1mm, 0.125mm 0.15mm, 0.175mm,0.2mm, 0.225mm, 0.25mm, 0.275mm, 0.3mm 0.4mm

ColorPak®

MSDS

MSDS for **ColorPak** press under-packing:

Our paper products that we manufacture and sell qualify for the **"Article" exemption under 29 CFR 1910. 1200(b)(6)(v)**. According to 29 CFR 1910.1200(c), the definition of "article" is the following: "Article means a manufacturing item other than a fluid or particle: (i) which is formed to a specific shape or design during manufacture; (ii)which has end use function(s) dependent in whole or in part upon its shape or design during end use; and (iii) which under normal conditions of use does not release more than very small quantities, e.g., minute or trace amounts of a hazardous chemical (as determined under paragraph (d) of this section), and does not pose a physical hazard or health risk to employees.".