THIAGARAJAR POLYTECHNIC COLLEGE

| Govt.Aided | Autonomous |

CENTRE FOR CIVIL TESTING AND CONSULTANCY

TEST REPORT

Test Report No.	TPT/CCTC/Test/2026/001	**Date of Test Report**		09.09.2026
Customer Address & Contact Details	Example Customer Salem	**Description of sample received**		Concrete
Name of Work (As Mentioned by Addressee)	Municipal construction works	**Sample received on**		01.09.2026
		Date	**Start of Test**	02.09.2026
			End of Test	09.09.2026
Testing Method	IS 516			

TEST RESULTS

Sl. No	Identification Marks	Weight in g	Length	Compressive Strength in MPa	Types of Failure
1	Sample 1	8912.5	150	35.0	Satisfactory
2	Sample 2	8831	150	34.0	Satisfactory
			Average	34.5	

Test	Result
Compressive Strength	32.0

Disclaimer: *The test results are related only to the samples submitted for testing. The Addressee is requested to check up the results with their norms noted in the work order conditions and as per relevant codes. This test report shall not be reproduced in part, without the permission of this laboratory. Any correction invalidates this test report. Balance sample, if any shall be discarded after 1 month from the date of issue of this Test Report, unless specified otherwise.*

**** End of test report ****

Test Conducted by

Reviewed by

Authorized Signatory