

ISO - STANDARD TECHNICAL SPECIFICATIONS

CHARACTERISTICS	STANDARD AS PER ISO-13006/2018 En14411 gr.bla	FLAIS VALUE	TEST METHOD
-----------------	---	-------------	-------------

Regulatory Properties

Deviation in Length & Width	±0.5%	±0.2%	ISO 10545-2
Deviation in Thickness	±5%	±5%	ISO 10545-2
Straightness of Sides	±0.5%	±0.2%	ISO 10545-2
Rectangularity	±0.5%	±0.2%	ISO 10545-2
Surface Flatness	±0.5%	±0.3%	ISO 10545-2
Colour Difference	▲ E<1.00	▲ E<0.30	ISO 10545-16
Glossiness	As per Mfg.	As per Mfg.	Gloss Meter

Structural Properties

Water Absorption	±5.0%	<0.03%	ISO 10545-3
Apparent Density	As per Mfg.	>2.20g/cc	ISO 10545-3

Massive Mechanical Properties

Modulus of Repture	Min.40N/mm ²	Min.40N/mm ²	ISO 10545-4
Breaking Strength	Min. 1300N	Min. 2000N	ISO 10545-4
Inpact Resistance	As per Mfg.	Min. 0.55	ISO 10545-4

Surface Mechanical Properties

Surface Abrasion Resistance	As per Mfg.	Min. Class 3	ISO 10545-4
Moh's Hardness	As per Mfg.	Min. Class 4	BS EN 15771

Thermo Hydrometric Properties

Frost Resistance	As per Mfg.	Frost Proof	ISO 10545-12
Thermal Shock Resistance	Min. 10 Cycle	Min. 10 Cycle	ISO 10545-9
Moisture Expansion	Max. 0.6mm/m	Max. 0.02mm/m	ISO 10545-10
Thermal Expansion	Max. 9.0x10 ⁻⁶	Max. 6.0x10 ⁻⁶	ISO 10545-8

Chemical Properties

Chemical Resistance	As per Mfg.	No Damage	ISO 10545-13
Stain Resistance	Resistant	Resistant	ISO 10545-14

Safety Properties

Slip Resistance	As per Mfg.	N.A.	DIN 51130
Fire Resistance	As per Mfg.	Fire Proof	N.A.

EUROPEAN STANDARD TECHNICAL SPECIFICATIONS

CHARACTERISTICS	STANDARD AS PER ISO-13006/2018 En14411 gr.bla	FLAIS VALUE	TEST METHOD EUROPEAN STD
-----------------	---	-------------	-----------------------------

Regulatory Properties

Deviation in Length & Width	±0.6%	±0.3%	BS EN ISO 10545-2
Deviation in Thickness	±5.0%	±0.3%	BS EN ISO 10545-2
Straightness of Sides	±5.0%	±0.3%	BS EN ISO 10545-2
Rectangularity	±0.6%	±0.3%	BS EN ISO 10545-2
Surface Flatness	±5.0%	±0.3%	BS EN ISO 10545-2
Colour Difference	▲ E<1.00	▲ E<0.30	BS EN ISO 10545-16
Glossiness	As per Mfg.	As per Mfg.	Gloss Meter

Structural Properties

Water Absorption	±5.0%	<0.05%	BS EN ISO 10545-3
Apparent Density	As per Mfg.	>2.20g/cc	BS EN ISO 10545-3

Massive Mechanical Properties

Breaking Strength	>1300N	>1500N	BS EN ISO 10545-4
Modulus of Rupture	>35N/mm2	>45N/mm2	BS EN ISO 10545-4
Resistance to Deep Abrasion	<175mm3	<150mm3	BS EN ISO 10545-6

Thermo Hydrometric Properties

Linear Thermal Expansion	≤9x10 ⁻⁸ °C ⁻¹	≤7x10 ⁻⁸ °C ⁻¹	BS EN ISO 10545-8
Thermal Shock Resistance	No visible defect	No visible defect	BS EN ISO 10545-9
Frost Resistance	Frost Proof	Frost proof	BS EN ISO 10545-12
Moisture Expansion	Nil	Nil	-

Chemical Properties

Resistance to Chemicals	No visible effect	No visible effect	BS EN ISO 10545-13
Apparent Density	Manufacturer to State Class	Stains removed Min. Class 2	BS EN ISO 10545-14

Surface Mechanical Properties

Colour Resistance	No Damage	No Damage	BS EN ISO 10545-16
Colour Resistance to UV Light	No Change in Color	No Change in Color	DIN 51094
Scratch Hardness(MOH's Scale)	MATT > 6 MOHS	MATT > 6 MOHS	EN 101
Surface Quality	Min. 95%	Min. 95%	BS EN ISO 10545-2
Skid Resistance (Friction Co-Efficient)	>0.4	>0.4	BS EN ISO 10545-17
Moisture Expansion	Nil	Nil	-

Safety Properties

Slip Resistance	As per Mfg.	N.A.	DIN 51130
Fire Resistance	As per Mfg.	Fire Proof	N.A.