
Distance between recaptures (RKM)
45
40
35
30
25
Hard (carboy)
Hard (large scale)
Soft (carboy)
Release Method
Release Methods
Hard (carboy)
Hard (large scale)
Soft (carboy)