

# The metallurgy of copper in Italian Prehistory. New archaeometric data from Sardinia

## Abstract

When looking at the earliest metallurgy in Italy, data from Sardinia indicates a beginning during the first half of the 4<sup>th</sup> millennium cal. BC, which was followed by very gradual development that intensified during the 3rd millennium. Here we present results of XRF analysis undertaken on copper artefacts recovered from the renowned sanctuary of Monte d'Accoddi (northern Sardinia), chiefly belonging to a period between the 4<sup>th</sup> and the early 2<sup>nd</sup> millennium cal. BC. Some finds were of particular interest in that they contained a high or anomalous concentration of silver.

## Keywords

XRF Analysis, Archaeometallurgy, Prehistory, Sardinia, Monte d'Accoddi

## 1 Introduction

Based on evidence of mining activity, as well as finds of metal artefacts, crucibles and slag deposits, it appears that the earliest phase of metallurgy in Italy occurs between the last centuries of the 5<sup>th</sup> and the first half of the 4<sup>th</sup> millennium cal. BC (Pearce 2015, *ivi* bibliography).

In Sardinia the most ancient metal artefacts, made from copper and silver, are datable to the first half of the 4<sup>th</sup> millennium cal. BC, whereas more direct evidence of metallurgical activity (crucibles) have been dated to the second half of the 4<sup>th</sup> millennium cal. BC (Melis 2009 and 2014): the available data suggests a limited development of metallurgy, that intensifies gradually during the second half of the 4<sup>th</sup> and the 3<sup>rd</sup> millennia cal. BC). The scarcity of finds and the restricted number of archaeometric analyses so-far completed (Lo Schiavo *et al.* 2005; Skeates *et al.* 2013; Brunetti *et al.* 2015) can only offer us a fragmentary view of the most ancient metallurgical practices and the ways in which related knowledge was transmitted.

Presented here are the results of the XRF analyses carried out on copper finds from excavations at the shrine at Monte d'Accoddi, run by Ercole Contu between 1952 and 1959 (Contu 2001; Melis 2011). The structure is a terraced monument situated in north-western Sardinia, surrounded by a village that was occupied in diverse periods of Prehistory. Architecturally it is unique in the Mediterranean panorama, although it has often been compared to the ziggurats of the Near East (as debated by Tinè and Traverso 1992), both for the presence of an entrance ramp and for its truncated-pyramid shape. Currently, however, the chronological data and the vague architectural similarities, but above all, the different social contexts, the absence of any documented contact with the Near East and its obvious connection to local Neolithic tradition, with which it shares material cultural and some architectural aspects of Monte d'Accoddi, means that the genetic hypothesis of eastern origin is impossible to confirm. The Sardinian monument therefore appears to be an original feature, although its inspiration may perhaps be related to western megalithism, which arrived in Sardinia during the second half of the 4<sup>th</sup> millennium cal BC (Guilaine 1996; Melis *et al.* 2007). The network of intense relationships surrounding the circulation of obsidian may have favoured the indirect contacts and the circulation of architectural ideas from more distant western territories that did not belong to the obsidian trade routes, places where monumental buildings and tumuli of great size, some of them stepped, are known to have existed, such as the structure at Barnenez in Brittany for example (Giot 1987).



The metal finds (Figure 1) included awls, axes, a dagger, a hook and a razor. Morphological analyses and chronological and cultural identification of the objects were in some cases compromised by the poor state of conservation; in fact, many of the pieces had significant parts missing. Nevertheless, integrating this data together with the little available information regarding the contexts in which they were found, it becomes possible to speculate about their association with several of the diverse phases of use of the shrine, between the 4<sup>th</sup> millennium cal. BC and the beginning of the second. The razor, which vaguely resembles Villanovan models, could indeed be attributable to the Iron Age.

The aims of the current research are several; increase the available archaeometric data in the context of Sardinia, provide new interpretative tools for studying the origins of metallurgy and to make a contribution to research on the dynamics of the use of one of the most important Prehistoric monuments of the Mediterranean.

The methodological choices made in relation to the diagnostic research were influenced by the unwillingness on the part of the *Soprintendenza Archeologica* to allow destructive analytical procedures. The decision, therefore, was to initially make an XRF analysis, the results of which are presented in the present work.

## 2 Methods

Determination of the structure and composition of a Cultural Heritage artifacts with XRF has been approached and described in the literature (Cesareo *et al.* 2004; Milazzo 2004; Manso *et al.* 2008; Cesareo *et al.* 2010; Guilherme *et al.* 2013; Cesareo *et al.* 2013; Brunetti *et al.* 2015; Brunetti *et al.* 2016a; Schiavon *et al.* 2016). In the case of monolayer samples with smooth surfaces any quantitative methods can be usefully adopted. The same holds for regular multilayered structures. Usually these methods requires the extraction of the background leaving only the peaks part of the spectrum which is used for the quantification step. Usually an iterative guess and try approach is applied and an estimative of the composition is obtained (Sherman 1965; Shiraiwa, Fujino 1966; Mantler 1986; De Boer 1990). Beside these methods the Fundamental Parameters Method probably is the most performing. The most critical step of these methods is connected to the extraction of the background which, especially in the case of small area peaks, can introduce large errors. In order to overcome this problem peak fit and background extraction are performed simultaneously in some implementation of this methods. In the case of multilayered structures some empirical and faster methods have been also described (Bustamante *et al.* 2013; Cesareo *et al.* 2008; Cesareo *et al.* 2009; Cesareo, Brunetti 2008). They are based on the determination of the influence (in terms of attenuation) of the outer layer on the fluorescence signal emitted by the inner layer. In order to simplify the estimative of the layer compositions and thicknesses, these methods require the use of a monochromatic or quasi monochromatic X-ray beam. Latter because the lower background is the easier is the extraction of the background and the complexity of the equations for the quantification. However, although in the measurements described in the literature this approach has produced good results (Bustamante *et al.* 2013; Cesareo *et al.* 2008; Cesareo *et al.* 2009; Cesareo, Brunetti 2008), it strongly depends on the sample composition, on the X-ray spectrum emitted by the source and, more in general, on the experimental setup, making its generalization to other experimental situations not straightforward. However, the quantitative estimation of multilayer structures is of great importance in Cultural Heritage analysis because the samples, especially the metallic ones, are often formed by at least two layers: the so called patina, i.e. corrosion products and incrustations due to the interaction with the sediment in which the sample was buried. Moreover the presence of patina or incrustation introduces a new difficulties for its quantitative characterization: a non smooth surface. The interaction of the X-ray photons strongly depends on the surface roughness (Brunetti, Golosio 2014). As a result, the presence of a rough surface can alter the area of the fluorescence peaks detected in a no easily predictable way, so making the quantitative estimation not reliable. It is possible to reduce the influence of irregular surfaces adopting some strategies in the experimental setup (Trojek *et al.* 2010; Trojek 2011; Bonizzoni *et al.* 2006; Trojek 2012). However, a better approach should be considered

the real surface in the quantitative algorithm utilized. So, resuming, two main problems can be identified for a quantitative characterization of Cultural Heritage samples: low intensities peaks connected to low chemical concentration and irregular surfaces. In order to solve both these problems we have developed and applied a different approach based on XRF measurements and Monte Carlo simulations (Brunetti *et al.* 2016a; Brunetti *et al.* 2016b; Bottaini *et al.* 2015). This method is not new at all, in the sense that the use of the Monte Carlo simulations have been proposed in the past (Trojek *et al.* 2010; Trojek 2011; Gardner, Doster 1979; Gardner, Doster 1982a; Gardner, Doster 1982b; Fernandez 1989; Schoonjans *et al.* 2012; Vincze *et al.* 1993; Bottigli *et al.* 2004; Golosio *et al.* 2014). The novelty is the speed of the Monte Carlo simulation that allows real-time simulation and the capability to simulated irregular surface. The Monte Carlo code used here is called *XRMC* (Bottigli *et al.* 2004; Golosio *et al.* 2014). It is a very versatile code able to simulated a wide range of X-Ray experiments, from XRF to phase contrast. As mentioned before, it is also able to simulate irregular surface and is under development a version which will be able to introduce in the simulation a tridimensional reproduction of the real surface of the sample.

The quantitative procedure used here is structured in the following steps. The first step is the experimental setup is described in the language of *XRMC*. The code requires the structure and composition of the sample, the position of the sample, the detector and the X-Ray source and their spectroscopic characteristics. Then the experimental XRF spectrum is acquired. The experimental setup used for the measured reported here is a custom portable one composed by an silver anode X-Ray tube working at 40 kVp and 5-10  $\mu$ A and a SDD detector. The geometry can be chosen according to the accessibility of the zoned to be analyzed, but usually the detector is placed orthogonally to the sample surface, while the X-Ray tube forms an angle of about 30° with respect to the detector, both 2-3 cm far from the surface. After the experimental measurement, the spectrum is also simulated by the Monte Carlo code. The two spectra are then compared superimposing each to other: if any difference is observed the structure and/or the composition of the sample introduced in the Monte Carlo is changed. This procedure is iteratively repeated until the simulated spectrum is a perfect reproduction of the experimental one, within the statistical fluctuations. In the last iterations a chi-squared test is also performed to help the user in the evaluation. In principle this procedure could be made automatically, but the high number of variables involved in this problem is, in our opinion, and so too hard to perform it without the user supervision. Some attempts in such direction are been done in PyMCA a well-known quantitative estimation code (Solé *et al.* 2007; Schoonjans *et al.* 2013). This approach has been extensively tested on reference samples as well as real Cultural heritage objects such as a couple of identical, same provenience, objects, only one of them restored, even in this case the results obtained were similar (Brunetti *et al.* 2016b). Based on this tests, the error on the concentration estimation is about 5% for the chemical element with concentration larger than 1%, and around 30% for concentration around 100 ppm. The minimum detectable concentration is around 20 ppm. The capability to perform analysis before restoration is of particular importance because sometimes, for example, an silver enrichment of the sample surface can be produced by the restoration technique itself (Moreno-Suárez *et al.* 2016). Of course, the signal emitted by the inner layer must be able to reach the surface of the sample and to be detected, this means that this technique cannot be applicable to sample with too thick, in XRF sense, patina.

### 3 Results

The results obtained on all the sample analyzed are reported in table I. However, in order to show how the procedure work, two examples will be discussed in details. In figure 2 the measured and simulated spectra of sample 12343 is depicted. The model utilized is a two layer one. The first layer, the patina, is 300nm thick and it is essentially formed by incrustation with calcium and iron are the majority element. The bulk part is almost pure copper (99.4%) with a low amount of silver (0.5%) and lead (0.1%). The pile-up peaks are due to the detector (too high dead time) and for this reason are not simulated.

The sample 14342 (Figure 3) has been also modeled as a two layer one. The incrustation layer has the same thickness of the previous one, but its slightly composition is different: calcium and copper oxide. More interesting is the compositing of the bulk where a copper (87%) and silver (13%) have been found together with a small amount of lead (0.1%).

**Table I.** Results of XRF analyses.

Inventory N.	Fig.3 N.	Chemical elements (%)							
		Ca	Fe	Cu	Zn	As	Ag	Sn	Pb
14339	1			98.9		0.1	1.0		
14340	2	2.4	0.3	96.2		0.4	0.3		0.4
14341	3		0.5	98.6			0.5		0.4
14342	4			84.9		0.1	15		
14343	5	1.0	0.1	99.2			0.5		0.1
14344	6	1.0	0.07	97.0		1.0	0.3	0.5	1.0
14345	7	1.0	0.1	98.2		0.15	0.1		0.4
14346	8	0.1	0.05	99.3		0.3	0.3		
14347	9	0.7	0.1	98.9			0.3		
14348	10			87.7		0.1	12		0.2
14349	11			93.5			3.5		3.0
14350	12	4.9	0.7	92.7		0.1	1.6		
14351	13			96.5			3.5		
14352	14		2.0	97.6	0.2	0.1	1.0		

#### 4 Discussion

The results of the analyses generally show a composition of pure copper. Arsenic (As) is present in very low percentages (0,1%-0,4%), except for in sample 14344 (1%). This is a fragmented artefact, difficult to identify or date. Lead (Pb) is also present in some of the objects, in quantities of lower than 1%, except for in samples 14344 (1%) and 14349 (3%). Silver (Ag) is present in almost all of the objects in varying degrees. In several examples the concentration is fairly high, reaching as much as 15% in sample 14342. In these cases it is improbable that the presence is casual; it seems more likely that the inclusion was intentional, perhaps with the aim of providing a chromatic effect, as has been suggested in the case of the dagger of Casanuova at S. Biagio (De Angelis 1995-1996; Melis 2014). A similar hypothesis has been formulated in relation to the intentional inclusion of arsenic in copper objects, with the objective of not only improving its mechanical characteristics but also to change the typical colour of copper in order to make it more similar to silver (Dolfini 2013, Giardino 2012, Giumla Mair 2005, Ottaway & Roberts 2008, Pearce 2007).

The question marks and issues raised by these preliminary results, the anomalies thus revealed and the difficulties in dating some of these artefacts together provide an indication of the route to take in furthering archaeological research, including any contribution that can be made through further archaeometric studies.

#### Acknowledgements

A few short months from his passing, kind thoughts and gratitude go to Prof. Ercole Contu, who entrusted Maria Grazia Melis with the work of processing the finds from Monte d'Accoddi. We wish to extend our thanks to Giovanni Carboni for his invaluable advice.

## References

- BONIZZONI, L.; MALONI, A. y MILAZZO, M. (2006) "Evaluation of effects of irregular shape on quantitative XRF analysis of metal objects" *X-Ray Spectrometry*, 35, pp. 390–399.
- BOTTAINI, C.; MIRÃO, J.; FIGUEREIDO, J. M.; CANDEIAS, A.; BRUNETTI, A. y SCHIAVON, N. (2015) "Energy dispersive X-ray fluorescence spectroscopy/Monte Carlo simulation approach for the non-destructive analysis of corrosion patina-bearing alloys in archaeological bronzes: The case of the bowl from the Fareleira 3 site (Vidigueira, South Portugal)" *Spectrochimica Acta Part B*, 103-104, pp. 9-13.
- BOTTIGLI, U.; BRUNETTI, A.; GOLOSIO, B.; OLIVA, P.; STUMBO, S.; VINCZE, L.; RANDACCIO, P.; BLEUET, P.; SIMIONOVICI, A. y SOMOGYI, A. (2004), "Voxel-based Monte Carlo simulation of X-ray imaging and spectroscopy experiments" *Spectrochimica Acta, Part B: Atomic Spectroscopy*, 59, pp. 1747-1754.
- BRUNETTI, A.; DEPALMAS, A.; DI GENNARO, F.; SERGES, A. y SCHIAVON, N. (2016) "X-ray fluorescence spectroscopy and Monte Carlo characterization of a unique nuragic artifact (Sardinia, Italy)" *Spectrochimica Acta Part B*, 121 (1), pp. 18-21.
- BRUNETTI, A.; FABIAN, J.; WESTER LA TORRE, C. y SCHIAVON, N. (2016b) "A combined XRF/Monte Carlo simulation study of multilayered Peruvian metal artifacts from the tomb of the Priestess of Chornancap" *Applied Physics. A, Materials Science & Processing*, 122, p. 571.
- BRUNETTI, A. y GOLOSIO, B. (2014) "A new Monte Carlo code for simulation of the effect of irregular surfaces on X-ray spectra" *Spectrochimica Acta, Part B: Atomic Spectroscopy*, 94-95, pp. 58-62.
- BRUNETTI, A.; GOLOSIO, B.; MELIS, M. G. y MURA, S. (2015) "A high-quality multilayer structure characterization method based on X-ray fluorescence and Monte Carlo simulation" *Applied Physics. A, Materials Science & Processing*, 118, pp. 497-504.
- BUSTAMANTE, A.; CESAREO, R.; BRUNETTI, A.; RIZZUTTO, M.; CALZA, C.; PEREIRA DE FREITAS, R.; HOLMSQUIT, U. y DIESTRA, D. (2013) "Analysis of Pre-Columbian objects from Cupisnique, one of the oldest culture from Perú, using a portable X-ray fluorescence equipment" *Applied Physics. A, Materials Science & Processing*, 113, pp. 1065-1067.
- CESAREO, R. y BRUNETTI, A. (2008) "Metal sheets thickness determined by energy-dispersive X-ray fluorescence analysis" *Journal of X-ray Science and Technology*, 16, pp.119-130.
- CESAREO, R.; BRUNETTI, A.; D'ORIANO, R.; CANU, A.; DEMONTIS, G. M. y CELAURO, A. (2013) "A Roman bronze statuette with gilded silver mask from Sardinia: an EDXRF study" *Applied Physics. A, Materials Science & Processing*, 113, pp. 905-910.
- CESAREO, R.; BRUNETTI, A. y RIDOLFI, S. (2008) "Pigment layers and precious metal sheets by energy-dispersive X-ray fluorescence analysis" *X-ray Spectrometry*, 37, pp. 309-316.
- CESAREO, R.; CALZA, C.; DOS ANJOS, M.; LOPES, R. T.; BUSTAMANTE, A.; FABIAN, S. J.; ALVA, W. y CHERO, Z. L. R. (2010) "Pre-Columbian alloys from the royal tombs of Sipan; energy dispersive X-ray fluorescence analysis with a portable equipment" *Applied Radiation and Isotopes*, 68, pp. 525-528.
- CESAREO, R.; CASTELLANO, A.; BUCCOLIERI, G.; QUARTA, S.; MARABELLI, M.; SANTOPADRE, P.; LEOLE, M. y BRUNETTI, A. (2004) "Portable equipment for energy dispersive X-ray fluorescence analysis of Giotto's frescoes in the Chapel of the Scrovegni" *Nuclear Instruments and Methods in Physics Research Section B*, 213, pp. 703-706.
- CESAREO, R.; RIZZUTTO, M. A.; BRUNETTI, A. y RAO, D. V. (2009) "Metal location and thickness in a multilayered sheet by measuring  $K\alpha/K\beta$ ,  $L\alpha/L\beta$  and  $L\alpha/L\gamma$  X-ray ratios" *Nuclear Instruments and Methods in Physics Research Section B*, 267 (17), pp. 2890-2896.

- CONTU, E. (2001) "Monte d'Accoddi tra esegesi, confronti e cronologie. Qualche nuova considerazione". En G. Serreli G. y D. Vacca (eds.), *Aspetti del megalitismo preistorico*. Dolianova: Grafica del Parteolla, pp. 59-66.
- DE ANGELIS, M. C. (1995-1996) "La struttura tombale di Casanuova di S. Biagio della Valle (Marsciano, Perugia)" *Rivista di Scienze Preistoriche*, 47, pp. 397-404.
- DE BOER, D. K. G. (1990) "Calculation of X-ray fluorescence intensities from bulk and multilayer samples" *X-ray Spectrometry*, 19, pp. 145-154.
- DOLFINI, A. (2013) "The Emergence of Metallurgy in the Central Mediterranean Region: A New Model" *European Journal of Archaeology*, 16 (1), pp. 21-62.
- FERNANDEZ, J. E. (1989) "Monte Carlo computer simulation of the XRF intensity dependence on the propagation plane inclination" *Computer Physics Communications*, 54, pp. 211-220.
- GARDNER, R. P. y DOSTER, J. M. (1979) "The Reduction of matrix effects in x-ray fluorescence analysis by the Monte Carlo, fundamental parameters method" *Advances in X-Ray Analysis*, 22, pp. 343-356.
- GARDNER, R. P. y DOSTER, J. M. (1982a) "The complete spectral response for EDXRF Systems- Calculation by Monte Carlo and Analysis applications. 1-homogeneous samples" *X-ray Spectrometry*, 11, pp. 173-180.
- GARDNER, R. P. y DOSTER, J. M. (1982b) "The complete spectral response for EDXRF Systems- Calculation by Monte Carlo and Analysis applications. 2-heterogeneous samples" *X-ray Spectro*, 11, pp. 181-186.
- GIARDINO, C. (2012) "From natural resources to cultural commodities metal technology in the central and south Italian Copper Age" *Accordia Research Papers*, 12, pp. 15-40.
- GIOT, P. R. (1987) *Barnenez, Carn, Guennoc*, vol. I-II. Travaux du Laboratoire Anthropologie – Préhistoire – protohistoire – Quaternaire armoricains. Rennes: Equipe de recherche n. 27 du C.N.R.S., Université de Rennes I.
- GIUMLIA-MAIR, A. (2005) "On surface analysis and archaeometallurgy" *Nuclear Instruments and Methods in Physics Research B*, 239, pp. 35-43.
- GOLOSIO, B.; SCHOONJANS, T.; BRUNETTI, A.; OLIVA, P. y MASALA, G. L. (2014) "Micro Monte Carlo simulation of x-ray imaging and spectroscopy experiments using quadric geometry and variance reduction techniques" *Computer Physics Communications*, 185, pp. 1044-1052.
- GUILAINE, J. (1996) "Proto-mégalithisme, rites funéraires et mobiliers de prestige néolithiques en Méditerranée occidentale" *Complutum Extra*, 6 (I), pp. 123-140.
- GUILHERME, A.; MANSO, M.; PESSANHA, S.; ZEGZOUTI, A.; ELAATMANI, M. R.; BENDAOU, R.; COROADO, J.; DOS SANTOS, J. M. F. y CARVALHO M. L. (2013) "Micro-XRF for characterization of Moroccan glazed ceramics and Portuguese tiles" *Journal of Instrumentation*, 8 (C02055), pp. 1-9.
- LO SCHIAVO, F.; GIUMLIA-MAIR, A.; SANNA, U. y VALERA, R. (eds.) (2005) *Archaeometallurgy in Sardinia: from the origins to the early iron Age*. Montagnac: Editions Monique Mergoil.
- MANSO, M.; COSTA, M. y CARVALHO, M. L. (2008) "X-ray fluorescence spectrometry on paper characterization: case study on XVIII and XIX century documents" *Spectrochimica Acta, Part B: Atomic Spectroscopy*, 63, pp. 1320-1323.
- MANTLER, M. (1986) "X-ray fluorescence analysis of multiple-layer films" *Analytica Chimica Acta*, 188, pp. 25-35.

MELIS, M. G. (2009) “L’Eneolitico antico, medio ed evoluto in Sardegna: dalla fine dell’Ozieri all’Abealzu”. En Atti della XLIV Riunione Scientifica dell’Istituto Italiano di Preistoria e Protostoria *La preistoria e la protostoria della Sardegna*. Cagliari, Barumini, Sassari, 23-28 novembre 2009, vol I, pp. 81-95, 107-109.

MELIS, M. G. (2011) “Monte d’Accoddi and the end of the Neolithic in Sardinia (Italy)”, *Documenta Praehistorica*, XXXVIII, pp. 207-219

MELIS, M. G. (2014) “Silver in Neolithic and Eneolithic Sardinia”. En H. Meller, R. Risch y E. Pernicka (eds.), *Metalle der Macht – Frühes Gold und Silber*. Metal of power – Early gold and silver. 6. Mitteldeutscher Archäologentag vom 17. bis 19. Oktober 2013 in Halle (Saale), Tagungen des Landesmuseums für Vorgeschichte Halle 11/II (Halle (Saale), pp. 483-494.

MELIS, M. G.; QUARTA, G.; CALCAGNILE, L. y D’ELIA, M. (2007) “L’inizio dell’età del Rame in Sardegna. Nuovi contributi cronologici” *Rivista di Scienze Preistoriche*, LVII, pp. 185-200.

MILAZZO M. (2004) “Radiation applications in art and archaeometry: X-ray fluorescence applications to archaeometry. Possibility of obtaining non-destructive quantitative analyses” *Nuclear Instruments and Methods in Physics Research Section B: Beam Interactions with Materials and Atoms*, 213, pp. 683-692.

MORENO-SUÁREZ, A. I.; AGER, F. J.; RODRÍQUEZ-SEGOVIA, C.; GÓMEZ-MORÓN, A.; CHAVES, F.; SCRIVANO, S.; GÓMEZ-TUBÍO, B.; PLIEGO, R. y RESPALDIZA, M. A. (2016) “Feasibility of different cleaning methods for silver-copper alloys by X-ray fluorescence: Application to ancient Greek silver coins” *Spectrochimica Acta Part B: Atomic Spectroscopy*, 116, pp. 85-91.

OTTAWAY, B. S. y ROBERTS, B. (2008) “The Emergence of Metalworking”. En A. Jones (ed.), *Prehistoric Europe: Theory and Practice*. Oxford: Wiley-Blackwell, pp.193-225.

PEARCE M. (2007) *Bright blades and red metal. Essays on north Italian prehistoric metalwork*. Accordia Specialist Studies on Italy, 14. London: Accordia Research Institute, University of London.

PEARCE M. (2015) “The spread of early copper mining and metallurgy in Europe: an assessment of the diffusionist model. A key-note lecture”. En A. Hauptmann y D. Modarressi-Tehrani (eds.), *Archaeometallurgy in Europe III*. Proceedings of the 3rd International Conference, Deutsches Bergbau-Museum Bochum, June 29 – July 1, 2011. Der Anschnitt, Beiheft 26. Bochum: Deutsches Bergbau-Museum, pp. 45-54.

SCHIAVON, N.; SORIA, V.; ARRUDA, A. M.; BELTRAME, M. y MIRÃO, J. (2016), “Losanga” decorated imitations of italic late republican black gloss tableware from South-Western Iberia: A multi-analytical/microchemical characterization” *Microchemical Journal*, 124, pp. 712-718.

SCHOONJANS, T.; SOLÉ, V. A.; VINCZE, L.; SANCHEZ DEL RIO, M.; APPEL, K. y FERRERO C. (2013) “A general Monte Carlo simulation of energy-dispersive X-ray fluorescence spectrometers — Part 6. Quantification through iterative simulations” *Spectrochimica Acta Part B: Atomic Spectroscopy*, 82, pp. 86-91.


SCHOONJANS, T.; VINCZE, L.; SOLÉ, V. A.; SANCHEZ DEL RIO, M.; BRONDEEL, P.; SILVERSMIT, G.; APPEL, K. y FERRERO, C. (2012) “A general Monte Carlo simulation of energy-dispersive X-ray fluorescence spectrometers - Part 5. Polarized radiation, stratified samples, cascade effects, M-lines” *Spectrochimica Acta Part B: Atomic Spectroscopy*, 70, pp. 10–23.

SHERMAN, J. (1965) “The theoretical derivation of fluorescent X-ray intensities from mixtures” *Spectrochimica Acta*, 7, pp. 283–306.

SHIRAIWA, T. y FUJINO N. (1966) “Theoretical calculation of fluorescent X-ray intensities in fluorescent X-ray spectrochemical analysis” *Japanese Journal of Applied Physics*, 5, pp. 886-899.

- SKEATES, R.; GRADOLI, M. G. y BECKETT, J. (2013) "The Cultural Life of Caves in Seulo, Central Sardinia" *Journal of Mediterranean Archaeology*, 26 (1), pp. 97-126.
- SOLE, V. A. ; PAPILLON, E. ; COTTE, M. ; WALTER, PH. y SUSINI, J. (2007) "A multiplatform code for the analysis of energy-dispersive X-ray fluorescence spectra" *Spectrochimica Acta Part B: Atomic Spectroscopy*, 62, pp. 63-68.
- TINÈ, S. y TRAVERSO, A. (1992) "Relazione preliminare". En S. Tine y A. Traverso (eds.), *Monte d'Accoddi, 10 anni di nuovi scavi*. Genova: Istituto Italiano Archeologia Sperimentale, pp. i-xliii.
- TROJEK, T. (2011) "Reduction of surface effects and relief reconstruction in X-ray fluorescence microanalysis of metallic objects" *Journal of Analytical Atomic Spectrometry*, 26, pp. 1253–1257.
- TROJEK, T. (2012) "Reconstruction of the relief of an investigated object with scanning X-Ray fluorescence microanalysis and Monte Carlo simulations of surface effects" *Applied Radiation and Isotopes*, 70, pp. 1206–1209.
- TROJEK, T.; CECHAK, T. y MUSILEK, L. (2010) "Monte Carlo simulations of disturbing effects in quantitative in-situ X-ray fluorescence analysis and microanalysis" *Nuclear Instruments and Methods in Physics Research Section A*, 619, pp. 266–269.
- VINCZE, L.; JANSSENS, K. y F. ADAMS, F. (1993) "A general Monte Carlo simulation of energy-dispersive X-ray fluorescence spectrometers-I: Unpolarized radiation, homogeneous samples" *Spectrochimica Acta Part B: Atomic Spectroscopy*, 48, pp. 553-573.





1 Figure 1. Copper artefacts from Monte d'Accoddi (photos M. G. Melis; graphics C. Caradonna).




Figure 2. XRF measurements of sample 12343.




Figure 3. XRF measurements of sample 14342.