PhotolithoTwin

Simulation Report

Kavipriya M

PhotolithoTwin · Digital Twin Photolithography

Generated: 15 October 2026 · Process step: Final Pattern

OPTICAL SYSTEM

Wavelength	248nm (DUV)
Numerical Aperture (NA)	0.63
Partial Coherence (Ã)	0.40
Defocus Offset	0 nm
Resolution Limit (k•·»/NA)	240 nm
Depth of Focus (»/NA²)	625 nm
PSF Blur Ã	161 nm
Image Log Slope (ILS)	11.16 /µm

PHOTORESIST

Resist Type	Positive (DNQ-Novolac)
Resist Thickness	500 nm
Contrast (³)	7.0
Dill C (absorptivity)	0.040 cm²/mJ

EXPOSURE & BAKE

Exposure Dose	120 mJ/cm²
Soft Bake	95°C · 60s
Post-Exposure Bake	Disabled
Hard Bake	120°C
Development Time	45s
Diffusion Strength	0.00

CRITICAL DIMENSION (CD) METRICS

CD…€ (linewidth at 50% height)	875 nm
CDˆ€ (linewidth at 80% height)	875 nm
CD Bias (CD…€" target)	-125 nm
Sidewall Angle	47.1°
Normalized ILS (NILS)	2.679

 · © 2026 Zafer Mutlu. All rights reserved.