



Authorized Distributor for TNPL Copier &  
Printing Paper  
**ESTD. 1972**

# TNPL Eco Maplitho Product

## Technical Sheet

---

[www.arunaandco.in](http://www.arunaandco.in)

+91 99624 18844

[hello@arunaandco.in](mailto:hello@arunaandco.in)





## TNPL Eco Maplitho

Eco-friendly maplitho-grade paper for general printing and stationery.

### Description


TNPL Eco Maplitho offers sustainable maplitho-grade performance suitable for general printing requirements

### Quick Highlights

- Excellent for notebook and textbook printing

### Key Features

- Even in smoothness and formation
- Excellent Opacity





#### TNPL ECO MAPLITHO - Specifications

| S.No | Property                             | Specification |
|------|--------------------------------------|---------------|
| 1    | Nominal GSM Range(g/m <sup>2</sup> ) | 47 - 120      |
| 2    | Substance Tolerance                  | ± 2.5 %       |
| 3    | Bulk cc/g                            | 1.30 ± 0.05   |
| 4    | Moisture %                           | 6.0 ± 0.5     |
| 5    | Breaking Length MD m                 | 4000 ± 200    |
| 6    | Breaking Length CD m                 | 2000 ± 200    |
| 7    | Tear Factor MD                       | 40 ± 5        |
| 8    | Tear Factor CD                       | 45 ± 5        |
| 9    | Burst Factor (Min)                   | 15            |
| 10   | Bendsten Smoothness TS ml/min        | 130 - 250     |
| 11   | Bendsten Smoothness WS ml/min        | 80 - 150      |
| 12   | Porosity ml/min (Max)                | 450           |
| 13   | Cobb 60 g/m <sup>2</sup>             | 25 ± 2        |
| 14   | Brightness -ISO % (Min)              | 87            |
| 15   | Opacity %                            | 84 - 96       |
| 16   | CIE Whiteness                        | 145 ± 5       |

### **---Products**

#### Greener Paper Solutions

Eco-friendly, ECF-bleached papers that look good, feel good, and do good for the planet.