

Water-solid Suspension Grafting of Dual Monomers on Polypropylene to Prepare Ion-imprinted Fibers for Selective Adsorption of Cr(VI)

Zhengwei Luo¹, Lei Li², Mulin Guo³, Hui Jiang¹, Wenhua Geng¹, Wuji Wei^{2*}, and Zhouyang Lian^{2*}

¹College of Biotechnology and Pharmaceutical Engineering, Nanjing Tech University, Nanjing 211816, China

²School of Environmental Science and Engineering, Nanjing Tech University, Nanjing 211816, China

³Nanjing Hydraulic Research Institute, Nanjing 210029, China

(Received February 20, 2020; Revised March 26, 2020; Accepted March 30, 2020)

Abstract: In this work, a new strategy was developed to prepare Cr(VI)-imprinted polypropylene (PP) fibers-based materials for the adsorption of Cr(VI) from water. Granular PP was modified with dual monomers (glycidyl methacrylate (GMA) and acrylamide (AM)) by water-solid suspension grafting copolymerization. Then, this fibers morphology was obtained by melt-blowing. Hence, the preparation steps of the fibrous Cr(VI)-imprinted adsorbent involved surface ion-imprinting and crosslinking. The influence of the grafting conditions on the grafting percentage was investigated. The maxima grafting percentages of GMA and AM were 16.4 and 10.6 %, respectively. The chemically modified products showed good mobility and stability, thus meeting the requirements of melt-blowing method. The prepared Cr(VI)-imprinted polymers showed a maximum adsorption capacity to Cr(VI) of 43.2 mg/g at pH 3. The adsorption data were well fitted by the pseudo-second-order and Langmuir adsorption models. The adsorbent showed good selectivity toward Cr(VI) in a mixed solution containing Cu(II) and SO₄²⁻. The X-ray photoelectron spectroscopy demonstrated that the adsorbed Cr(VI) was partly reduced to Cr(III).

Keywords: Suspension grafting, Dual monomers, Polypropylene fibers, Ion-imprinting, Cr(VI)

Introduction

Hexavalent chromium (Cr(VI)) mainly originates from mining, metal smelting, electroplating, tanning, and other industries. Due to its extremely high toxicity and confirmed carcinogenic, teratogenic, and mutagenetic effects, the discharge of wastewater without proper pretreatment and containing Cr(VI) in a higher concentration than the legally allowed level is a real threat to the environment and human health [1,2]. Adsorption is one of the main methods for the removal of Cr(VI) from water, with the selective adsorption and removal of Cr(VI) by ion-imprinted polymer materials being the most commonly used nowadays [3-5]. Ion imprinting has emerged as an effective way to provide adsorbents with selective recognition and adsorption capabilities toward ions, which ultimately can be used for the preconcentration, detection, and especially the adsorption of ions [6-10]. Compared with bulk polymerization imprinted materials, surface imprinted materials have the advantages of fast adsorption, easy separation, and high recycling efficiency, with potential in real applications [11,12]. Polypropylene (PP) fibers can be successfully used to prepare imprinted materials due to the high porosity, large external surface area, high mass transfer efficiency, and easy recycling. Therefore, these polymer fibers have attracted the attention of researchers [13-15].

However, the preparation of imprinted PP involves first the surface modification of PP fibers with functional groups, which is commonly performed by surface grafting methods,

such as radiation-induced initiation [14] and plasma initiation [16]. In our previous study, the acrylic acid was grafted on the surface of PP fiber by plasma initiation and then Cr(VI) surface imprinted materials were prepared by amination, imprinting, and crosslinking [16]. The obtained material exhibited a good selectivity towards the adsorption of Cr(VI). Plasma polymerization is easy to perform, the polymerization time is short, and it is an environmentally friendly technique. However, it is challenging to construct large-size reactors, which, alongside with other specific technical problems, still limits the application of this method for the large-scale production. On the other hand, the grafted functional groups on the surface of PP fibers should be further modified, such as by amination, and after that they can be used for the preparation of ion-imprinted material.

The water-solid suspension grafting method uses water and polymer particles as dispersant and dispersed phase, respectively, to form a suspension system under mechanical agitation. In this suspension, each polymer particle can be regarded as an independent reaction bed, and the functional monomers can be grafted on the polymer surface in the presence of an initiator [17]. The grafting percentage of the suspension grafting polymerization is high, the reaction is performed under mild conditions, and the post-treatment of the products is simple [18]. Zhou *et al.* grafted maleic anhydride on the surface of PP and the melt-blown fibers showed significant increase in hydrophilicity and good adsorption capacity for Cu²⁺ [19]. Currently, single monomers are commonly used for the suspension grafting of PP, but grafting of comonomers is a more promising strategy because modified materials with various functionalities can be obtained [20-22]. Li *et al.* used water as dispersant,

*Corresponding author: wjwei@njtech.edu.cn

*Corresponding author: lianzyl1985@163.com

acetone as interfacial agent, and benzoyl peroxide as initiator to graft methyl methacrylate on PP [23]. The product was then used as a compatilizer of PP/acrylonitrile-styrene-acrylate mixture. In addition, the use of styrene comonomer increased the grafting percentage of methyl methacrylate. Zhao *et al.* grafted butyl acrylate and acrylic castor oil on the surface of PP by suspension grafting [24]. The influence of the polymerization parameters on the grafting efficiency was investigated and the mechanical properties of grafted products were significantly improved.


In this work, glycidyl methacrylate (GMA) and acrylamide (AM) were used as grafting monomers, and loaded on PP surface by a one-step suspension grafting. Then, the PP-g-(GMA-AM) (PGA) fibers were made by melt-blowing technology. Finally, the PP-g-(GMA-AM) ion-imprinted (IPGA) fibers were prepared by surface ion imprinting method. The effects of the monomers ratio, total monomer content, as well as dispersant and interfacial agent amounts, on the grafting percentage of GMA and AM were studied. The surface morphology, chemical composition, and structure of the modified materials were characterized by scanning electron microscopy (SEM), X-ray electron spectrometry (XPS), Fourier transform infrared spectroscopy (FT-IR), thermogravimetry analysis (TGA), and melt flow rate (MFR). The adsorption capacity and selectivity of the ion-imprinted fibers were investigated. The mechanism of adsorption was also proposed.

Experimental

Preparation of Ion-imprinted PP Fibers

The schematic diagram of IPGA synthetic process is illustrated in Scheme 1, where the entire process is divided into three steps. (1) Pre-treatment of PP [19]. PP resin (P6313, Shanghai Expert in the Developing of New Material Co., Ltd., Shanghai, China) and xylene (3 ml/g PP) were introduced into a magnetic stirring reactor and heated to 140 °C with a rate of 3 °C/min under magnetic stirring. Then, the mixture was poured into an ice water mixture (0 °C) for fast cooling and to enable the precipitation of PP from xylene and formation of low-crystallized microporous PP powders. The powder was recovered by filtration and then dried to a constant weight.

(2) Suspension grafting. PP powders (0.5 mm in diameter), dispersant (deionized water), and interfacial agent (xylene) were added to a magnetic stirring reactor and stirred at 90 °C for 1 h in the argon atmosphere to fully swell and disperse the PP powder. A certain amount of initiator (benzoyl peroxide, BPO) and monomers (GMA and AM) were added and copolymerized at 90 °C for 3 h. The obtained grafted products were washed with deionized water and acetone to remove the unreacted monomers and homopolymers. The grafting percentage of GMA and AM was calculated based on the titration and elemental analysis methods [25,26].



Scheme 1. Schematic diagram of IPGA fibers synthetic process.

Then, GMA and AM copolymerized PP fibers (PGA) were prepared through melt-blowing method [26].

(3) Surface ion-imprinting and crosslinking. PGA fibers were placed in 100 mg/l potassium dichromate solution and shaken at pH 3 and 25 °C for 90 min to allow the adsorption of Cr(VI) on the functional groups. Then, the fibers were introduced into a diethylenetriamine/ethanol solution and refluxed at 60 °C for 4 h for crosslinking. After crosslinking, the fibers were washed with 0.1 mol/l NaOH solution until Cr(VI) was not detected in the eluent. The resultant Cr(VI)-imprinted fibers were denoted as IPGA. The non-imprinted fibers were also prepared without addition of Cr(VI) ion, and denoted as NIPGA.

Characterizations

Scanning electron microscopy (JEOL JSM-5900 microscope) was used to observe the surface morphology of fibers before and after modification. The fiber surface was observed after gold spraying treatment, and then the surface morphology was observed at a voltage of 15 kV. Fourier-transform infrared spectrometry (Nexus 670 spectrometer, Nicolet) was used to characterize the functional groups on the fiber surface before and after modification, and the surface attenuation total reflection mode was used for scanning. The samples were scanned within the range of 500–4000 cm⁻¹ with a resolution of 1 cm⁻¹. The water contact angle formed by water on fibers was measured on a contact Angle tester (JC2000D, Shanghai Zhongchen technology Co., Ltd.). Deionized water (5 μl) was injected and the contact angle was recorded by a high-resolution camera. Five measurements were performed on different regions of the fiber and the results are their average. X-ray photoelectron spectroscopy (250XI spectrometer, Thermo Fisher) was used to characterize the surface chemical composition of the fibers. The melt

flow rate (MFR) of PP was measured at a temperature of 230 °C with a load of 2.16 kg. Three measurements were performed for each grafting percentage and averaged. A thermal analyzer (Pyris 1 DSC, PerkinElmer) was used to measure the weight loss and heat flow before and after chemical modification. The test temperature ranged from 25 to 600 °C with a heating rate of 20 °C/min under nitrogen gas with a flow of 20 ml/min.

Adsorption Experiments

Adsorption experiments were carried out in batch mode, and the average value of the three repeated experiments was reported. Fibers were immersed into a Cr(VI) solution at constant pH and temperature. After adsorption under shaking for a certain interval of time, the concentration of Cr(VI) in the solution was measured on an inductively coupled plasma - optical emission spectrometer (ICP-OES, iCAP 6300, Thermo Fisher scientific). The adsorption capacity (q_e) was calculated as:

$$q_e = \frac{(C_0 - C) \times V}{m} \quad (1)$$

where C_0 and C (mg/l) are the concentrations of Cr(VI) before and after adsorption, V (L) is the volume of solution, and m (g) is the mass of fibers.

The adsorption kinetics were fitted with pseudo-first-order (equation (2)) and pseudo-second-order (equation (3)) models [16].

$$\ln(q_e - q_t) = \ln q_e - k_1 t \quad (2)$$

$$\frac{t}{q_t} = \frac{1}{k_2 q_e^2} + \frac{t}{q_e} \quad (3)$$

where q_e is the equilibrium adsorption capacity, q_t is the adsorption capacity at time t , and k_1 (min^{-1}) and k_2 ($\text{mg}/(\text{g min})$) are the rate constants of pseudo-first-order and pseudo-second-order models, respectively.

The Scatchard equation is expressed as [27]:

$$\frac{q_e}{C_e} = \frac{q_{\max} - q_e}{K_s} \quad (4)$$

where q_e (mg/g) is the adsorption capacity at equilibrium, $q_{\max}$ (mg/g) is the maximum adsorption capacity, C_e (mg/l) is the residual concentration of Cr(VI), and K_s is the equilibrium dissociation constant.

The adsorption isotherm was fitted with Langmuir, Freundlich, and Temkin models [16]:

$$\text{Langmuir: } \frac{C_e}{Q_e} = \frac{C_e}{Q_m} + \frac{1}{K_L Q_m} \quad (5)$$

$$\text{Freundlich: } \ln Q_e = \ln K_F + \frac{1}{n} \ln C_e \quad (6)$$

$$\text{Temkin: } Q_e = \frac{RT}{B_T} \ln(K_T C_e) \quad (7)$$

where C_e (mg/l) is the concentration of Cr(VI) at equilibrium, Q_e (mg/g) and Q_m (mg/g) are the adsorption capacity at equilibrium and the maximum adsorption capacity, respectively, K_L (l/mg), K_F (l/mg), and K_T (J/mol) are the constants of Langmuir, Freundlich, and Temkin models, respectively.

The thermodynamics of the adsorption processes was evaluated, and the thermodynamic parameters, i.e., Gibbs free energy (ΔG), enthalpy (ΔH), and entropy (ΔS), were calculated with the equations below [5].

$$\ln \frac{Q_e}{C_e} = -\frac{\Delta H}{R} \times \frac{1}{T} + \frac{\Delta S}{R} \quad (8)$$

$$\Delta G = \Delta H - T \times \Delta S \quad (9)$$

where R (8.314 J/(mol K)) is the ideal gas constant and T (K) is the absolute temperature. The values of ΔH and ΔS were obtained from the slope and intercept of the plot of $\ln(Q_e/C_e)$ against $1/T$.

Cu(II), SO_4^{2-} , and Mo(VI) were selected as interfering ions to evaluate the adsorption selectivity of IPGA fibers towards Cr(VI). The concentration of interfering ions was varied from 20 to 100 mg/l, and the concentration of Cr(VI) was constant (100 mg/l). After adsorption experiments, the distribution coefficient (K_d , ml/g), selectivity coefficient (K), and relative selectivity coefficient (K') were calculated using equations (10)-(12) [28].

$$K_d = \frac{C_0 - C_e}{C_e} \times \frac{V}{m} \quad (10)$$

$$K = \frac{K_f(\text{Cr(VI)})}{K_d(\text{competing ion})} \quad (11)$$

$$K' = \frac{K_{\text{IPGA}}}{K_{\text{NIPGA}}} \quad (12)$$

Results and Discussion

Dual Monomer-grafting of PP Fibers

The influences of the ratio of two monomers, total monomer content, as well as the content of interfacial agent and dispersant on the grafting percentage are shown in Figure 1. As can be seen from Figure 1(a), the grafting percentage of GMA and AM increased first and then decreased slightly with the increase in GMA: AM ratio. When the GMA: AM ratio was 1.2: 1, the grafting percentage of monomers reached the maximum. It should be mentioned that in the grafting polymerization process, the interfacial agent swells the PP fibers generating an interfacial layer where the grafting reaction mainly takes place. Therefore,

the oil-soluble GMA is first grafted on PP surface. As the GMA: AM ratio increases, the grafting percentage of GMA increases, but until a certain ratio (i.e., 1.2). After that, the excessive GMA tends to homopolymerize [29]. As a result, a slight decrease in the grafting percentage of GMA is noticed. Theoretically, the Q values of GMA and AM (1.03 and 1.12, respectively) are around 1 and slightly higher than 1, respectively, indicating that GMA and AM can be easily converted into free radicals and are prone to copolymerize. The e values of GMA and AM (0.57 and 1.19, respectively) are significantly different, highlighting the tendency of the two monomers to alternate in the copolymer chain. These values show that AM is usually grafted onto PP through the "bridge" of GMA, and GMA and AM alternate in the macromolecular chain. Therefore, the grafting percentage of GMA is higher than that of AM [26]. AM mainly exists in the aqueous phase. When the amount of AM is high, the GMA sites available for copolymerization are limited, resulting in a low grafting percentage of GMA and AM.

Figure 1(b) shows the influence of the total monomer content (GMA, AM) on the grafting percentage of GMA and AM at the optimum GMA: AM ratio of 1.2. As observed, the grafting percentage of both GMA and AM increases first and then decreases with increasing the total monomer content. At a total monomer content of 60 % of the PP mass,

the grafting percentage of both monomers reached the maximum. Appropriate monomer content promotes the collisions between monomers and free radicals, which is conducive to the grafting reaction. However, above this limit, excessive monomer concentration may lead to the homopolymerization of monomers, as well, phenomenon reflected by the decrease in monomer grafting percentage.

Figure 1(c) shows the effect of the content of dispersant (deionized water) on the grafting percentage of monomers. As can be seen, the grafting percentage of GMA and AM increased first and then decreased with the increase in water content. When the amount of deionized water was 8 mL/g PP, the grafting percentage of monomers reached the maximum. At low amount of water (< 8 mg/l), the PP particles could not be effectively dispersed, leading to aggregation and low grafting percentage. When the amount of dispersant is too high (> 8 mg/l), the concentration of the monomer dissolved in water is relatively low, causing a small concentration gradient between the dispersant and the interfacial reaction layer. Hence, the monomer cannot be effectively transferred to the interfacial reaction layer and participate in the graft polymerization reaction.

Above this concentration, the impact of this parameter on the grafting percentage of the two monomers was different. Therefore, the grafting percentage of GMA was almost




Figure 1. Effect of the (a) GMA to AM ratio, (b) monomer concentration, (c) water content, and (d) interfacial agent concentration on the grafting percentage of GMA and AM.

constant with only an insignificant decrease while that of AM decreased significantly. Therefore, increasing the amount of interfacial agent until an optimum concentration is helpful for the grafting reaction. However, when the amount of interfacial agent is too high, the concentration of GMA in the interfacial layer is low, which reduces the grafting efficiency. Moreover, the solubility of AM in the interfacial agent is low, and excessive interfacial agent seriously affects the mass transfer process, significantly decreasing the grafting percentage of AM.

Characterizations

The polar branched chains of GMA and AM increase the strength of interaction of PGA molecules, with impact on the flow of the raw material and thus, on the melt-blown spinning process. Figure 2 shows how monomer grafting influences the MFR of grafted products. The MFR of pristine PP is about 1300 g/10 min. The MFR kept almost constant, with a slight increase, up to a grafting percentage of about 6 %. The α -H of PP macromolecular chain is easily captured by the benzoyl peroxide to produce free radicals




Figure 2. Effect of the grafting percentage on the MFR of PP powders.




Figure 3. (a) TGA and (b) DTG curves of PP, PGA, and IPGA fibers.

[18]. At this time, the β bonds are broken, resulting in a slight decrease in molecular weight and increase in MFR. Afterwards, as the grafting percentage continued to increase, the strength of hydrogen bonds between the polar side chains increased, and the MFR of PGA decreased rapidly [24]. In the light of the obtained results, it can be stated that the MFR of the grafted product meets the requirements of melt-blown spinning process.

Figure 3 displays the TGA and DTG curves of PP resin, PGA, and IPGA fibers. According to the TGA curves (Figure 3(a)), the suspension of the grafted PGA resin has better thermal stability than the unmodified PP resin. No significant weight loss before 200 °C was obtained and mainly associated with the removal of the physisorbed water. Therefore, the grafted product exhibits the thermal stability required by the melt-blown spinning process. However, the thermally resistant cross-linking products in the IPGA fibers are not decomposed even at temperatures higher than 500 °C. In addition, Figure 3(b) shows that the maximum temperature of the degradation of IPGA imprinted fibers is slightly higher than those of PP and PGA, which is attributed to the cross-linking products on the fiber surface.

Figure 4(a), (b), and (c) display the SEM images of PP, PGA, and IPGA fibers, respectively. As noticed, the surface morphology and diameter of PGA fibers did not significantly change compared with those of unmodified PP fibers. Therefore, the suspension grafting had no influence on the morphology and diameter of PGA fibers, which are mainly controlled by the melt-blowing process. The surface of imprinted IPGA fibers is rough and porous, mainly due to the imprinting and crosslinking on the fiber surface [30]. As illustrated in Figure 4(d), deionized water spread out on the surface of IPGA nonwoven fabrics instantly while the droplets of water formed on the PP fiber are illustrated in the inset. This demonstrates that the modified fiber has a good hydrophilicity.

As can be seen from Figure 5, illustrating the FT-IR spectra of samples, the spectrum of PGA displays the




Figure 4. SEM images of (a) PP, (b) PGA, (c) IPGA fibers, and (d) water contact angle of IPGA and PP nonwoven fabrics.

characteristic vibration bands of the grafted monomers. The stretching vibration band of the C=O bond of GMA appeared at 1725 cm^{-1} . The stretching vibration band of the C-O-C group of GMA is found at 1151 cm^{-1} , whereas the vibration bands of the epoxy group appeared at 902 and 840 cm^{-1} , respectively [31]. The stretching vibration band of the N-H functional group from primary amide in AM is found as a broad peak ranging from 3540 to 3125 cm^{-1} . The stretching vibration band of the C=O from AM is shifted at lower wavenumber due to the unshared electron pair on the nitrogen atom and the p-conjugation of the carbonyl group compared with the C=O bond in GMA. Hence, the band at 1668 cm^{-1} is attributed to the C=O stretch vibration of AM. The infrared spectrum of IPGA imprinted fibers are similar to those of PGA, excepting the characteristic vibration bands at 902 and 840 cm^{-1} of epoxy group, which disappear as a




Figure 5. FT-IR spectra of PP, PGA, and IPGA fibers.

result of the open-loop crosslinking between diethylenetriamine (DETA) and epoxide.

Adsorption Capacity

Effect of the pH

The adsorption capacity of IPGA toward Cr(VI) at different pH values ranging from 1 to 9 is depicted in Figure 6. As noticed, with the increase in pH of solution from 1 to 3, the adsorption capacity of IPGA increased slowly, achieving a maximum value of 43.2 mg/g at pH 3. After that, the adsorption capacity decreased rapidly with the increase in pH value. At low pH, the solution is rich in H^+ , which can combine with the lone pair electrons of N atom in $-\text{NH}_2$ on the surface of IPGA, resulting in positively charged $-\text{NH}_3^+$. At this point, the Cr(VI) exists as anion state in the solution, which can combine with protonated functional groups through electrostatic interaction. It also can be seen in the figure that the pH drift (initial pH - final pH) of IPGA is relatively high at pH 3, indicating that the fiber surface is mainly positively charged and the adsorption amount of Cr(VI) is the highest [32]. When the pH value is less than 3, the adsorption capacity of the fibers decreased slightly, because within this pH range, the HCrO_4^- will be partially converted into non-ionic H_2CrO_4 , which is difficult to combine with the protonated functional groups. However, when the pH value is higher than 3, the deprotonation of functional groups on the surface of the fiber increases gradually with the pH, resulting in a competitive adsorption of OH^- and Cr(VI). In addition, during the preparation of IPGA, the Cr(VI) template ion is mainly as HCrO_4^- and thus, the resulted imprinted cavities display the memory of HCrO_4^- anion [33-35].

Adsorption Kinetics

Figure 7 shows the change in the adsorption capacity of IPGA over time. As can be seen, the adsorption Cr(VI) on the imprinted fiber was very fast within the first 30 min.




Figure 6. Effect of the pH on the adsorption capacity of IPGA to Cr(VI) and pH drift.

Then, the adsorption capacity of Cr(VI) increased slowly with the adsorption time. After 90 min of adsorption, the




Figure 7. Effect of the contact time on Cr(VI) adsorption capacity of IPGA and fittings by pseudo-first-order and pseudo-second-order models.

adsorption at equilibrium is 43.2 mg/g. Figure 7 shows the pseudo-first-order and pseudo-second-order kinetic fittings of the adsorption data, and the calculated parameters are listed in Table 1. The correlation coefficients of the two models are above 0.90, but R^2 of the pseudo-second-order kinetic model is higher ($R^2=0.995$) than that of the pseudo-first-order kinetic model ($R^2=0.940$). Furthermore, the value of the adsorbed amount at equilibrium assessed by pseudo-second-order is closer to the experimental value. Therefore, the adsorption process follows the pseudo-second-order kinetic model, indicating the prevalence of the chemical adsorption.

Adsorption Isotherm

Figure 8(a) depicts the influences of the initial concentrations of Cr(VI) (10–80 mg/L) and temperature (20–35 °C) on the adsorption on IPGA. The experimental results revealed that the Cr(VI)-adsorption capacity increases with the initial concentration of Cr(VI) and temperature. Langmuir, Freundlich, and Temkin adsorption models were used to fit the adsorption data. The fitting results are depicted in Figure

Table 1. Kinetic parameters of Cr(VI) adsorption by IPGA

Q (mg/g)	Pseudo-first-order			Pseudo-second-order		
	q (mg/g)	k_1 (min^{-1})	R^2	q (mg/g)	k_2 ($\text{g}/(\text{mg}\cdot\text{min})$)	R^2
43.2	41.21	0.0645	0.952	44.37	0.0067	0.994




Figure 8. (a) Adsorption isotherm and fittings using (b) Langmuir, (c) Freundlich, and (d) Temkin models for Cr(VI) adsorption on IPGA fibers at different initial concentrations of Cr(VI) and temperatures.

Table 2. Isotherm parameters for the adsorption of Cr(VI) on IPGA

T (°C)	Langmuir			n	Freundlich		Temkin		
	Q_m (mg/g)	K_L (l/mg)	R^2		K_F (l/mg)	R^2	B_T	K_T (J/mol)	R^2
20	48.1	0.0216	0.995	2.120	4.493	0.953	11.97	0.241	0.988
27	58.4	0.0249	0.999	1.870	3.954	0.947	14.80	0.185	0.981
35	59.5	0.0362	0.991	1.954	5.211	0.955	14.36	0.289	0.964

8(b)-(d), and the relevant fitting parameters are listed in Table 2. The fitting curve and the correlation coefficient, R^2 , indicate that the Langmuir adsorption model better explains the Cr(VI) adsorption on IPGA, indicating that the process involves the adsorption of Cr(VI) as a monolayer [36]. In addition, the K_L values increase with the increase in temperature, indicating that adsorption is an endothermic process, and temperature is conducive to the adsorption. K_L values of the Langmuir adsorption model are in the range of 0-1, prove of a favorable adsorption process [37].

Adsorption Thermodynamics

The thermodynamic parameters of the adsorption process obtained by fitting are listed in Table 3. As can be seen, ΔG_0 of Cr(VI) adsorption on IPGA is negative irrespective of the temperature, indicating that the adsorption process is spontaneous. In addition, the absolute value of ΔG_0 increases with the increase in temperature, confirming the positive role of the temperature in the Cr(VI) adsorption. The positive value of ΔH_0 indicates that the adsorption process is endothermic and a high temperature (e.g., 27 °C) is beneficial to the adsorption of Cr(VI). Since hydrated Cr(VI) ions may release water molecules during the adsorption on the surface of fibers, the degree of disorder increases, resulting in an positive value of ΔS_0 [38].

Adsorption Selectivity


Figure 9 depicts the isotherms of Cr(VI) adsorption on IPGA and NIPGA fitted with the Scatchard model. It can be seen that the Scatchard plot analysis of IPGA led to two straight lines with different slopes and intercepts. The left end of the fitting curve is associated with the high affinity and selectivity of the adsorption sites while the right end shows the low affinity and selectivity of the sites [39]. The maximum apparent adsorbed amount and the equilibrium dissociation constant can be calculated based on the slope and intercepts of these curves. Therefore, according to the obtained lines, the surface of IPGA displays both specific

and non-specific adsorption sites. The data of Cr(VI) adsorption on non-imprinted fibers (NIPGA) is fitted by a straight line, indicating the presence of the non-specific sites exclusively.

Figure 10 shows the selectivity coefficient, K and relative selectivity coefficient, K' , of IPGA and NIPGA for Cr(VI) at different concentrations of the competitive ions (Cu(II) , SO_4^{2-} , and Mo(VI)). The experimental results show that K of IPGA and NIPGA decrease with increasing competing ion concentration, indicating the influence of the competing ions on the adsorption of Cr(VI). However, K value of IPGA is higher than that of NIPGA, demonstrating that the specific adsorption sites generated by the imprinting process can effectively recognize Cr(VI) ion, which is in contrast to NIPGA. In addition, K value of IPGA and NIPGA in the presence of SO_4^{2-} and Mo(VI) is significantly lower than that of Cu(II) , indicating that SO_4^{2-} and Mo(VI) are more competitive for Cr(VI) adsorption. This is because SO_4^{2-} and Mo(VI) (especially Mo(VI)) are anions and have similar structure and electric charge compared with Cr(VI), thus interfering with the selective recognition of Cr(VI) on IPGA fibers [5,6]. Furthermore, the competitive adsorption of anionic SO_4^{2-} and Mo(VI) on NIPGA is stronger, in which K' value in the presence of these two anions is higher than that of Cu(II) . In spite of the influence of competitive ions on the selective adsorption of Cr(VI), IPGA fibers show preferential adsorption to Cr(VI) due to the imprinted cavities, which are similar to Cr(VI) ion in shape, size,

Table 3. Thermodynamic parameters for Cr(VI) adsorption on IPGA

T (°C)	$\ln K_0$	ΔG_0 (kJ/mol)	ΔH_0 (kJ/mol)	ΔS_0 (kJ/mol·K)
20	0.6687	-1.63		
27	0.9204	-2.30	18.57	0.070
35	1.0260	-2.63		

**Figure 9.** Scatchard analysis of IPGA and NIPGA for Cr(VI) adsorption.




Figure 10. Effect of the (a) $Cu(II)$, (b) SO_4^{2-} , and (c) $Mo(VI)$ competitive ions on K and K' of IPGA and NIPGA for Cr(VI) adsorption.

charge, and three-dimensional structure.

Adsorption Mechanism

To understand the mechanisms of Cr(VI) adsorption on IPGA, the XPS spectra of IPGA fibers after Cr(VI) adsorption was recorded. The survey spectrum displays four

main peaks, which shows the presence of C, N, O, and Cr in the sample. The N 1s signal (Figure 11(b)) was fitted with three peaks. The peaks at 398.2 and 399.0 eV were assigned to NH_2 and N-H, respectively, and the peak at 399.9 eV was attributed to the amine-Cr complex. The coordination of the amine groups to Cr(VI) involves sharing of electrons of N atom with Cr(VI) ions. As a result, the outer electron pair of N moves, the electron cloud density decreases, and a new characteristic peak at higher binding energy, 399.9 eV, appears. Figure 11(c) shows the high-resolution O 1s spectrum. The O 1s signal was fitted with three peaks. The peak at 533.2 eV was attributed to the complex made between oxygen-containing groups of IPGA and Cr species, whereas the peaks at 532.1 and 531.6 eV were attributed to O=C and C-O-C, respectively [40]. Cr 2p $_{3/2}$ signal was fitted with two peaks at 577.0 and 580.0 eV, indicating that part of Cr(VI) was reduced to Cr(III). In line with the previous studies, it can be affirmed that the amine groups can act as electron donors that reduce Cr(VI) into Cr(III) [40]. However, the redox potential of amino groups on IPGA may not be high enough to totally convert the adsorbed Cr(VI) into Cr(III) [41].

Reusability

The reusability of IPGA fibers for Cr(VI) adsorption was investigated. The adsorption experiments were conducted in batch mode. Typically, IPGA fibers were placed into Cr(VI) solution and sonicated for adsorption. The adsorption conditions were: temperature at 30 °C, Cr(VI) concentration of 100 mg/l and volume of 50 ml (pH=3). After 90 min, IPGA fibers were removed and Cr(VI) was eluted using dilute NaOH solution (0.5 mol/l) several times until Cr(VI) was not detected in the elute solution. The elute was collected and the concentration of Cr(VI) was analyzed using ICP-OES, then the Cr(VI) adsorption capacity was calculated. After regeneration, rinsing with water, and dried, IPGA fibers were used in the next adsorption-regeneration cycle. The results of 6 cycles are shown in Figure 12. Therefore, Cr(VI) adsorption capacity slightly decreases after 6 cycles, indicating that IPGA fibers are stable and have potential for practical application.

Conclusion

In summary, this work proposes new IPGA imprinted fibers prepared by suspension graft polymerization and Cr(VI) ion-imprinting technology. The fibers were grafted with two monomers (GMA and AM) and the synthesis conditions affecting the grafting percentage were systematically studied. The pristine and modified fibers were carefully characterized and then the adsorption ability of the imprinted fibers towards Cr(VI) was investigated. The results showed that the best modified fibers were obtained at a GMA: AM monomer ratio of 1.2: 1, a total monomer content of 60 %, a dispersant concentration of 8 ml/g, and an interfacial agent




Figure 11. XPS spectra (a) full spectra, (b) N 1s, (c) O 1s, and (d) Cr 2p_{3/2} of IPGA after Cr(VI) adsorption.




Figure 12. Variation of Cr(VI) adsorption capacity after 6 cycles.

concentration of 5 mg/g. Under these conditions, the grafting percentages of GMA and AM were of 16.4 and 10.6 %, respectively. The results of FT-IR, SEM, TGA, and water contact angle characterizations demonstrated the successful preparation of IPGA. The pH was an important factor affecting the adsorption of Cr(VI) on IPGA, the maximum adsorption capacity being at a pH value of 3, and the adsorption at equilibrium was 43.2 mg/g at 90 min. It was

found that the adsorption of Cr(VI) on IPGA was consistent with the Langmuir model, involving the formation of a monolayer. The thermodynamics results revealed that the adsorption of Cr(VI) on IPGA is spontaneous and endothermic. The Scatchard analysis showed the presence of both specific and non-specific adsorption sites on the IPGA surface, whereas the corresponding non-imprinted fibers have only non-specific adsorption sites. The IPGA exhibited selectivity towards Cr(VI) in the presence of competing Cu(II) and SO_4^{2-} ions. However, the experimental studies revealed that the competitive effect of the SO_4^{2-} is more obvious than that of Cu(II). The adsorption mechanism was established based on XPS analysis performed for the IPGA fibers loaded with Cr(VI). The XPS results showed that N and O elements in functional groups participate to the adsorption process of Cr(VI), and the adsorption mechanism involved the electrostatic attraction between Cr(VI) and functional groups while a part of Cr(VI) was reduced into Cr(III).

Acknowledgements

This study was supported by National Natural Science Foundation of China (Grant Number 21676144).

References

1. Z. Zhou, X. Liu, M. Zhang, J. Jiao, H. Zhang, J. Du, B.

- Zhang, and Z. Ren, *Sci. Total Environ.*, **699**, 134334 (2020).
2. F. He, Z. Lu, M. Song, X. Liu, H. Tang, P. Huo, W. Fan, H. Dong, X. Wu, and G. Xing, *Appl. Surface Sci.*, **483**, 453 (2019).
 3. D. Kong, F. Zhang, K. Wang, Z. Ren, and W. Zhang, *Ind. Eng. Chem. Res.*, **53**, 4434 (2014).
 4. G. Bayramoglu and M. Y. Arica, *J. Hazard. Mater.*, **187**, 213 (2011).
 5. R. Huang, X. Ma, X. Li, L. Guo, X. Xie, M. Zhang, and J. Li, *J. Colloid Interface Sci.*, **514**, 544 (2018).
 6. M. Y. Zhang, R. F. Huang, X. G. Ma, L. H. Guo, Y. Wang, and Y. M. Fan, *Anal. Bioanal. Chem.*, **411**, 7165 (2019).
 7. Y. Chen, X. Ma, M. Huang, J. Peng, and C. Li, *Analytical Methods*, **8**, 824 (2016).
 8. M. Ghanei-Motlagh and M. A. Taher, *Chem. Eng. J.*, **327**, 135 (2017).
 9. S. Hassanpour, M. Taghizadeh, and Y. Yamini, *J. Polym. Environ.*, **26**, 101 (2018).
 10. Z. Ren, D. Kong, K. Wang, and W. Zhang, *J. Mater. Chem. A*, **2**, 17952 (2014).
 11. Z. Lu, G. Zhou, M. Song, X. Liu, H. Tang, H. Dong, P. Huo, F. Yan, P. Du, and G. Xing, *Appl. Catal. B: Environ.*, **268**, 118433 (2020).
 12. Z. Lu, G. Zhou, M. Song, D. Wang, P. Huo, W. Fan, H. Dong, H. Tang, F. Yan, and G. Xing, *J. Mater. Chem. A*, **7**, 13986 (2019).
 13. L. Zhang, S. Yang, J. Qian, and D. Hua, *Ind. Eng. Chem. Res.*, **56**, 1860 (2017).
 14. T. Li, S. Chen, H. Li, Q. Li, and L. Wu, *Langmuir*, **27**, 6753 (2011).
 15. M. A. Söylemez, M. Barsbay, and O. Güven, *Radiat. Phys. Chem.*, **142**, 77 (2018).
 16. Z. Luo, J. Xu, D. Zhu, D. Wang, J. Xu, H. Jiang, W. Geng, W. Wei, and Z. Lian, *Polymers*, **11**, 1508 (2019).
 17. Z. Li, L. Wang, Y. Ma, and W. Yang, *Chinese Chem. Lett.*, **26**, 1351 (2015).
 18. F. Liang, H. Yuan, Q. Shao, and W. Song, *Des. Monomers Polym.*, **21**, 130 (2018).
 19. Q. Zhou, M. Li, X. Yao, Z. Lian, C. Zhang, W. Wei, and J. Huang, *Fiber Polym.*, **15**, 2238 (2014).
 20. Y. Zheng, S. Zhao, L. Cheng, and B. Li, *Polym. Bull.*, **64**, 771 (2010).
 21. R. Tao, Q. Pang, T. Xu, L. Xu, X. Yang, and X. Zhu, *J. Appl. Polym. Sci.*, **137**, 48300 (2020).
 22. T. B. Mostafa, *J. Appl. Polym. Sci.*, **111**, 11 (2009).
 23. Z. Li, Y. Ma, and W. Yang, *J. Appl. Polym. Sci.*, **129**, 3170 (2013).
 24. D. Zhao, L. Wang, R. Zhang, Y. Ma, D. Chen, C. Zhao, and W. Yang, *Polym. Eng. Sci.*, **58**, 86 (2018).
 25. Y. Kong, Y. Li, G. Hu, J. Lin, D. Pan, D. Dong, E. Wujick, Q. Shao, M. Wu, J. Zhao, and Z. Guo, *Polymer*, **145**, 232 (2018).
 26. M. Guo, C. Zhang, J. Xu, Z. Luo, and W. Wei, *Fiber Polym.*, **17**, 1123 (2016).
 27. L. He, Y. Su, Y. Zheng, X. Huang, L. Wu, Y. Liu, Z. Zeng, and Z. Chen, *J. Chromatogr. A*, **1216**, 6196 (2009).
 28. F. He, Z. Lu, M. Song, X. Liu, H. Tang, P. Huo, W. Fan, H. Dong, X. Wu, and S. Han, *Chem. Eng. J.*, **360**, 750 (2019).
 29. S. Saxena, A. R. Ray, and B. Gupta, *J. Appl. Polym. Sci.*, **116**, 2884 (2010).
 30. Y. Zheng, H. Liu, P. V. Gurgel, and R. G. Carbonell, *J. Membr. Sci.*, **364**, 362 (2010).
 31. Y. Kong, Y. Li, G. Hu, J. Lin, D. Pan, D. Dong, E. Wujick, Q. Shao, M. Wu, J. Zhao, and Z. Guo, *Polymer*, **145**, 232 (2018).
 32. L. S. Balistrieri and J. W. Murray, *Am. J. Sci.*, **281**, 788 (1981).
 33. G. Bayramoglu and M. Y. Arica, *J. Hazard. Mater.*, **187**, 213 (2011).
 34. M. Etemadi, S. Samadi, S. S. Yazd, P. Jafari, N. Yousefi, and M. Aliabadi, *Int. J. Biol. Macromol.*, **95**, 725 (2017).
 35. J. Fang, Z. Gu, D. Gang, C. Liu, E. S. Ilton, and B. Deng, *Environ. Sci. Technol.*, **41**, 4748 (2007).
 36. M. M. Motsa, J. M. Thwala, T. A. M. Msagati, and B. B. Mamba, *Phys. Chem. Earth*, **36**, 1178 (2011).
 37. A. Baraka, P. J. Hall and M. J. Heslop, *React. Funct. Polym.*, **67**, 585 (2007).
 38. A. D. Gupta, S. Pandey, V. K. Jaiswal, V. Bhadauria, and H. Singh, *Carbohydr. Polym.*, **222**, 114964 (2019).
 39. P. Liu, H. An, Y. Ren, J. Feng, and J. Ma, *Chem. Eng. J.*, **349**, 176 (2018).
 40. G. Dognani, P. Hadi, H. Ma, F. C. Cabrera, A. E. Job, D. L. S. Agostini, and B. S. Hsiao, *Chem. Eng. J.*, **372**, 341 (2019).
 41. S. Yu, G. Yuan, H. Gao, and Y. Liao, *J. Mater. Sci.*, **55**, 163 (2020).



Styrene-assisted acrylic acid grafting onto polypropylene surfaces: preparation, characterization, and an automatically latex-coagulating application

Chaiwute Vudjung¹ · Pranee Nuinu¹ · Ponsakda Yupas¹ · Rattapong Seelakun¹ · Sayant Saengsuwan^{1,2}

Received: 12 October 2021 / Revised: 21 February 2022 / Accepted: 22 May 2022

© The Author(s), under exclusive licence to Springer-Verlag GmbH Germany, part of Springer Nature 2022

Abstract

This work aimed to modify the polypropylene (PP) surface by grafting with acrylic acid (AA) monomer in toluene solution using styrene (ST) and benzoyl peroxide (BPO) as comonomer and initiator, respectively, for potential application as an automatically latex-coagulating cup. The grafting percentage of PP-g-PAA was slightly increased with increasing time of surface activation, grafting reaction time, and concentrations BPO and AA. Interestingly, the presence of ST comonomer significantly improved the grafting percentage of AA onto PP sheets (PP-g-P(ST-co-AA)) and its ion exchange capacity from 5.76 to 25% and 8.87×10^{-5} to 43.1×10^{-5} meq/g, respectively. This indicated that the incorporation of ST could significantly enhance the grafting reaction of AA onto the PP surfaces. The possible mechanism of grafting reaction was also described and demonstrated. Besides, the PP-g-P(ST-co-AA)25 exhibited high coagulum performance of natural rubber latex (NRL) of 93.8% and high NRL coagulation rate of 63.5% %/h. Thus, the grafted PP with ST/AA monomers as an automatically latex-coagulating cup/container could offer not only the lower production cost and lesser environmental problems but also improved properties, qualities, and price of cup lump products.

Keywords Surface modification · Natural rubber · Ion exchange capacity · Cup lump · Acetic acid

✉ Sayant Saengsuwan
sayant.s@ubu.ac.th; sayants181@gmail.com

¹ Laboratory of Advanced Polymer and Rubber Materials (APRM), Department of Chemistry, Faculty of Science, Ubon Ratchathani University, Ubon Ratchathani, Warinchamrap 34190, Thailand

² Department of Chemistry and Center of Excellence for Innovation in Chemistry (PERCH-CIC), Faculty of Science, Ubon Ratchathani University, Ubon Ratchathani, Warinchamrap 34190, Thailand

Introduction

Generally, cup lump is an upstream and important product in natural rubber (NR) industries which is mostly supplied for block rubber productions [1]. Cup lump is produced by coagulation process of the field natural rubber latex (NRL) in a cup container. The rubber particles of NRL have a core-shell structure consisting of *cis*-1,4-polyisoprene as a core and mixed membranes of proteins and lipids as a shell [2–4]. To harvest latex in the solid state, the NRL can be coagulated by either natural or chemical coagulations using the bacteria action or weak acid, respectively [2–5]. However, the natural coagulation of NRL takes very long time. Thus, weak acid is normally used instead to lessen the coagulation time. Formic and acetic acids are recommended as latex coagulant for the upstream production of NR manufacturing such as rubber sheet and cup lump but sulfuric acid (H_2SO_4) is more popular latex coagulant used by Thailand rubber farmers due to its low price and ready to use [6]. However, it causes the lower plasticity and low final properties of rubber blocks, compared to the Standard Thailand Rubber (STR). Besides, it generates H_2SO_4 wastewater with H_2S toxic gases and rotten eggs smell [7]. Therefore, if the NRL can be automatically coagulated in a collecting cup without using any acids or with less acid content, it could not only reduce the labor time, production cost, and environmental impact but also improve the properties, qualities, and price of cup lump products. Polypropylene (PP) is well known as a commodity thermoplastic polymer used widely in several applications. It is a non-polar and mechanically rugged material with high chemical resistance and low price [8]. Therefore, PP is extensively used as raw material for NRL container (cup) in Thailand. PP has also been modified for various applications such as textile dyeability, adhesion, and polarity improvement of packaging industry, plastic parts for many industries including consumer products, and elaborated membranes with specific properties [9]. Acrylic acid monomer (AA) is used as a raw material for proton exchange membrane because polyacrylic acid (PAA) is an anionic polyelectrolyte possessing the high charge density based on the dissociated carboxyl group [10]. The AA monomer is usually grafted with polyurethane and poly(ethylene terephthalate) for tissue engineering and antibacterial properties, respectively [11, 12]. Moreover, it is popularly chosen to modify the PP surface as reported by several researches [13–16]. For instance, AA monomers were grafted on PP films with grafting percentage of 34.55% by simultaneous radiation grafting reaction to improve hydrophilicity and their biodegradability [13]. The PP monofilaments were grafted with PAA by plasma-induced graft polymerization to immobilize chitosan onto the PP filaments for enhancing the antibacterial and antifungal properties [14]. In addition, PP film was grafted with AA using photo-initiated graft polymerization and the grafted PP film was assembled with chitosan and sodium alginate to remove the trace transition metal ions which catalyze the oxidation in food [15]. PAA was also grafted on the PP surface film by radical photo-grafting polymerization but its grafting percentage was just only 12.9% for covalent bonding with specific organic molecules (dye, antimicrobial or antifungal drugs, etc.) [16]. However, the grafting percentage of

AA monomers onto the PP surface, in particular the solution free-radical polymerization, is normally low and thus inadequate to generate the enough positively charged ions for NRL coagulation process. To solve this drawback, improvement of the grafting percentage by grafting copolymerization could be an alternative pathway. Also, styrene (ST) as a comonomer is also found to be an effective way for improving the grafting degree of maleic anhydride (MA) onto the polymer matrix [17, 18]. The presence of ST comonomer generates electrons which can promote the MA activity and reduce its unsymmetrical structure and its π radical-anion bonds [17]. For example, Phadnis et al. [18] prepared the ST/AA comonomers grafted onto fluorinated ethylene propylene copolymer via pre-irradiation technique. The grafting degree increased with increasing monomer content, radiation dose, temperature, and reaction time. Moreover, considerable researches have been devoted to graft ST/AA comonomers onto the different polymers for several application such as hydrophilic fibers, ion exchange membranes, and environment fields [19, 20]. To the best of our knowledge and the above literature reviews, the surface modification of PP grafting with ST/AA comonomers prepared by using solution free-radical polymerization has been rarely reported especially an automatically NRL coagulating application. The main aim of this study was to improve the surface-grafting degree of PP sheet with ST/AA comonomers. The PP sheet was grafted with AA in toluene using benzoyl peroxide (BPO) as an initiator. More importantly, styrene (ST) comonomers were also incorporated to enhance the grafting degree of AA monomers on the PP surfaces. The effects of time of surface activation, grafting time, concentration of BPO and AA, and ratio of ST/AA on the grafting percentage were carried out. The grafted PP samples were then characterized by FTIR, EDX, SEM, and AFM techniques. Contact angle and ion exchange capacity (IEC) including hardness and impact strength of the grafted PP samples were also investigated. Finally, the coagulation of NRL by using the grafted PP sheets was also evaluated to see their efficiency. Results reveal that the presence of ST monomer significantly enhances the grafting percentage of PP-g-P(ST-co-AA) which is 377% higher than that of PP-g-AA. And the obtained PP-g-P(ST-co-AA)25 sheet can be applied as an automatically latex-coagulating material and exhibits the excellent coagulum content of 93.8%.

Experiments

Materials

Isotactic polypropylene (PP, 1100PK POLIMAXX) produced for rubber cup injection molding was obtained from IRPC Public Co. Ltd, Thailand. The official data sheet of manufacturer has reported that PP has a melt flow index = 15 g/10 min (230 °C and 2.16 kg, ASTM D1238), and tensile strength and elongation at yield = 36 N/mm² and 26%, respectively. Acrylic acid (AA; Loba Chemie PVT. Co. Ltd., India), styrene (ST; Arcos Organic Co. Ltd., Belgium), and benzoyl peroxide (BPO; Arcos Organic Co. Ltd, Belgium, as initiator) were obtained for use in this work. The ST and AA monomers were firstly purified by distillation prior to use.

Acetone, xylene, toluene, NaOH, and NaCl were obtained from Fisher Chemical Co. Ltd., USA. The field natural rubber latex (NRL) was harvested from rubber trees clones RRIM 600 cultivated by Faculty of Agriculture, Ubon Ratchathani University, Thailand. The field NRL without alkaline preservation was ca. 30% dry rubber content (DRC).

Preparation of polypropylene (PP) sheet

PP pellets were molded into a sheet (7 mm thick) by a compression molding at 210 °C for 7 min and rapidly cooled down to room temperature in cooling press. The prepared PP sheets were then cut into a rectangle bar of 13×64×7 mm³ and washed with an excess acetone for 10 min to remove any impurity adhered on its surface.

Grafting reaction

In order to produce PP sheet with automatically latex-coagulating properties, the PP surface was modified by a free-radical grafting reaction with AA and ST monomers in toluene adopted from Wang et al. [21] The PP sheets were firstly washed and placed into a three-necked reaction flask with an overhead stirrer, a thermometer, a reflux condenser, and nitrogen supply. The grafting procedure can be divided into two steps as follows. In the first step, the surface activation), toluene (250 mL), and BPO (15–25 wt% of PP) were added into the flask and kept for 0.5 – 2.5 h at 95±5 °C. In the latter step, the grafting reaction, various AA/ST mixed solutions (150–350 mL) at volume ratios of 100/0, 90/10, 80/20, 70/30, 60/40, and 50/50 were added in the reaction flask and the grafting reaction was performed under N₂ atmosphere for 1–9 h. At the predetermined time, the reaction was cooled down quickly in water bath to yield the PP-g-P(ST-co-AA) sheets. For comparison, the grafted PP without ST comonomer (the PP-g-PAA) was also prepared with the same procedures without using ST in the reaction. The chemical compositions and reaction conditions for preparation of PP-g-PAA and PP-g-P(ST-co-AA) samples are summarized in Table 1.

Purification of grafted PP products

The grafted PP products were washed with acetone and xylene mixture (1:1 ratio) for 1 h to remove the unreacted AA, ST, and AA/ST reactants and then dried in a vacuum oven at 80 °C for 15 h until weight constants. The grafting percentage is calculated by using Eq. (1) [12].

$$\text{Grafting percentage (\%)} = \frac{w - w_o}{w_o} \times 100 \quad (1)$$

where w is weight of the grafted PP sheets after washing with acetone and xylene, and w_o is weight of PP sheet before grafting.

Table 1 Chemical compositions and reaction conditions for preparation of PP-g-PAA and PP-g-P(ST-co-AA) samples

Sample	PP-g-PAA	PP-g-P(ST-co-AA)
<i>Surface acting step</i>		
PP sheets (g)	5	5
Toluene (mL)	250	250
BPO (wt% of PP)	15–25	25
Reaction time (h)	0.5–2.5	25
Temperature (°C)	95 ± 5	95 ± 5
<i>Grafting reaction step</i>		
AA (wt% of PP)	0–350	
AA/ST (wt%)		100/0, 90/10, 80/20
(total weight = 250 wt% of PP)		70/30, 60/40 and 50/50
Monomer (wt% of PP)	150–350	250
Reaction time (h)	1–9	7
Temperature (°C)	95 ± 5	95 ± 5

Characterizations

FTIR spectroscopy

The chemical compositions of unmodified PP, PP-g-PAA, and PP-g-P(ST-co-AA) sheets were analyzed using an attenuated total reflectance Fourier transform infrared spectrometer (ATR-FTIR, Spectrum Two, Perkin Elmer) equipped with a diamond head for 16 scans in the range between 4000 and 650 cm^{-1} .

Scanning electron microscopy (SEM) and energy-dispersive X-ray spectroscopy (EDX)

A field emission scanning electron microscopy (FESEM, JSM-7610F Plus, JEOL, Japan) was used to observe the surface morphology of the unmodified PP, PP-g-PAA, and PP-g-P(ST-co-AA) sheets previously dried in an oven at 80 °C for 30 min. All specimens were firstly mounted onto stubs and then coated with gold plasma before observation. The SEM morphology of gold-coated samples was later taken at various magnifications. Besides, energy-dispersive X-ray spectroscopic (EDX) technique was also performed. The acquisition time was set to 196.6 s.

Atomic force microscopy (AFM)

The AFM morphology of all the specimens (unmodified PP, PP-g-PAA and PP-g-P(ST-co-AA) sheets) was taken by Park XE100 instrument (Parks Systems, South Korea). Scanning was carried out in tapping mode and collected with a unique XY (30 μm) axis at a scan rate of 2 – 4 lines/s in ambient conditions. The tested

specimens were mounted onto a double-sided tape on magnetic AFM sample stubs before observation.

Contact angle measurement

The unmodified PP, PP-*g*-PAA, and PP-*g*-P(ST-*co*-AA) sheets were cut into $\sim 1.0 \times 4.0 \times 0.1$ cm³ dimension. The contact angle of deionized water as a test liquid on the samples was also analyzed at room temperature using a goniometer equipped with a system of drop shape analysis (DM-CE2, Kyowa, Japan). The contact angle values of all samples with maximum values of five measurements were averaged and reported.

Ion exchange capacity

Ion exchange capacity (IEC) of the grafted PP sheets is defined as the number of exchangeable ions per dry weight of the sample (meq/g). Titration method was used, in this work, to determine the IEC of the surface of modified PP sheets, adopting from El-Arnaouty et al. [22] and Jiang and Ladewing [23]. All the grafted PP sheets (in H⁺ form) were immersed in 3 M NaCl solution for 24 h to convert H⁺ into Na⁺ forms. During the conversion process, the H⁺ ions were released into the solution. The grafted PP sample was then removed from the solution and completely washed with DI water. Then, the released solution was titrated with 0.01 M NaOH using phenolphthalein as an indicator. The IEC value of the grafted PP samples was determined by using Eq. (2).

$$ICE (meq/g) = \frac{CV}{w_{dry}} \quad (2)$$

where C and V are the concentration and consumed volume of NaOH solution, respectively, and w_{dry} is the dry weight of the grafted PP sample in the H⁺ forms.

Hardness analysis

The hardness of the unmodified PP, PP-*g*-PAA, and PP-*g*-P(ST-*co*-AA) sheets were measured using Shore durometer (Durometer GS-706G, Teclock, Japan). The hardness test was conducted on specimens according to ASTM D2240 standards, each reading was 6 mm in between each point. The maximum hardness values of 5 measurements were averaged and reported.

Impact strength

The impact strength of the unmodified PP, PP-*g*-PAA, and PP-*g*-P(ST-*co*-AA) sheets were measured using Izod Impact Tester (GT 7045 Impact tester, GOTECH, Taiwan). The impact test was conducted on specimens according to ASTM D 256 standard. Dimension of Izod type impact test specimen was $64 \times 12.7 \times 3.2$ mm. Notching was made on the impact specimens in v-notch with an angle of 60° and

a width of 0.25 mm. At least five replicates of each specimen were made for the impact test and the average values were reported.

Evaluation of latex coagulation

The possible application of the grafted PP sheets as an automatically latex-coagulating container was evaluated from the efficiency of the field NRL coagulation. The coagulum content or sieve residue was chosen as coagulation of latex in this research adapting from the ISO 706. The unmodified PP, PP-g-PAA4, and PP-g-P(ST-co-AA)25 sheets ($64 \times 12.7 \times 3.2$ mm³) were immersed in the field NRL (100 g) with impurity filtered and without alkaline preservation for 1–3 h to evaluate their coagulation efficiency. At time interval of 30 min, the coagulated NRL (including coagulum, rubberized-trapped on PP sheets, stable latex) was filtered by a sieve or stainless-steel wire cloth with an average aperture width of 180 ± 10 μ m to obtain the residue coagulum on sieve (larger coagulum was also taken from the surface of PP sheets to combine with the residue coagulum on sieve). The obtained coagulum was then compressed between two-steel rolls where the excess of serum was squeezed out and dried at 100 ± 5 °C until the weight was constant. The coagulum content was then calculated by using Eq. (3).

$$\text{Coagulum content (\%)} = \frac{w_2 - w_1}{w_o} \times 100 \quad (3)$$

where w_o is the weight of dry rubber in the field NRL before coagulation testing, w_1 is the weight of test sieve or stainless-steel wire cloth, and w_2 is the dry weight of dried residue (coagulum) and sieve.

Results and discussion

Preparation of PP-g-PAA and PP-g-P(ST-co-AA) sheets

The main purpose of this study was to fabricate the PP sheets with the released ability of H⁺ or positively charged ions for an automatically latex-coagulating application. To reach the goal, the AA monomer was carefully chosen to graft on the surface of PP for delivering the H⁺ ions from its carboxylic groups (–COOH). Firstly, the reaction conditions of grafting polymerization; time of surface activation (forming the radical species on the PP surfaces), grafting time, BPO, and AA monomer concentrations were thus optimized, as shown in Fig. 1, to gain the best grafting percentage of AA onto the PP sheet. It can be seen that the grafting percentages of AA on the PP sheet are increased with increasing time of surface activation (see Fig. 1A) and BPO concentration (see Fig. 1B), yielding a maximum value at 2 h and 25 wt% of PP, respectively. This could be due to the increase in active sites on the PP surface with increasing the time of surface activation and BPO concentration. In other words, the higher active sites result in the higher free radicals on the PP surface, subsequently accelerating the grafting reaction.





Fig. 1 The effect of (A) time of surface activation, (B) BPO concentration, (C) grafting time, and (D) AA concentration on the grafting percentage of AA on the PP surface

However, when the time of surface activation and BPO concentration were higher than 2 h and 25 wt% of PP, respectively, the grafting percentage was slightly decreased. This may be due to the fact that when density of active sites on the PP surface was too high, the PP surface was bombarded and etched violently [24], resulting in the weight loss and the decrease of grafting percentage of AA onto the PP sheets. The effect of grafting/reaction time and AA concentration on the grafting percentage of AA onto the PP surface is also presented in Fig. 1C and D, respectively. It is obviously seen that the grafting percentage is initially increased and tends to remain steady with increasing the grafting time and AA concentration. The grafting percentage trends to linearly increase in the first 1–5 h of reaction time and reaches the maximum grafting percentage of 5.43% at 7 h of reaction time. In the first 5 h of reaction time, the AA monomers could fully contact in the rapid chain-growth reaction of PAA. After 5 h of reaction time, the active sites on the PP surface could be decreased, resulting in the reduction of grafting reaction and the termination of chain growth reaction (Fig. 1C). However, when AA concentration was higher than 250 wt% (Fig. 1D), the grafting percentage is somewhat decreased due to the physical absorption of AA monomers onto the grafted PP surfaces and the PAA formation on the PP surface [12]. In

summary, the optimum conditions to obtain the highest grafting percentage of AA monomer onto the PP surface without ST monomer (5.43%) were found to be as follows; time of surface activation = 2 h, BPO content = 25 wt% of PP, grafting reaction time = 7 h and AA concentration = 250 wt%, at a fixed temperature of 95 °C. However, these optimized conditions still provided the very low grafting percentage of AA monomer onto the PP surface which could not practically apply for an automatically latex-coagulating method in the cup lump production. In order to promote the grafting percentage of AA onto the PP surface, the graft copolymerization technique of AA and ST monomers onto the PP surface has been chosen and applied by variation of AA/ST ratios (total weight = 250 wt% of PP). The various ratios of AA/ST at 100/0, 90/10, 80/20, 70/30, 60/40, and 50/50 wt% were carried out using the optimized conditions listed in Table 1. Figure 2 shows the effect of AA/ST ratios on the grafting percentage of AA/ST onto PP surfaces. It is apparent that the grafting percentage of AA on the PP surface are sharply increased with the presence of ST monomer compared to the absence one (PP-g-PAA; AA/ST = 100/0). The grafting percentages of AA onto the PP surfaces are slightly increased with increasing AA/ST ratio of 90/10 wt% and increased sharply to the maximum value of 25.91% at the AA/ST ratio of 80/20 wt%, after that they are slightly decreased. Therefore, the optimum AA/ST ratio for obtaining the highest grafting percentage of AA onto the PP sheet was 80/20 wt%. The highest grafting percentage of PP-g-P(ST-co-AA) (25.91%) is found to be about 377% higher than that of the PP-g-PAA sample without ST (5.43%). This could be due to the more miscibility and wettability between reactive grafting ST molecules and the PP substrates [18], resulting in the higher reactivity of grafting reactions and the higher grafting percentages. Besides, it is found that solubility parameter of ST monomer ($9.1 \text{ (cal/cm}^3)^{1/2}$) is almost similar to that of PP ($8.08 \text{ (cal/cm}^3)^{1/2}$) and toluene ($8.9 \text{ (cal/cm}^3)^{1/2}$) [25, 26]. Consequently, the ST monomer could interact strongly with the PP surface and react effectively with the active sites on the PP surfaces. In contrast, the grafting percentage of AA onto the PP surface without ST monomer is significantly deteriorated because the solubility parameter of AA monomer ($14.04 \text{ (cal/cm}^3)^{1/2}$) is much different

Fig. 2 The effect of AA/ST weight ratios (total weight = 250 wt% of PP) on the grafting percentage of AA/ST onto the PP surface



from that of the PP substrates ($8.08 \text{ (cal/cm}^3)^{1/2}$) [25]. Moreover, AA monomer has lesser reactivity with PP, compared to the ST monomer [27]. Similar behavior was also observed in the deproteinized NR grafted with maleic anhydride (MA) using ST monomer as an assistant monomer in the graft copolymerization. It was reported that the strong improvement of grafting percentage of MA onto the PP was because the ST molecules acted as an electron donor to activate the $\text{C}=\text{C}$ bonds of MA molecules by generating a charge transfer complex between them, leading to highly activates the weakly reactive double bonds of MA toward the rubber macroradicals [28]. However, it is found that when the AA/ST ratios are lower or higher than 80/20 wt%, their AA grafting percentages are significantly lower than at the optimum ratio. At the lower ST content (10 wt%), the free radicals on the surface of PP surface were fully contacted with ST monomers, resulting in the rapidly chain-growth reactions of ST and AA monomers. While, at the higher ST content (30–50 wt%), the active sites on the PP surface were decreased and the chain-growth reaction was thus gradually slowed down [24]. Moreover, with the richer phase of ST monomers, polystyrene formed by the ST self-polymerization and the previous P(ST-co-AA) grafted onto the PP surface could prevent the diffusion of ST and AA molecules onto the PP surfaces, resulting in a significant lower grafting reaction and eventually low grafting percentage [29, 30].

FTIR analysis and possible mechanism of PP-g-PAA and PP-g-P(ST-co-AA)

The chemical structures of PP-g-PAA and PP-g-P(ST-co-AA) samples washed with acetone and xylene were examined by FTIR technique as shown in Fig. 3.





Fig. 3 ATR-FTIR spectra of unmodified PP, PP-g-PAA, and PP-g-P(ST-co-AA) samples

The PP-g-PAA with grafting percentage of 2.86% and 4.49% and PP-g-P(ST-co-AA) with grafting percentage of 4.77% and 25.91% were labeled as PP-g-PAA2, PP-g-PAA4, and PP-g-P(ST-co-AA)4, PP-g-P(ST-co-AA)25, respectively, as representative samples. For the unmodified PP sheet, it exhibits the characteristic absorption bands of -CH stretching vibration at $3000\text{--}2850\text{ cm}^{-1}$, -CH_3 bending vibration at 1458 and 1375 cm^{-1} and -CH_2 bending vibration at 1465 cm^{-1} . For PP-g-PAA, the presence of absorption bands at 1559 and $1406\text{--}1410\text{ cm}^{-1}$ is attributed to the stretching vibrations of carboxylate groups (-COOH) in the AA fractions. In addition, three new peaks appeared at $3000\text{--}3600$, 1727 and 1167 cm^{-1} are ascribed to the stretching vibrations of -OH , C=O and C-O of carboxylic groups, respectively [31]. For the FTIR spectra of PP-g-P(ST-co-AA) sheets, the characteristic bands of CH stretching (3028 cm^{-1}) and C=C out of plane bending (754 and 698 cm^{-1}) of aromatics in the styrene structure are clearly observed [32]. Moreover, the carboxylic groups of AA monomers exhibit OH stretching vibration at $3000\text{--}3600\text{ cm}^{-1}$, C=O stretching at 1727 cm^{-1} and C-O stretching at 1167 cm^{-1} . Certainly, the intensity of OH, C=O and C-O peaks are found to strongly increase with increasing grafting percentage values of the PP-g-P(ST-co-AA) samples. Besides, the peak at around 704 cm^{-1} is assigned to out-of-plane deformation of the benzene rings of ST molecules. Subsequently, these evidences could confirm that the P(ST-co-AA) copolymers were fruitfully grafted onto the PP surfaces, producing the successful PP-g-P(ST-co-AA) samples. As previous described, the surface modification of PP grafted with AA and ST monomers was carried out through the chemical free radical reactions in toluene solution using BPO initiator. The possible mechanism of grafting reaction of the PP-g-P(ST-co-AA) is graphically presented in Scheme 1. Firstly, the BPO initiator is decomposed by thermal heating at $95\text{ }^\circ\text{C}$ [31] to generate two macroradicals which then interacts with hydrogen atoms (H) on the PP molecular chains to deliver the free radicals (-C) on the PP surface (see Scheme 1A). Then, these free radicals will react with the AA monomers resulting in the polymerization of AA monomers to form the PP-g-PAA (see Scheme 1B). In the presence of ST monomers having more reactivity, and more miscibility and wettability with PP than the AA monomers, hence in the first stage, the C radicals on the PP surface could firstly reacted with the ST monomers to polymerize with ST monomers to produce PP-g-PST with radicals at the ends. In the second stage, the PP-g-PST sections could further react with the AA monomers to produce the PP-g-P(ST-co-AA) (see Scheme 1C).

Surface morphology of PP-g-PAA and PP-g-P(ST-co-AA)

Morphology, elemental quality and quantity, and topography of the unmodified PP and grafted PP sheets were performed by scanning electron microscopy (SEM), energy-dispersive X-ray spectroscopy (EDX), and atomic force microscopy (AFM) as revealed in Fig. 4. It is seen that the surface of unmodified PP sheet (Fig. 4A) is rather smooth with no wrinkles on the surface totally differing from the grafted PP sheets. While, the surface of grafted PP sheet is heterogeneous and non-uniform surface due to the considerable deposition of AA and ST monomers onto the PP



Scheme 1 The possible mechanism of PP grafted with PAA and P(ST-co-AA); (A) surface acting step, (B) PP-g-PAA, and (C) PP-g-P(ST-co-AA)

surfaces [13, 33]. The AFM analysis is usually employed to observe the surface morphology and the average surface roughness (R_a) of polymer after the grafting process. The topographical surface morphologies of the unmodified PP and all the




Fig. 4 SEM (left), AFM (middle), and EDX spectra (right) of (A) unmodified PP, (B) PP-g-PAA2, (C) PP-g-PAA4, (D) PP-g-P(ST-co-AA)4, and (E) PP-g-P(ST-co-AA)25 sheets

grafted PP sheets were therefore investigated by AFM as displayed in Fig. 4 (middle column). It is found that the surface roughness of unmodified PP ($R_a=0.22\text{ }\mu\text{m}$) is smoother than that of all the grafted PP ($R_a=0.63\text{--}0.76\text{ }\mu\text{m}$). In addition, the grafting percentage of both the PP-*g*-PAA and PP-*g*-P(ST-*co*-AA) samples are increased with increasing the surface roughness of the grafted PP samples. The surface roughness of PP is mostly related to the sites of graft initiation, frequently taking place in the amorphous regions rather than in the crystalline sections [33]. Furthermore, it is seen that the surfaces of all the grafted PP samples exhibit hill-valley structures with significant heterogeneity. However, it is also observed that the increase in grafting percentage may response to the increase in the flattening surface of the PP surface, possibly resulting from the incorporation and/or agglomeration of the P(ST-*co*-AA) polymer chains within the valleys (see Fig. 4D). Obviously, it is seen from Fig. 4D and E (left and middle column, respectively) that the R_a is significantly decreased from $0.72\text{ }\mu\text{m}$ to $0.33\text{ }\mu\text{m}$ when the grafting percentage is increased from 4.77% to 25.91%, respectively. In this case, the smoother surface of PP-*g*-P(ST-*co*-AA) Samples at the higher grafting levels could be due to the higher extent of homogenization [14, 34]. Similar trends of the morphological arrangement were also observed in the chitosan immobilization on the PP-*g*-PAA monofilament surfaces [14] and the glassy and rubbery polymer brush layers [34]. Therefore, from these results, it could be concluded that the P(ST-*co*-AA) fractions were successfully grafted on the PP surface. In order to confirm the existence of PAA on the grafted PP samples, EDX analysis was also performed in this work to detect the oxygen (O) atoms derived from the carboxylate groups (Fig. 4 (right column)). It is found that the O atoms amount on the unmodified PP surface is detected to be very low just 0.69 wt%, resulting from some oxidation reactions took place on the surface of PP sheet during the processing at high temperature [32]. After the grafting process, the O atom amounts on all the grafted PP surfaces are found to be strongly increased when compared to that of the unmodified PP sample. For the PP-*g*-PAA samples, the O atom fractions increase from 3.80 wt% to 6.19 wt% with increasing the grafting percentage from 2.86% to 4.49%, respectively. Fascinatingly, for the PP-*g*-P(ST-*co*-AA) samples, the fractions of O atom are reported to be 7.14 wt% and 21.37 wt% when the grafting percentages are increased from 4.77% to 25.91%, respectively, which are about 1.67 – 5.43 times higher than those of the PP-*g*-PAA samples. These results are in good agreement with the SEM, AFM, and FTIR results. Therefore, the remarkable improvement of grafting percentage of PAA on the PP surface can be successfully obtained by using the styrene-assisted grafting reaction pathway which was already reported by many researches [35–37].

Contact angle of PP-*g*-PAA and PP-*g*-P(ST-*co*-AA) sheets

Fundamentally, the contact angle is very sensitive to the chemical and structural changes occurred on the polymer surfaces because the liquid contacts outermost molecular layer of the surface [36]. In order to investigate the structural change of the unmodified PP and grafted PP surfaces, the contact angle measurement was also thus performed. The values of water contact angle on the sample sheets with different




Fig. 5 (A) Contact angle, IEC and impact strength of the unmodified PP, PP-g-PAA, and PP-g-P(ST-co-AA) sheets and (B) the relationship of grafting percentage and ICE versus the O contents of the grafted PP sheets

grafting percentages are illustrated in Fig. 5A (black line). It is seen that the value of water contact angle on the unmodified PP sheet (101.7°) is the largest value compared to all values of the grafted PP sheets ($88.2\text{--}97.7^\circ$). Besides, it is observed that the contact angle values tend to decrease with increasing the grafting percentage of AA onto the PP surfaces. The lowest value of contact angle (88.2°) is exhibited by the PP-g-P(ST-co-AA)25 sample containing the AA grafting percentage of 25.91%. This result indicates that surfaces of the grafted PP sheets have more significant polarity compared to the unmodified PP sheet due to the presence of more carboxylate groups of PAA on their surfaces. Similar behavior was also observed in the PAA grafted on the PP surface films by a radical photo-grafting polymerization [16, 38]. For example, Fasce et al. [16] reported that the values of liquid contact angle of the surface of PP-g-PAA were decreased from $79.7 \pm 1.1^\circ$ (the unmodified PP) to $18.6 \pm 3.5^\circ$ (the grafted PP). Li et al. [38] also studied the adaptation and kinetics of random copolymerization composed of ST and AA monomers and reported that the receding contact angle was decreased with increasing the AA content. In conclusion, the growth of polar components could mainly contribute to the improved affinity of the grafting surfaces, directly resulting in the decrease of contact angle values and the increase of grafting percentages of AA onto the PP surfaces.

Ion exchange capacity (IEC) of the unmodified PP and grafted PP sheets

Fundamentally, ion exchange capacity (IEC) informs us about the ion exchangeable groups presenting in a polymer matrix. The ICE values are accountable for the conduction of protons and therefore it is an indirect and reliable estimation of the proton conductivity [22, 23, 39]. The IEC values of all the grafted PP sheets are plotted in Fig. 5A (red line). It is seen that the IEC values of the grafted PP samples tend to increase with increasing the grafting percentages as shown in Fig. 5B. The IEC values of the PP-g-PAA samples are increased from 5.32×10^{-5} to 8.87×10^{-5} meq/g when the grafting percentages are increased from 2.28% to 4.77%, respectively.

Similar behavior is also observed in the PP-g-P(ST-co-AA) sheets. The IEC values of the PP-g-P(ST-co-AA)4 and PP-g-P(ST-co-AA)25 samples are found to be 9.4×10^{-5} and 43.1×10^{-5} meq/g, respectively. The increment of ICE values is in good agreement with the amount of oxygen atoms in the grafted PP sheets (see Fig. 4 (right column) and Fig. 5B), especially in the PP-g-P(ST-co-AA)25 sample. Hence, the relation between grafting percentage values, ICE values, and O contents of all the grafted PP sheets is plotted as shown in Fig. 5B. As expectedly, it is found that the increase in oxygen (O) contents results in the similar behavior of both the grafting percentages of AA onto the PP surfaces and the ICE values of the grafted PP specimen. In other words, the grafting percentages and the ICE values are correlated very well with increasing O contents on the grafted PP sheets, confirming the successful grafting reaction of AA monomers onto the PP surfaces.

Mechanical properties of the unmodified PP and grafted PP sheets

In general, the surface modification of PP sheets via grafting copolymerization may also cause some degradations of the polymer chains. Hence, the attention needs to be taken to ensure that the mechanical properties of the PP-g-PAA and PP-g-P(ST-co-AA) samples did not suffer from the treatment. The impact strength and hardness as basic properties of the unmodified PP and grafted PP samples are measured and presented in Fig. 5A (blue line). It is seen that the impact strength of the grafted PP sheets is slightly increased with increasing grafting percentages up to 4% and then slightly decreased. The slight increase in impact strength could be due to the formation of physical crosslinking of the grafted polymer chains and the intermolecular hydrogen bonding interactions between the grafted PAA chains [31]. However, it is found that the grafting copolymerization and the grafting percentages of AA onto the PP surface sheets did not affect significantly on the hardness properties of all PP sheets because the thickness of PAA grafted films attached onto the PP surface is very thin. As a result, the hardness values were determined to be 69.9 ± 0.4 , 71.3 ± 0.3 , 70.1 ± 0.1 , 70.6 ± 0.4 and 67.9 ± 1.8 Shore D for the unmodified PP, PP-g-PAA2, PP-g-PAA4, PP-g-P(ST-co-AA)4, and PP-g-P(ST-co-AA)25 sample, respectively.

Evaluation of latex coagulation

To explore the efficiency of the grafted PP sheets as an automatically latex-coagulating materials, the field NRL sample was immersed by the grafted PP sheets for 3 h to investigate the coagulum content (%). The unmodified PP, PP-g-PAA4 and PP-g-P(ST-co-AA)25 sheets were used as representative samples. The efficiency of




Fig. 6 The coagulum content (%) of the unmodified PP, PP-g-PAA4, and PP-g-P(ST-co-AA)25 sheets as a function of immersing time (h) (dashed lines define the rate of NRL coagulum)





Fig. 7 Latex coagulation of (A) unmodified PP, (B) PP-g-PAA4, and (C) PP-g-P(ST-co-AA)25 sheet at different soaking times (h)

coagulation was reported as the obtained coagulum content (%) which is calculated using Eq. (3). The calculated results are presented in Fig. 6. Evidently, it is seen that the field NRL immersed with the unmodified PP sheet was stable in the latex state (see Fig. 7). Interestingly, the coagulum contents of the PP-g-PAA4 and PP-g-P(ST-co-AA)25 sheets at 3 h were significantly higher than that of the unmodified PP sheet. As can be seen from Fig. 6, at the immersion time of 1.0–1.5 h, the rates of coagulum content of the PP-g-PAA4 and PP-g-P(ST-co-AA)25 samples are steadily increased with immersion time. However, the coagulum content of the PP-g-P(ST-co-AA)25 sheet is significantly higher than that of the PP-g-PAA4 sheet. The average coagulation rate of NRL over time was evaluated by dividing the change in coagulum content or concentration by the time interval used. The instantaneous rate ($d[\text{coagulum}]/dt$) of coagulation can thus be obtained from the slope of the plot of coagulation content (%) versus time (t) as presented in Fig. 6. It is obviously seen that the coagulation behavior of the NRL influenced by the grafted PP sheets

contains three stages; initial (0–1.5 h), growth (1.5–2.5 h), and equilibrium stages (> 2.5 h). The calculated NRL coagulation rates of the unmodified PP, PP-g-PAA4, and PP-g-P(ST-co-AA)25 samples, at the initial stage, are found to be 0.58, 4.12, and 15.38%/h, respectively. While at the growth stage, the coagulum contents of the PP-g-P(ST-co-AA)25 and PP-g-PAA4 sheets are sharply increased from 24.42% to 93.8% and from 6.77% to 48.46%, respectively. The coagulation rates of NRL immersed with the unmodified PP, PP-g-PAA4, and PP-g-P(ST-co-AA)25 sheets are about 1.52, 41.69 and 63.48%/h, respectively. The significant increase in the NRL coagulation rate (63.48%/h) caused by the PP-g-P(ST-co-AA)25 could mainly be due to the incorporation of ST comonomer, facilitating the remarkable grafting percentage of the PAA fractions onto the PP surface sheet. The photographs of coagulation of the NRL immersed with the unmodified PP, PP-g-PAA4, and PP-g-P(ST-co-AA)25 sheets are presented in Fig. 7. It is seen that the NRL coagulum was trapped on the surface of PP sheets. The NRL coagulum were firstly trapped by the unmodified PP, PP-g-PAA4, and PP-g-P(ST-co-AA)25 sheets at 3, 2, and 1 h, respectively. The coagulum size was increased from the beginning of the first-trapped NRL and continuously improved with increasing the immersion time. This result indicates that the hydrogen ions (H^+) located on the grafted PP surfaces could neutralize and coagulate the rubber particles as proposed by the possible mechanism of coagulum process (see Fig. 9). Furthermore, the coagulum contents of PP-g-P(ST-co-AA)25 sheet are significantly higher than that of the PP-g-PAA4 and unmodified PP sheets. This is because the positively charged ions generated from the PAA grafted on the PP surface cause the instability and coagulation of the NRL particles. Thus, from this result, it could summarize that the PP surface grafted with positively charged ions or proton donors is a promising candidate to produce an automatically latex-coagulating container. The effect of coagulating cycles on the coagulum content (%) of the PP-g-P(ST-co-AA)25 sheet was also investigated as shown in Fig. 8. The result demonstrates that the coagulum content of NRL decreases drastically with increasing the coagulating cycle. The coagulum contents in the 1st, 2nd, 3rd, and 4th cycles are found to be 93.8%, 45.0%, 23.7%, and 11.4%, respectively. The significant

Fig. 8 The effect of coagulating cycles on the coagulum content (%) of PP-g-P(ST-co-AA)25 sample at 3 h






Fig. 9 Possible graphical mechanism of latex coagulation of the PP-*g*-PAA and PP-*g*-P(ST-*co*-AA) sheets

decrease in coagulum content with increasing the coagulating cycles could result from the reduction of the amount of H^+ ions which were used each coagulating cycle. Therefore, the PP-*g*-P(ST-*co*-AA) sheet developed in this research could be potentially applied for cup lump production, reducing an inappropriate coagulant used and being environmentally friendly. Furthermore, our result could provide the useful information for the further development of an automatically latex-coagulating PP container to have more coagulating cycles which can be eventually produced as a commercial product in the near future.

Possible mechanism of latex coagulation by the grafted PP sheets

The possible mechanism of latex coagulation by the grafted PP sheet is schematically illustrated in Fig. 9. In the NRL state, each rubber particle is made up of rubber polymers covered by negative charges of protein membrane layers [40]. The negatively charged rubber particles repel each other, preventing themselves from

the combination and coagulation (see Fig. 9A). When the NRL is collected in the grafted PP container, the hydrogen ions (H^+) as positive charges from the carboxylic groups on the surface of grafted PP sheet will neutralize the negative charges of rubber particles and thus neutral rubber particles is then generated (see Fig. 9B). In addition, when these neutral particles collide with each other, their outer membrane layers will be broken up (see Fig. 9C). The rubber polymers are then set free and start to be coagulated by combining each rubber particles together to form a larger lump of rubber polymer which is subsequently precipitated from the latex solution (see Fig. 9D and E).

Comparison of percentage grafting values of AA onto PP and other substrates

In order to compare the grafting percentage value of AA onto the PP sheets and other substrates, the grafting efficiency (%), grafting methods, and potential applications are listed in Table 2. It is found that the grafting percentage of our grafted PP-g-P(ST-co-AA)25 sheet (25.91%) was in gradual range compared to that of other samples attained by other grafting methods. The grafting efficiency of AA onto the different substrates is varied from the low to very high measurement values. However, according to the potential applications listed in Table 2, there is no work reporting that their modified samples have been applied as an automatically latex-coagulating application. Interestingly, even the grafting percentage of our PP-g-P(ST-co-AA)25 sample was in just 25.91% but it exhibited the satisfactory coagulum content of 93.8% in the first cycle. However, the PP-g-P(ST-co-AA) sheet is further needed to improve their grafting percentage and their coagulating cycles for the large-scale production and commercial products on the future.

Conclusion

The automatically latex-coagulating PP sheet was successfully fabricated by surface-grafting modification using various AA/ST monomer ratios. Grafting percentage, contact angle, and ion exchange capacity (IEC) of grafted PP sheet increased with increasing the ST-assisted grafting and AA concentration. The possible mechanism of an automatically latex-coagulating PP sheet was proposed by the fact that the negative charges on the surface of rubber particle membranes was neutralized by H^+ ions released from the PP-g-P(ST-co-AA) surfaces. The latex coagulation performance of PP-g-P(ST-co-AA)25 (93.8%) and PP-g-PAA4 (48.46%) at 3 h (equilibrium) was significantly higher than the unmodified PP sheet (5.43%), corresponding well to the coagulation rates of 63.48, 41.69, and 1.52%/h, respectively. Our results demonstrated that the PP-g-P(ST-co-AA) sheet could be used as an automatically latex-coagulating container for cup lump production, with the benefit of reducing the inappropriate coagulant acid and the environmental impact but also increase in the added value of cup lump product.

Table 2 Degree of grafting of AA onto the different substrates using several methods and their potential applications

Sample	Grafting method	Degree of Grafting	Application	Ref.
Grafted PAA/FTO ^a	Plasma-initiated graft polymerization	84 $\mu\text{g}/\text{cm}^2$	Water-oxidation catalysts	[41]
PAA-PA ^b membrane	UV-initiated graft polymerization	120 $\mu\text{g}/\text{cm}^2$	Pervaporation membrane	[42]
PAA-g-PPM ^c	Ultrasonic-assisted graft polymerization	0.82 mg/cm ²	Membrane	[43]
AA-g-fiber. ^d	Radiation-induced graft polymerization	190%	Pharmaceutical	[44]
AA-grafted fiber. ^e	Electron beam polymerization	1.63%		[45]
PAA-g-PCL ^f	Plasma-induced	18 $\mu\text{g}/\text{cm}^2$	Human healthcare	[46]
PAA-g-PET TeMS ^g	Photoinduced graft polymerization	112 nmol/cm ²	Track-etched membrane	[47]
AA-g-PEEK ^h	UV-induced graft polymerization	3.5 mg/cm ²	Knee arthroplasty	[48]
PP-g-P(ST-co-AA)	Free-radical polymerization	25.91%	An automatically latex-coagulating cup	This work

Acknowledgements This work was financial supported by Faculty of Science, Ubon Ratchathani University. The center of excellent for innovation in chemistry (PERCH-CIC), Ministry of Higher Education, Science, Research, and Innovation are also acknowledged for some partial supports.

Declarations

Conflict of interest The authors declare that they have no conflict of interest or personal relationships that could have appeared to influence the work reported in this paper.

References

- Suchat S, Theanjumol P, Karrila S (2015) Rapid moisture determination for cup lump natural rubber by near infrared spectroscopy. *Ind Crops Prod* 76:772–780
- Narongwongwattana S, Rittiron R (2015) The rapid determination of volatile fatty acid number in para rubber latex using fourier transform-near infrared spectroscopy based on quantification and discrimination model. *J Innov Opt Heal Sci* 8(5):1550042
- Pamornnak B, Pipitsunthornsan P, Somwong S et al (2020) A microwave reflectometer technique for classifying a rubber cup lump. *Comput Electron Agric* 168:105152
- Santipanusopon S, Riyajan S (2009) Effect of field natural rubber latex with different ammonia contents and storage period on physical properties of latex concentrate, stability of skim latex and dipped film. *Phys Procedia* 2:127–134
- Bei-long Z, Hong-hai H, Yong-zhou W et al (2016) Effect of maturation time of coagulum of fresh natural rubber latex on oxidation kinetics of natural rubber. *Adv Comput Sci Res* 71:1244–1250
- Nepacina MRJ, Foronda JRF, Haygood KJF et al (2019) Differentiation of rubber cup coagulum through machine learning. *Sci Agric Bohem* 50(1):51–55
- Nguyen NH, Luong TT (2012) Situation of wastewater treatment of natural rubber latex processing in the Southeastern region Vietnam. *J Viet Env* 2(2):58–64
- Liang F, Yuan H, Shao Q et al (2018) Study of suspension grafting process of polypropylene. *Des Monomers Polym* 21(1):130–136
- Dogu   LJ, Mermilliod N, Gandini A (1995) Modification of industrial polypropylene film by grafting of poly(acrylic acid). *J Appl Polym Sci* 56:33–40
- Smitha B, Sridhar S, Khan AA (2004) Polyelectrolyte complexes of chitosan and poly(acrylic acid) as proton exchange membranes for fuel cells. *Macromolecules* 37:2233–2239
- Butruk-Raszeja BA, Trzaskowska PA, Ku  minska A et al (2016) Polyurethane modification with acrylic acid by Ce(IV)-initiated graft polymerization. *Open Chem* 14:206–214
- Abdolahifard M, Bahrami SH, Malek RMA (2011) Surface modification of PET fabric by graft copolymerization with acrylic acid and its antibacterial properties. *ISRN Org Chem*. <https://doi.org/10.5402/2011/265415>
- Mandal DK, Bhunia H, Bajpai PK et al (2017) Optimization of acrylic acid grafting onto polypropylene using response surface methodology and its biodegradability. *Radiat Phys Chem* 132:71–81
- Saxena S, Ray AR, Gupta B (2010) Chitosan immobilization on polyacrylic acid grafted polypropylene monofilament. *Carbohydr Polym* 82:1315–1322
- Yu Z, Lua L, Lua L et al (2020) Multilayers assembly of bio-polyelectrolytes onto surface modified polypropylene films: Characterization, chelating and antioxidant activity. *Carbohydr Polym* 245:116456
- Fasce LA, Costamagna V, Pettarin V et al (2008) Poly(acrylic acid) surface grafted polypropylene films: Near surface and bulk mechanical response. *EXPRESS Polym Lett* 2(11):779–790
- Du J, Wang Y, Xie X et al (2017) Styrene-assisted maleic anhydride grafted poly(lactic acid) as an effective compatibilizer for wood flour/poly(lactic acid) bio-composites. *Polym* 9(11):623
- Phadnis S, Patri M, Hande VR et al (2003) Proton exchange membranes by grafting of styrene–acrylic acid onto FEP by preirradiation technique. I. Effect of synthesis conditions. *J Appl Polym Sci* 90:2572–2577
- Benavides R, Urbano R, Morales-Acosta D et al (2019) Effect of gamma radiation on crosslinking, water uptake and ion exchange on polystyrene-co-acrylic acid copolymers useful for fuel cells. *Int J Hydrogen Energ* 44(24):12525–12528

20. Melo L, Benavides R, Martínez G et al (2017) Sulfonated polystyrene-co-acrylic acid membranes modified by transmembrane reduction of platinum. *Int J Hydrogen Energ* 42(51):30407–30416
21. Wang W, Wang L, Chen X et al (2006) Study on the graft reaction of poly(propylene) fiber with acrylic acid. *Macromol Mater Eng* 291:173–180
22. El-Arnaouty MB, Abdel Ghaffar AM, Eid M (2013) Properties of grafted polymer metal complexes as ion exchangers and its electrical conductivity. *Polym Eng Sci* 53(4):792–799
23. Jiang S, Ladewig BP (2017) High ion-exchange capacity semihomogeneous cation exchange membranes prepared via a novel polymerization and sulfonation approach in porous polypropylene. *ACS Appl Mater Interfaces* 9:38612–38620
24. Luo Z, Chen H, Xu J et al (2018) Surface grafting of styrene on polypropylene fibers by argon plasma and its adsorption-regeneration of BTX. *J Appl Polym Sci* 135(17):46171
25. Belmares M, Blanco M, Goddard WA III et al (2004) Hildebrand and Hansen solubility parameters from molecular dynamics with applications to electronic nose polymer sensors. *J Comput Chem* 25(15):1814–1826
26. Hadi AJ, Najmuldeen GF, Yusoh KB (2013) Dissolution/reprecipitation technique for waste polyolefin recycling using new pure and blend organic solvents. *J Polym Eng* 33(5):471–481
27. Chernikova EV, Zaitsev SD, Plutalova AV et al (2018) Control over the reactive reactivities of monomers in RAFT copolymerization of styrene and acrylic acid. *RSC Adv* 20(8):14300–14310
28. Wongthong P, Nakason C, Pan Q et al (2014) Styrene-assisted grafting of maleic anhydride onto deproteinized natural rubber. *Eur Polym J* 59:144
29. Wang D, Wang J, He S et al (2021) Efficient approach to produce functional polypropylene via solvent assisted solid-phase free radical grafting of multi-monomers. *Appl Petrochem Res* 11:99–111
30. El-Sayed Hegazy D (2012) Selectivity of acrylic acid radiation grafted non-woven polypropylene sheets towards some heavy metals ions. *Open J Polym Chem* 2:6–13
31. Abudonia KS, Saad GR, Naguib HF, Eweis M, Zahran D, Elsabee MZ (2018) Surface modification of polypropylene film by grafting with vinyl monomers for the attachment of chitosan. *J Polym Res*. <https://doi.org/10.1007/s10965-018-1517-3>
32. Hassan MIU, Taimur S, Khan IA et al (2018) Surface modification of polypropylene waste by the radiation grafting of styrene and upcycling into a cation-exchange resin. *J Appl Polym Sci* 47145:1–8
33. Mandal DK, Bhunia H, Bajpai PK et al (2016) Radiation-induced grafting of acrylic acid onto polypropylene film and its biodegradability. *Radiat Phys Chem* 123:37–45
34. Julthongpipit D, LeMieux M, Tsukruk VV (2003) Micromechanical properties of glassy and rubbery polymer brush layers as probed by atomic force microscopy. *Polym* 44:4557–4562
35. El-Toony MM, Abdel-Hady EE, El-Kelesh NA (2016) Application of poly (tetrafluoroethylene) grafted with styrene/acrylic acid for proton exchange fuel cell. *Egypt J Chem* 59(5):799–818
36. Flores-Gallardo SG, Sanchez-Valdes S, Ramos De Valle LF (2001) Polypropylene/polypropylene-grafted acrylic acid blends for multilayer films: Preparation and characterization. *J Appl Polym Sci* 79:1497–1505
37. Dong Q, Liu Y (2004) Free-radical grafting of acrylic acid onto isotactic polypropylene using styrene as a comonomer in supercritical carbon dioxide. *J Appl Polym Sci* 92(4):2203–2210
38. Li X, Silge S, Saal A et al (2021) Adaptation of a styrene–acrylic acid copolymer surface to water. *Langmuir* 37(4):1571–1577
39. Lutful Kabir MD, Kim HJ, Choi S (2017) Comparison of several acidified chitosan/Nafion® composite membranes for fuel cell applications. *J Nanosci Nanotechnol* 17:8128–8131
40. Berthelot K, Lecomte S, Estevez Y et al (2014) Rubber particle proteins, HbREF and HbSRPP, show different interactions with model membranes. *Biochim Biophys Acta Biomembr* 1:287–299
41. Badiel YM, Traba C, Rosales R et al (2021) Plasma-initiated graft polymerization of acrylic acid onto fluorine-doped tin oxide as a platform for immobilization of water-oxidation catalysts. *ACS Appl Mater Interfaces* 13:14077–14090
42. Ang MBMY, Huang S, Chang M et al (2020) Ultraviolet-initiated graft polymerization of acrylic acid onto thin-film polyamide surface for improved ethanol dehydration performance of pervaporation membranes. *Sep Purif Technol* 235:116155
43. Chen F, Xie L (2020) Enhanced fouling-resistance performance of polypropylene hollow fiber membrane fabricated by ultrasonic-assisted graft polymerization of acrylic acid. *Appl Surf Sci* 502:144098

44. Matsuzaki Y, Itabashi T, Kawai-Noma S et al (2019) Improvement of protein binding capacity of acrylic-acid-grafted fibers by polymer root-to-brush shift. *Radiat Phys Chem* 158:131–136
45. Xu L, Hu J, Ma H et al (2018) Electron-beam-induced post-grafting polymerization of acrylic acid onto the surface of Kevlar fibers. *Radiat Phys Chem* 145:74–79
46. Gupta B, Krishnanand K, Deopura BL (2012) Oxygen plasma-induced grafted polymerization of acrylic acid on polycaprolactone monofilament. *Eur Polym J* 48:1940–1948
47. Korolkov IV, Mashentseva AA, Güven O, Taltenov AA (2015) UV-induced graft polymerization of acrylic acid in the sub-micronchannels of oxidized PET track-etched membrane. *Nucl Instrum Methods Phys Res Sec B: Beam Inter Mater Atoms* 365:419–423. <https://doi.org/10.1016/j.nimb.2015.07.057>
48. Zhao X, Xiong D, Wang K et al (2017) Improved biotribological properties of PEEK by photo-induced graft polymerization of acrylic acid. *Mater Sci Eng C* 75:777–783

Publisher's Note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.