GREASES · CLAY-THICKENED & NON-MELTING GREASES

BENTONE 2.

A clay-thickened, non-melting grease.

110 cSt	> 285 °C	2	Brown
Viscosity @ 40°C	Dropping point	NLGI grade	Colour

APPLICATION

- Bearings at elevated temperature
- Oven and dryer applications
- Where a soap grease would melt out

NOT RECOMMENDED

- × **Applications requiring an NSF H1 food-grade grease**
- × **Mixing with greases of a different thickener type without purging the bearing first**
- × **Continuous service above the stated upper temperature limit**

BENEFITS

- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable - will not soften and leak in service

TYPICAL PROPERTIES

PROPERTY	UNIT	TYPICAL
Appearance Visual		**Smooth, adhesive grease**
Colour ASTM D1500		**Brown**
Thickener		**Organically modified clay**
NLGI Classification		**2**
Base Oil Viscosity @ 40°C (IP71)	cSt	**110**
Oil Separation (IP121)	%	**2.5**
Dropping Point (IP132)	°C	**> 285**
Four Ball Weld Load (IP 239) kg		**200**
100 Hours @ 99°C Pressure Drop psi		**4.5**
Worked Penetration (IP50)		**265 to 295**
Copper Corrosion (IP112)		**1b**
Operating Temperature Range short periods to +160°C	°C	**-20°C to +140**

Typical values, not a specification.

PACK SIZES

400 g cartridge, 3 kg, 12.5 kg, 50 kg, 180 kg

HEALTH & SAFETY

Refer to SDS for proper handling and disposal. Please note that the SDS includes handling, health and disposal information which should be passed on to your employees, and to anyone else who comes in contact with our product. Additional advice can also be obtained from your local representative.

Note: Read and understand all precautions on container labels before using this product.

SAR Lubricants (Squire A. Radcliffe & Sons Ltd)
Gill Bridge Oil Works, Lowlands Road,
Mirfield, WF14 8LU, England

+44 (0)1924 494371
enquiries@sarlubricants.co.uk
sarlubricants.co.uk

Registered in England
05866783
VAT 889171963