GREASES · CLAY-THICKENED & NON-MELTING GREASES

BENTONE HP.

A clay-thickened, non-melting grease.

460 cSt	>285 °C	2
Viscosity @ 40°C	Dropping point	NLGI grade

APPLICATION

- Hot bearings under shock load
- Heavy plant working at temperature
- Furnace and forge equipment

NOT RECOMMENDED

- × **Applications requiring an NSF H1 food-grade grease**
- × **Mixing with greases of a different thickener type without purging the bearing first**
- × **Continuous service above the stated upper temperature limit**

BENEFITS

- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable - will not soften and leak in service

TYPICAL PROPERTIES

PROPERTY	UNIT	TYPICAL
Appearance Visual		**Smooth, adhesive grease**
Colour ASTM D1500		**Grey/black**
Thickener		**Organically modified clay**
Solid Lubricant Content	%	**3**
NLGI Classification		**2**
Base Oil Viscosity@40°C (IP71) cSt	cSt	**460**
Worked Penetration (IP50)		**265 to 295**
Dropping Point (ASTM D1264)	°C	**>285**
Four Ball Weld Load (IP239) kg		**250**
Operating temperature range	°C	**-10°C to +160°C, occasional peak to 180**

Typical values, not a specification.

PACK SIZES

400 g cartridge; 3 kg; 12.5 kg; 50 kg; 180 kg

HEALTH & SAFETY

Refer to SDS for proper handling and disposal. Please note that the SDS includes handling, health and disposal information which should be passed on to your employees, and to anyone else who comes in contact with our product. Additional advice can also be obtained from your local representative.

Note: Read and understand all precautions on container labels before using this product.

SAR Lubricants (Squire A. Radcliffe & Sons Ltd)
Gill Bridge Oil Works, Lowlands Road,
Mirfield, WF14 8LU, England

+44 (0)1924 494371
enquiries@sarlubricants.co.uk
sarlubricants.co.uk

Registered in England
05866783
VAT 889171963