GREASES · LITHIUM COMPLEX GREASES

LITHIUM COMPLEX EP2.

A lithium complex grease.

150 min cSt	250 min °C	2
Viscosity @ 40°C	Dropping point	NLGI grade

APPLICATION

- Extended lubrication intervals under load
- Hot-running industrial and automotive bearings
- Wheel bearings and hub units
- Where a plain lithium grease is at its temperature limit

NOT RECOMMENDED

- × **Applications requiring an NSF H1 food-grade grease**
- × **Mixing with greases of a different thickener type without purging the bearing first**
- × **Continuous service above the stated upper temperature limit**

BENEFITS

- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable - will not soften and leak in service

HEALTH & SAFETY

Refer to SDS for proper handling and disposal. Please note that the SDS includes handling, health and disposal information which should be passed on to your employees, and to anyone else who comes in contact with our product. Additional advice can also be obtained from your local representative.

Note: Read and understand all precautions on container labels before using this product.

SAR Lubricants (Squire A. Radcliffe & Sons Ltd)
Gill Bridge Oil Works, Lowlands Road,
Mirfield, WF14 8LU, England

+44 (0)1924 494371
enquiries@sarlubricants.co.uk
sarlubricants.co.uk

Registered in England
05866783
VAT 889171963

GREASES · LITHIUM COMPLEX GREASES · CONTINUED

LITHIUM COMPLEX EP2.

TYPICAL PROPERTIES

PROPERTY	UNIT	TYPICAL
Colour & Appearance		**Smooth Adhesive Grease**
Colour ASTM D1500		**Red or Blue**
NLGI Classification		**2**
Thickener		**Lithium Complex**
Base Oil		**Solvent Refined Mineral Oil**
Base Oil Viscosity @ 40°C (IP71)	cSt	**150 min**
Worked Penetration (IP50)		**265 to 295**
Roll Stability (ASTM D1831) 100 hrs		**+30 Points Change In Penetration, max.**
Dropping Point (IP132)	°C	**250 min**
Oil Separation (IP121)	%	**5 max.**
Copper Corrosion (IP112)		**Pass**
EMCOR (IP220)		**0 : 0**
Water Washout (IP215) @ 79°C	%	**3**
Four Ball Weld Load (IP239) kgs		**450**
Wear Load Index		**62**
Timken OK Load (IP326) kgs (lbs)		**20 (45)**
Oxidation Stability (IP142) 500 hrs @ 99°C Pressure Drop psi		**8 max.**
Operating Temperature Range	°C	**-20°C to +150**

Typical values, not a specification.

PACK SIZES

400 g cartridge, 3 kg, 12.5 kg, 50 kg, 180 kg