GREASES · LITHIUM GREASES

SUPER MOLY 5.

A conventional lithium soap grease on solvent-refined mineral oil with an EP and anti-corrosion package - the most widely used grease chemistry there is, and for most general plant and vehicle greasing points the correct

180 cSt	185 min. °C	2
Viscosity @ 40°C	Dropping point	NLGI grade

APPLICATION

- Extreme shock and boundary load conditions
- Heavy plant pins and bushes
- Slow oscillating joints carrying full load
- Very dusty and abrasive sites

NOT RECOMMENDED

- × **Applications requiring an NSF H1 food-grade grease**
- × **Mixing with greases of a different thickener type without purging the bearing first**
- × **Continuous service above the stated upper temperature limit**

BENEFITS

- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable - will not soften and leak in service

HEALTH & SAFETY

Refer to SDS for proper handling and disposal. Please note that the SDS includes handling, health and disposal information which should be passed on to your employees, and to anyone else who comes in contact with our product. Additional advice can also be obtained from your local representative.

Note: Read and understand all precautions on container labels before using this product.

SAR Lubricants (Squire A. Radcliffe & Sons Ltd)
Gill Bridge Oil Works, Lowlands Road,
Mirfield, WF14 8LU, England

+44 (0)1924 494371
enquiries@sarlubricants.co.uk
sarlubricants.co.uk

Registered in England
05866783
VAT 889171963

GREASES · LITHIUM GREASES · CONTINUED

SUPER MOLY 5.

TYPICAL PROPERTIES

PROPERTY	UNIT	TYPICAL
Appearance Visual		**Smooth Grease**
Colour ASTM D1500		**Grey / Black**
NLGI Classification		**2**
Thickener		**Lithium Soap**
Base Oil		**Mineral Oil**
Base Oil Viscosity @ 40°C (IP 71)	cSt	**180**
Worked Penetration (IP 50)		**265 to 295**
Dropping Point (IP 132)	°C	**185 min.**
Oil Separation (IP 121)	%	**5 max.**
Copper Corrosion (IP 112)		**Pass**
Resistance To Corrosion Emcor (IP 220)		**0 : 0**
Water Washout (ASTM D1264) @ 39°C	%	**3**
Four Ball Weld Load (IP 239) kgs		**450**
Timken OK Load (IP 326) lbs		**50**
Oxidation Stability @ 100°C (IP 142) Pressure Drop After 100 hrs psi		**4**
Molybdenum Disulphide Content	%	**5**
Operating Temperature Range	°C	**-20°C to +140**

Typical values, not a specification.

PACK SIZES

400 g cartridge, 3 kg, 12.5 kg, 50 kg, 180 kg